

SATRA Technology Centre Ltd, Wyndham Way, Telford Way, Kettering Northamptonshire, NN16 8SD, United Kingdom

Tel: +44 (0) 1536 410000 Fax +44 (0) 1536 410626 email: footwear@satra.co.uk



Stanbee Asia Ltd Job reference: FWT0206418/1230/Z Firm:

700/273 Moo 1

Amata Nakorn Industrial Estate Date: 8th August 2012

Samples received:

26th July 2012

Tambol Bankao **Amphur Panthong**

Chonburi 20160

Thailand

Attention of: Chutipa Laoprasertsiri Testing completed: 8th August 2012

TECHNICAL SERVICES REPORT

Subject: Evaluation of stiffener material

Sample reference: Verge 25

Tests requested SATRA TM 1 1992 Thickness of leather and insole materials

The samples were stored in a standard controlled environment of 20 ± 2 °C/65 ± 2 %RH for at least 24

hours prior to testing and testing was carried out in this atmosphere.

SATRA TM 83 2009 (2012) Measurement of the area shape retention and collapsing load of

formed toe puff and stiffener materials

The samples were stored in a standard controlled environment of $20 \pm 2^{\circ}\text{C}/65 \pm 2^{\circ}\text{RH}$ for at least 24 hours after forming. Testing was carried out in a conditioned atmosphere of $23\pm2^{\circ}\text{C}/50\pm2\%\text{RH}$.

Conditions of Issue:

This report may be forwarded to other parties provided they are members of SATRA and that it is not changed in any way. It must not be given to non-members nor published, for example by including it in advertisements, without the prior, written permission of SATRA.

Results given in this report refer only to the samples submitted for analysis and tested by SATRA. Comments are for guidance only.

Tests marked † fall outside the UKAS Accreditation Schedule for SATRA. All interpretations of results of such tests and the comments based upon them are outside the scope of the UKAS accreditation and are based on current SATRA

A satisfactory test report in no way implies that the product tested is approved by SATRA and no warranty is given as to the performance of the product tested. SATRA shall not be liable for any subsequent loss or damage incurred by the customer as a result of information supplied in the report.

Please note uncertainty of measurement has not been applied to the results in this report. SATRA uncertainty of measurement values are available on request.

Report signed by: Kala Tidball-Wykes

Footwear Consultant

Footwear Technology - Testing

On behalf of SATRA Technology Centre Ltd

(Page 1 of 3)

SATRA Technology Centre Ltd. A subsidiary of SATRA. Registered in England No. 3856296



Technical Services Report



RESULTS

Reference: Verge 25
Type: Thermoplastic
Activation conditions: 95°C for 8.5 minutes

Test Method	Property	Result	Hardness categories and related performance levels				2 - /
			Very hard	Hard	Medium	Soft	Category
SATRA TM 1 1992	Thickness (mm)	0.75	-	-	<u>-</u>	-	-
SATRA TM 83 2009 (2012)	Initial collapsing load (N)	54	>130	130-81	80-31	30 or less	Medium
	Resilience (1) (%)	78	Min 25	Min 30	Min 40	Min 50	Satisfactory

O 81				SAT	A		
Properties not re	lated to hardness			A	В	C	Category
SATRA TM 83 2009 (2012)	Moisture resistance (2) (%)		85	Min 80	Min 60	Min 40	A
	Dry area shape retention (%)	Initial	95	Min 85	Min 70	Min 55	A
		After 10 collapses	95	Min 75 ⁽³⁾	Min 60	Min 45	A

Note:

- Resilience is percentage retention of initial collapsing load after ten collapses.
- 2 Moisture resistance is percentage retention of initial dry collapsing load after 1 hour immersion.
- 3 60% minimum is applicable to hard or very hard stiffeners.

COMMENTS

This material falls into the medium hardness category and, as such, the resilience is satisfactory. Overall, the properties not related to hardness meet Performance Level A.

(Page 2 of 3)

This material should be suitable for use in all footwear applications requiring a medium hardness stiffener.

Firm: Stanbee Asia Ltd
Job reference: FWT0206418/1230/Z

Date: 8th August 2012

Signed:





Technical Services Report



TERMS AND CONDITIONS OF BUSINESS

GENERAL

Work done or services undertaken are subject to the terms and conditions detailed below and all other conditions, warranties and representations, expressed or implied are hereby excluded.

PRICES

Prices are based on current material and production costs, exchange rates, duty and freight and are subject to change without notice.

3 DELIVERY ESTIMATES

Delivery estimates are made in good faith and date from receipt of a written order and full information to enable us to proceed. While SATRA or its subsidiaries (hereafter referred to as "SATRA") make every effort to fulfil them, such estimates are subject to unforeseen events and if not maintained, cannot give rise to any claim. Offers "ex stock" are subject to prior sale.

4. CANCELLATION AND RETURNS

Cancellation of orders for goods, services, training or consultancy is only acceptable by prior agreement of SATRA and a charge will normally be made.

5 CLAIMS

Claims for errors, shortages etc should be notified within 10 days of date of receipt. In the event of goods damaged in transit, packing materials should be retained for examination; otherwise no liability can be accepted.

6. PAYMENT TERMS

Payment terms are net 21 days from date of invoice. Failure to comply with the terms of payment may result in delayed delivery of goods and services and a review of the Customer's credit account. Should the customer become subject to an administration order, or becomes bankrupt or goes into liquidation, SATRA has a right to cancel any contract and discontinue any work. SATRA reserves the right to adjust US Dollar and Euro sales price where customer exceeds credit terms and where the exchange rate has moved more than 10% since invoicing.

7. RETENTION OF TITLE

All goods remain the property of SATRA until paid in full. Under no circumstances will a customer's purchase order override our Retention of Title clause. In the case of software, the ownership of the software remains with SATRA. Payment of invoices in full will entitle the customer to use the software under licence until (a) they cease to be a member of SATRA or (b) they cease trading. In both instances, the licence shall then revert to SATRA.

8. GUARANTEE

All goods manufactured by SATRA are guaranteed both as regards material and workmanship. Any part returned carriage paid, within twelve months from date of supply and found defective, will be repaired or replaced at SATRA's option free of charge. SATRA admits no liability for loss, damage or delay consequent on any defect in any goods supplied by SATRA.

9. TEST REPORTS

Results given in test reports refer only to samples submitted for analysis and tested by SATRA. A satisfactory test report in no way implies that the product tested is approved by SATRA and no warranty is given as to the performance of the product tested. SATRA shall not be liable for any subsequent loss or damage incurred by the client as a result of information supplied in a test report.

10. TEST SAMPLES

Unless otherwise agreed in advance, test samples will be disposed of 6 weeks after the date of the final report. If required, samples can be returned at the Customer's expense.

11. RESPONSIBILITY

Every effort is made to ensure accuracy in description, drawings and other information in correspondence, catalogues, etc but no warranty is given in this respect and SATRA shall not be liable for any error therein. SATRA carries out all tests and/or advises only on the basis that the same are carried out, made or given without any responsibility whether for negligence or otherwise. SATRA and its servants or agents will not be liable for any damage or loss direct or indirect of whatsoever kind, whether or not the same results directly or indirectly from negligence on the part of SATRA or its servants or agents.

12. CONFIDENTIALITY

Unless specifically excluded in the terms of an individual contract between SATRA and its Customer, the following shall apply to all reports, advice, drawings, photographs, specifications or data:

- i. The above shall not be disclosed to third parties or used in litigation without the consent of SATRA.
- ii. Where SATRA has given consent to disclosure, the Customer shall draw the attention of the third party to these terms of business and the basis on which SATRA undertakes test, reporting and advising. The Customer shall indemnify SATRA for any failure to do so.
- iii. The above items are submitted to the Customer as confidential documents. Confidentiality shall continue to apply after completion of the business, but shall cease to apply to information or knowledge which may come into the public domain.

13. CONSTRUCTION AND ARBITRATION

The laws of England shall govern all contracts and the parties submit to exclusive jurisdiction of the courts of England, unless otherwise agreed.

Issue Date: 1st October 2009

Firm: Stanbee Asia Ltd
Job reference: FWT0206418/1230/Z

Date: 8th August 2012

(Page 3 of 3)



Signed: