

ZETALUB NEUVO

LUBRICATING AGENT / ANTI-CREASING AGENT

Product Description:

As the pinnacle of our lubricant portfolio, Zetalub NEUVO represents the epitome of efficiency and performance in addressing critical crease formation problems. Engineered to surpass industry standards, it excels in reducing textile-to-textile and metal-to-fabric friction, thereby preventing the formation of permanent crease marks during wet processing. Its advanced formulation facilitates better levelness in fabric ropes and promotes smooth running of heavy GSM fabrics, ensuring impeccable dyeing results and a polished fabric appearance.

With superior characteristics like high efficiency at all temperature and pH levels, excellent yield, and low foaming, Zetalub NEUVO guarantees consistent, high-quality results across all stages of textile wet processing. By optimising fabric run and maintaining liquor stability, it eliminates dye agglomeration, staining, or specking issues, ensuring flawless outcomes with every batch processed.

Key Benefits:

- 1. Smooth Gliding & Soft Handle:** Imparts a smooth gliding effect and an exquisite soft handle to fabric.
- 2. Superior Friction Reduction:** Reduces friction between fibres and between fibres and metal surfaces.
- 3. Shade & Fastness Preservation:** Maintains dye shade and fastness properties without compromise, including polyester fibres dyed with disperse dyes.
- 4. High GSM Fabric Performance:** Highly viscous liquid specially suited for heavy GSM fabrics, promoting better levelness in fabric ropes.
- 5. Broad Compatibility:** Resilient against fluctuations in pH, electrolytes, and water hardness. High efficiency at all temperature and pH levels with low foaming.
- 6. Eliminates Specking & Staining:** Maintains liquor stability, eliminating dye agglomeration, staining, and specking issues.
- 7. Recommended Dosage:** 0.5% to 1.0% (1.0–2.0 GPL), particularly in high-temperature processing scenarios.

Properties:

Chemical Constitution	Aqueous preparation of acrylamide and fatty ester polymer
Ionic Character	Anionic
pH	6 – 8
Specific Gravity at 20°C	1.3 gm/cc
Physical Form	Clear to slightly hazy liquid

Storage Stability	Stable for 1 year at 20°C; sensitive above 50°C and below 0°C
Stability to Alkalis	Very Good
Stability to Acids	Very Good
Stability to Oxidants	Very Good

Applications:

For best effect, Zetalub NEUVO should be added to the treatment bath before the goods are entered. Dilute by pouring onto warm water and stirring before addition. The product is pumpable. Recommended dosage: 1.0–2.0 GPL or 0.5%–1.0% on weight of material.

1. Scouring & Oxidative Bleaching Bath — RFD / RFP Fabrics

Function	Product	Dosage	Parameters & Conditions
Lubricating Agent	ZETALUB NEUVO	0.5%–1.0%	Auxiliary dosing – raise to 60°C – Caustic Soda dosing (2 cycles) – H ₂ O ₂ 50% dosing (2 cycles) – raise to optimum temp & hold (95°C × 45–60 min or 110°C × 20–30 min) – Drain at 80°C
Wetting Agent	Zetawet SWLF CONC	0.4%–0.6%	
Sequestering Agent	Zetaplex SQT CONC	0.3%–0.5%	
Peroxide Stabilizer	Zetastab BR	0.2%–0.3%	
Alkali	Caustic Soda Flakes	1.2%–2.5%	
Oxidative Bleaching Agent	Hydrogen Peroxide 50%	1.5%–3.0%	

2. Scouring & Oxidative Bleaching Bath — Full White (FW) Fabrics

Function	Product	Dosage	Parameters & Conditions
Lubricating Agent	ZETALUB NEUVO	0.5%–1.0%	Auxiliary dosing – raise to 60°C – Caustic Soda (2 cycles) – H ₂ O ₂ 50% (2 cycles) – raise to optimum temp & hold – drain at 80°C – Hot wash at 80°C, add OBA (20 min dosing + 20 min holding) – Drain bath
Wetting Agent	Zetawet SWLF CONC	0.4%–0.6%	
Sequestering Agent	Zetaplex SQT CONC	0.3%–0.5%	
Peroxide Stabilizer	Zetastab BR	1.0%–1.5%	
Alkali	Caustic Soda Flakes	2.0%–3.0%	
Oxidative Bleaching Agent	Hydrogen Peroxide 50%	6.0%–8.0%	
OBA (base)	Zetabright HCE	0.7%–1.0%	
OBA (tint)	Zetabright BB	0.02%–0.1%	

3. Dyeing Bath

Function	Product	Dosage	Parameters & Conditions
Lubricating Agent	ZETALUB NEUVO	0.5%–1.0%	Auxiliary dosing – raise to 60°C – Dye dosing then hold – Salt dosing then hold – Alkali dosing then hold (as per shade depth and recommended process)
pH Buffer cum DBC	Zetalev AB-55	0.3%–0.5%	
Levelling Agent	Zetalev CLD	0.5%–1.0%	

Dyes	Reactive Dyes	R%	
Salt	Glauber's Salt	X%	
Alkali	Soda Ash	Y%	
Alkali	Caustic Soda Flakes	Z%	

Disclaimer: Biochem Technologies retains the right to alter product and technical information. We assure that our products will meet Biochem Technologies' specifications, with our liability limited to product replacement. The information provided in this datasheet serves as a guideline, believed to be accurate. Users are advised to assess recommendations before actual application. Safety Data Sheet (SDS) is available upon request.