

ZETAWASH HPS NEW

HIGH-PERFORMANCE SOAPING AGENT / WASHING AGENT

Product Description:

Zetawash HPS NEW is a concentrated acrylate-based formulation combining surfactants and alcohols into a powerful, low-foaming soaping agent. Specifically engineered for reactive-dyed and printed cellulosic fabrics, it delivers fast, thorough removal of residual unfixed dyes and surface impurities with minimal foam — making it ideal for both open-width and jet dyeing machines.

Its excellent dispersing ability prevents redeposition of removed dyes onto the fabric, while effective complexing action ensures consistent performance even in hard water conditions. Biodegradable and eco-friendly, Zetawash HPS NEW delivers superior soaping results without compromising effluent standards.

Key Benefits:

Superior Detergency: Efficiently removes unfixed reactive dyes and impurities from the fabric surface for bright, clean final shades.

Excellent Dispersing Ability: Keeps removed dyes dispersed in the bath, preventing redeposition and back-staining on the fabric.

Effective Complexing Action: Performs consistently in hard water by complexing calcium and magnesium ions that could otherwise reduce soaping efficiency.

Low-Foaming Formula: Specially designed for foam-sensitive jet and overflow dyeing machines; maintains stable bath conditions throughout the soaping cycle.

Eco-Friendly: Readily biodegradable formulation supports responsible wet processing with minimal environmental impact.

Properties:

Chemical Constitution	Sodium salts of modified polyacrylates
Ionic Character	Anionic
pH of 5% Solution	7 – 8
Specific Gravity at 20°C	1.2 gm/cc
Physical Form	Colourless to pale yellow viscous liquid
Storage Stability	1 year at 20°C
Compatibility	Compatible with non-ionic and anionic chemicals

Applications & Dosage:

Recommended dosage: 0.3% – 1.0% on weight of fabric (owf). Best results achieved at 95°C for 12–15 minutes.

Soaping / After-Wash — Reactive Dyed & Printed Cellulosic Fabrics

Shade Depth	Method	Dosage	Temperature & Time
Light Shades	Single Bath	0.3% – 0.5%	80°C × 12–15 min
Medium Shades	Single Bath	0.5% – 0.8%	95°C × 12–15 min
Turquoise / Dark Shades	Double Bath	0.8% – 1.0%	95°C × 12–15 min (each bath)

Disclaimer: Biochem Technologies retains the right to alter product and technical information. We assure that our products will meet Biochem Technologies' specifications, with our liability limited to product replacement. The information provided in this datasheet serves as a guideline, believed to be accurate. Users are advised to assess recommendations before actual application. Safety Data Sheet (SDS) is available upon request.