

ZETALUB EAC

LUBRICATING AGENT

Product Description:

Zetalub EAC is a very effective lubricating agent designed to combat the challenges of creasing, wrinkling, and chafe marks encountered in textile wet processing. Crafted as an aqueous preparation of anionic acrylamide polymer and fatty ester mixture, it seamlessly integrates into various dyeing shades. By addressing fabric-to-fabric and fabric-to-metal friction, Zetalub EAC forms a thin, uniform protective coating around fibres, effectively minimising the formation of durable creases. Key features include imparting a soft handle to yarn, maintaining dye shade and fastness properties, and compatibility across different bath conditions. With a clear, colourless, highly viscous liquid appearance and an approximate pH of 6.0 to 8.0, Zetalub EAC offers reliability and efficiency in textile processing.

Key Benefits:

- 1. Smooth Gliding & Soft Handle:** Imparts a smooth gliding effect and an exquisite soft handle to yarn during processing.
- 2. Friction Reduction:** Reduces friction between fibres and between fibres and metal surfaces, preventing crease marks.
- 3. Shade & Fastness Preservation:** Maintains dye shade and fastness properties without compromise, including polyester fibres dyed with disperse dyes.
- 4. Broad Bath Compatibility:** Resilient against fluctuations in pH, electrolytes, and water hardness.
- 5. Wide Application Range:** Suitable for usage across all stages of textile wet processing, from pre-treatment to dyeing baths.
- 6. Anionic Nature:** Anionic character makes it suitable for a wide range of dyeing applications.
- 7. Recommended Dosage:** 0.5% to 1.0%, particularly in high-temperature processing scenarios.

Properties:

Chemical Constitution	Aqueous preparation of acrylamide and fatty ester polymer
Ionic Character	Anionic
pH	6 – 8
Specific Gravity at 20°C	1.1 gm/cc
Physical Form	Clear to slightly hazy liquid
Storage Stability	Stable for 1 year at 20°C; sensitive above 50°C and below 0°C
Stability to Alkalis	Very Good
Stability to Acids	Very Good
Stability to Oxidants	Very Good

Applications:

1. Scouring & Oxidative Bleaching Bath — RFD / RFP Fabrics

Function	Product	Dosage	Parameters & Conditions
Lubricating Agent	ZETALUB EAC	0.5%–1.0%	Auxiliary dosing – raise to 60°C – Caustic Soda dosing (2 cycles) – H ₂ O ₂ 50% dosing (2 cycles) – raise to optimum temp & hold (95°C × 45–60 min or 110°C × 20–30 min) – Drain at 80°C
Wetting Agent	Zetawet SWLF CONC	0.4%–0.6%	
Sequestering Agent	Zetaplex SQT CONC	0.3%–0.5%	
Peroxide Stabilizer	Zetastab BR	0.2%–0.3%	
Alkali	Caustic Soda Flakes	1.2%–2.5%	
Oxidative Bleaching Agent	Hydrogen Peroxide 50%	1.5%–3.0%	

2. Scouring & Oxidative Bleaching Bath — Full White (FW) Fabrics

Function	Product	Dosage	Parameters & Conditions
Lubricating Agent	ZETALUB EAC	0.5%–1.0%	Auxiliary dosing – raise to 60°C – Caustic Soda (2 cycles) – H ₂ O ₂ 50% (2 cycles) – raise to optimum temp & hold – drain at 80°C – Hot wash at 80°C, add OBA (20 min dosing + 20 min holding) – Drain bath
Wetting Agent	Zetawet SWLF CONC	0.4%–0.6%	
Sequestering Agent	Zetaplex SQT CONC	0.3%–0.5%	
Peroxide Stabilizer	Zetastab BR	1.0%–1.5%	
Alkali	Caustic Soda Flakes	2.0%–3.0%	
Oxidative Bleaching Agent	Hydrogen Peroxide 50%	6.0%–8.0%	
OBA (base)	Zetabright HCE	0.7%–1.0%	
OBA (tint)	Zetabright BB	0.02%–0.1%	

3. Dyeing Bath

Function	Product	Dosage	Parameters & Conditions
Lubricating Agent	ZETALUB EAC	0.5%–1.0%	Auxiliary dosing – raise to 60°C – Dye dosing then hold – Salt dosing then hold – Alkali dosing then hold (as per shade depth and recommended process)
pH Buffer cum DBC	Zetalev AB-55	0.3%–0.5%	
Levelling Agent	Zetalev CLD	0.5%–1.0%	
Dyes	Reactive Dyes	R%	
Salt	Glauber's Salt	X%	
Alkali	Soda Ash	Y%	
Alkali	Caustic Soda Flakes	Z%	

Disclaimer: Biochem Technologies retains the right to alter product and technical information. We assure that our products will meet Biochem Technologies' specifications, with our liability limited to product replacement. The information provided in this datasheet serves as a guideline, believed to be accurate. Users are advised to assess recommendations before actual application. Safety Data Sheet (SDS) is available upon request.