

ZETAWET SWLF CONC

WETTING & RE-WETTING AGENT

Product Description:

Zetawet SWLF CONC emerges as a breakthrough in textile treatment, offering a revolutionary solution for fabric pre-treatment. This highly efficient re-wetting agent and detergent boasts exceptional qualities, making it an ideal choice for exhaust, semi-continuous, and continuous processing of cellulosic and synthetic fibres. Notably, it enhances fabric hydrophilicity, ensuring optimal absorption for subsequent dyeing and printing processes. Moreover, its shear-stable nature guarantees seamless performance without the risk of separation. This APEO-free formulation prioritises environmental sustainability while delivering outstanding bio-elimination properties. Its pumpable liquid form ensures effortless handling, while its compatibility with alpha-amylase enzymes, oxidative bleaching agents, alkalis, and acids underscores its versatility and reliability in textile treatment.

Key Benefits:

- 1. Enhanced Hydrophilicity:** Facilitates optimal absorption for dyeing and printing, ensuring consistent results and increased reproducibility.
- 2. Powerful Emulsification:** Effectively removes oily, greasy impurities, and soil particles, maintaining fabric cleanliness.
- 3. Versatile Compatibility:** Resistant to oxidative and reductive bleaching agents, stable with alkalis, acids, and enzyme-compatible.
- 4. Efficient Wetting and Re-wetting:** Strong properties enable low dosage usage, reducing storage needs and manual handling efforts.
- 5. Padding Application:** Ideal for heat setting processes, especially for elastane/spandex blends, offering versatility in fibre types.
- 6. Convenient Formulation:** Liquid pumpable design facilitates easy handling and automatic dispensing, suitable for high turbulence machines.

Properties:

Chemical Constitution	Formulated with fatty alcohol ethoxylate based surfactants
Ionic Character	Non-ionic
pH of 1% solution	Approx. 6 to 7
Specific Gravity at 20°C	Approx. 1 gm/cc to 1.5 gm/cc
Physical Form	Liquid
Storage Stability	Stable for 1 year at 20°C; sensitive above 50°C and below 0°C
Stability to Alkalis	Very Good
Stability to Acids	Very Good

Stability to Oxidants	Very Good
------------------------------	-----------

Applications:

1. Pre-heat Setting Bath

Function	Product	Dosage	Process Conditions
Lubricating Agent	ZETALUB EAC	5–10 GPL	Pick up 80%, dwell time 30 seconds, optimum temperature 180°C
Wetting Agent	ZETAWET SWLF CONC	3–5 GPL	Pick up 80%, dwell time 30 seconds, optimum temperature 180°C

2. De-mineralizing Bath

Function	Product	Dosage	Process Conditions
Lubricating Agent	ZETALUB EAC	0.5%–1.0%	Auxiliary dosing – raise temperature to 70°C–80°C and hold for 20 to 30 minutes
Wetting Agent	ZETAWET SWLF CONC	0.3%–0.5%	
Sequestering Agent	ZETAPLEX SQT CONC	0.3%–0.5%	

3. Scouring & Oxidative Bleaching Bath — RFD / RFP Fabrics

Function	Product	Dosage	Process Conditions
Lubricating Agent	ZETALUB EAC	0.5%–1.0%	Auxiliary dosing – raise to 60°C – Caustic Soda dosing (2 cycles) – H ₂ O ₂ 50% dosing (2 cycles) – raise to optimum temp & hold (95°C × 45–60 min or 110°C × 20–30 min) – Drain at 80°C
Wetting Agent	ZETAWET SWLF CONC	0.4%–0.6%	
Sequestering Agent	ZETAPLEX SQT CONC	0.3%–0.5%	
Peroxide Stabilizer	ZETASTAB BR	0.2%–0.3%	
Alkali	Caustic Soda Flakes	1.2%–2.5%	
Oxidative Bleaching Agent	Hydrogen Peroxide 50%	1.5%–3.0%	

4. Scouring & Oxidative Bleaching Bath — Full White (FW) Fabrics

Function	Product	Dosage	Process Conditions
Lubricating Agent	ZETALUB EAC	0.5%–1.0%	Auxiliary dosing – raise to 60°C – Caustic Soda (2 cycles) – H ₂ O ₂ 50% (2 cycles) – raise to optimum temp & hold – drain at 80°C – Hot wash at 80°C, add OBA (20 min dosing + 20 min holding) – Drain bath
Wetting Agent	ZETAWET SWLF CONC	0.4%–0.6%	
Sequestering Agent	ZETAPLEX SQT CONC	0.3%–0.5%	
Peroxide Stabilizer	ZETASTAB BR	1.0%–1.5%	
Alkali	Caustic Soda Flakes	2.0%–3.0%	
Oxidative Bleaching Agent	Hydrogen Peroxide 50%	6.0%–8.0%	
OBA (Base)	ZETABRIGHT HCF	0.7%–1.0%	

OBA (Tint)	ZETABRIGHT BB	0.02%– 0.1%	
------------	----------------------	----------------	--

Disclaimer: Biochem Technologies retains the right to alter product and technical information. We assure that our products will meet Biochem Technologies' specifications, with our liability limited to product replacement. The information provided in this datasheet serves as a guideline, believed to be accurate. Users are advised to assess recommendations before actual application. Safety Data Sheet (SDS) is available upon request.