

Indrayani Corrupack Pvt. Ltd. - QC Laboratory

Test Report No. ICP/QC/2026/0917 | Date: 22-09-2026 | Sample: 5-ply RSC 375x285x300 (Classic Lager 650x12)

Parameter	Specification	Result	Status
Box Compression (BCT), kgf	>= 450	512	PASS
Bursting strength, kg/cm2	>= 11.0	12.4	PASS
Edge Crush (ECT), kN/m	>= 6.5	7.1	PASS
Moisture content, %	7 - 9	7.8	PASS
Board GSM (total)	>= 690	702	PASS

Tested in-house on Universal Box Compression Tester (Cap. 2000 kgf), calibrated 04-2026. Conditioning: 27 C / 65% RH for 24 h.

Checked by: QC Executive Approved by: QA Manager