

Research Article

Gas-Phase Photodegradation of Decane and Methanol on TiO₂: Dynamic Surface Chemistry Characterized by Diffuse Reflectance FTIR

William Balcerski, Su Young Ryu, and Michael R. Hoffmann

W. M. Keck Laboratories, California Institute of Technology, Pasadena, CA 91125, USA

Correspondence should be addressed to Michael R. Hoffmann, mrh@caltech.edu

Received 24 July 2007; Accepted 4 January 2008

Recommended by Russell Howe

Diffuse reflectance infrared Fourier transform spectroscopy (DRIFTS) was used to study illuminated TiO₂ surfaces under both vacuum conditions, and in the presence of organic molecules (decane and methanol). In the presence of hole scavengers, electrons are trapped at Ti(III)–OH sites, and free electrons are generated. These free electrons are seen to decay by exposure either to oxygen or to heat; in the case of heating, reinjection of holes into the lattice by loss of sorbed hole scavenger leads to a decrease in Ti(III)–OH centers. Decane adsorption experiments lend support to the theory that removal of surficial hydrocarbon contaminants is responsible for superhydrophilic TiO₂ surfaces. Oxidation of decane led to a mixture of surface-bound organics, while oxidation of methanol leads to the formation of surface-bound formic acid.

Copyright © 2008 William Balcerski et al. This is an open access article distributed under the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

1. INTRODUCTION

TiO₂ is of great interest in the field of heterogeneous photo-oxidation catalysis, especially in the area of environmental cleanup. TiO₂ has the advantage of being relatively cheap, nontoxic, and stable, all of which make it attractive for remediation of environmental organic pollutants [1]. Studies on the surface chemistry of TiO₂ help to answer important questions such as the active species for photo-oxidation, the fate of charge carriers, and the mechanism for transfer of charge to species bound to the surface [2]. Previously, we used FTIR (DRIFT) spectroscopy to monitor surface species, surface electron, and hole traps on TiO₂ powders [3–5]; and to attribute broad spectral features to free conduction band electrons [3].

Representative hydrocarbon species (e.g., decane and methanol) were chosen for further investigation of hydrocarbon adsorption and photo-oxidation on the surface of illuminated TiO₂. The primary objective of these studies is to gain insight into the gas-phase and surface-bound photo-oxidation products.

2. EXPERIMENTAL PROCEDURES

TiO₂ (Degussa P25; 25% rutile, and 75% anatase), decane (99.9%, Aldrich), methanol (99.9%, Aldrich), methanol-d₄ (CD₃OD, 99% isotopic purity, Aldrich), and formic acid (88%, Aldrich) were used as received. Oxygen gas (99.9%) was passed through a water trap before use in FTIR experiments.

DRIFT spectra were acquired using a Bio-Rad FTS-45 spectrometer with a liquid N₂-cooled MCT detector. Spectra were collected at 8 cm^{−1} resolution using a Spectra-Tech Collector diffuse-reflectance accessory. The solid samples were held in the sample cup of a Spectra-Tech high-temperature environmental chamber (HTEC) that could be resistively heated to 1000 K (±1 K), and the chamber evacuated to 10 μTorr. A gas manifold connected to the sample chamber allowed for pure gas samples (e.g., O₂) or organic vapors (e.g., decane and methanol vapor) to be introduced and removed as needed. The organic samples were attached to the system via a glass bulb, and these samples underwent several freeze-thaw cycles to remove dissolved gases. UV radiation from a 1 kW Oriel Xe lamp was

focused into the HTEC chamber through a moveable mirror and lens system that allowed for photolysis experiments to be conducted without breaking system purge.



3. RESULTS AND DISCUSSION

3.1. Hole and electron trapping on TiO₂ surfaces

One of the primary results of our previous work [3] was an observed rise in the DRIFT spectrum baseline when TiO₂ is irradiated in vacuo, which was caused by the generation of free electrons. The baseline gradually decayed over the course of several hours, leading to a stable trapped electron in a Ti(III)–OH group at 3714 cm⁻¹. We now believe that the impurities seen in previously C–H bands found at 2927 and 2859 cm⁻¹ are indicative of surface-bound species responsible for hole trapping. To test this hypothesis, a small amount of methanol vapor was added to the system, followed by the normal vacuum pumping on the system to remove as much methanol as possible. Experiments conducted in the weeks following the methanol exposure led to a background C–H signal, which had been observed previously, but more importantly led to the expected baseline increase and Ti(III)–OH formation upon irradiation.

Figure 1 shows the DRIFT spectra for TiO₂ powder in vacuo under different conditions. In the untreated powder, bridging hydroxyl groups are seen at 3414 cm⁻¹ and Ti(IV)–OH stretches are seen around 3645 cm⁻¹. There is also a broad adsorption between 3000 and 3600 cm⁻¹ due to surface-bound water molecules. Upon heating to 200°C, surface water is lost, allowing the bridging hydroxyl groups to be more clearly seen in the spectrum. Furthermore, the Ti(IV)–OH peak becomes more clearly defined as a single peak at around 3645 cm⁻¹. Upon irradiation, bridging hydroxyl groups are completely lost, the Ti(IV)–OH peak is reduced in intensity, and a new peak at 3714 cm⁻¹ is seen, which corresponds to trapped electrons in Ti(III)–OH groups. These results are consistent with our earlier work [3].

Alcohols are known to chemisorb to TiO₂ surfaces, [6–8] thus the expected surface species in the case of methanol vapor would be Ti–OCH₃. This adsorbed species provides a viable hole trap, by either direction hole transfer or through a chemical reaction to form formate:



In either case, free electrons are present in the conduction band, leading to the aforementioned rise in baseline and a change in the color of the powder from white to blue as a result of Ti(III) atoms.

In the reaction described by (2), the injection of an electron into the lattice would create a current-doubling effect, which is well known for the case of organic photo-oxidation by TiO₂ [9–12]. Thus, some of the free electrons observed after photolysis may be a result of such an effect.




FIGURE 1: DRIFT spectra showing the effect of heating (to 200°C) and UV irradiation on P25 TiO₂ powder in vacuo in presence of hole scavenger contaminants.

The electron-generating reaction would have to proceed under anoxic conditions, and would likely be initiated by the loss of a proton. Figure 2 shows the effect of sequential heat treatment (523 K) and UV treatment in vacuo on a TiO₂ surface which had been exposed to methanol vapor. The heat treatment effectively removed all the water and some of the methanol, but the UV treatment led to an additional decrease in C–H intensity, as seen in the difference spectrum. Thus, there is a photochemical methanol loss pathway, even in vacuo, which supports the mechanism postulated in (2).

When the system was under a constant 1.0 atm N₂ and the fresh TiO₂ sample was not exposed to a vacuum, the baseline did not increase upon irradiation. This was most likely due to the inability of methanol molecules to desorb or detach from the walls and diffuse to the powder surface. The background methanol persisted in the system on the order of weeks and months, unless vigorous cleaning methods (frequent purging of the gas manifold with N₂ or O₂) were taken. Given the well-known affinity for TiO₂ to sorb hydrocarbons, [2] it is not unlikely that a small amount of impurity in the system could transfer from the walls to the TiO₂ powder, especially given that the amount of manifold surface area is several thousand times larger than the surface area of the powder in the sample compartment. Indeed, work with other organic samples such as methoxychlor and lindane led to a several-month contamination of the experimental setup, as new TiO₂ samples would continually turn orange from picking up these long-lived residual pesticide molecules. The problem of reproducing clean TiO₂ systems is not unique, as seen by the debate over the cause of UV-induced hydrophilicity on TiO₂ crystal surfaces, which has only recently been shown to be a result of the removal of surface hydrocarbon contaminants [13].






FIGURE 2: DRIFT spectra of TiO_2 powder heated and irradiated in vacuo after absorbing methanol vapor, and the difference spectrum showing the effect of irradiation on the surface which had already undergone heat treatment.

Given this new information, some of the previous conclusions need to be refined, especially in regards to postirradiation baseline relaxation. As reported earlier, both thermal treatment at 423 K as well as exposure to O_2 at 300 K led to a rapid relaxation of the baseline, as opposed to slow relaxation if the system was left alone [3]. These experiments were repeated, and in the case of relaxation by O_2 , the resulting peak at 3714 cm^{-1} is much larger, as seen in Figure 3. This can be explained as follows. The slow relaxation is a result of charge recombination, and has been studied previously [5]. The rapid relaxation from exposure to oxygen is due to electron scavenging by oxygen, as it is a well-known electron acceptor:



The relaxation from thermal treatment is due to injection of trapped holes back into TiO_2 upon methanol desorption, which begins to occur at 400 K under vacuum conditions [6]. Not all methanol will be removed by this pathway though, as even at 475 K, the TiO_2 surfaces can contain alkoxides [7]:



The injected holes can then recombine with bulk electrons, that is, annihilation, but they can also combine with the trapped electrons in the form of $\text{Ti(III)}-\text{OH}$ groups:



Thus, since the O_2 treatment does not remove the surface methanol, there are both less holes injected into the lattice




FIGURE 3: DRIFT spectra of TiO_2 powder irradiated in the presence of methanol vapor, followed by either thermal or O_2 treatment.

and more hole traps, leading to an increased intensity of the $\text{Ti(III)}-\text{OH}$ peak at 3714 cm^{-1} .

It was observed that the $\text{Ti(III)}-\text{OH}$ groups could be removed by illumination under O_2 , but only after being partially rehydrated under H_2O vapor [3]. This result is consistent with loss of chemisorbed methanol (and thus hole injection) upon rehydration as reported elsewhere [14]. Thus, the previous explanation for this observed behavior, which stated that defects were stabilized by surface reconstruction involving OH groups, needs to include the possibility of the methanol loss pathway. Likewise, the role of lattice O-vacancies in the mechanism of hole-trapping, while not completely disproved, cannot account for all the experimental results.

3.2. Decane adsorption and degradation on TiO_2 surfaces

A potential practical application of TiO_2 is in the remediation of oil spills by coated glass beads [15]. In order to gain insight into alkane photocatalysis by TiO_2 , decane was chosen as a sample hydrocarbon for a series of photoexperiments. The primary reasons for choosing decane were its simplicity (straight-chain alkane) and its vapor pressure (~ 1 Torr at room temperature, ideal for dosing samples via the gas manifold).

Hydrocarbon oxidation on TiO_2 has been studied extensively. Several decades ago, Djeghri et al. [16] used a flow-through reactor to study the UV-illuminated photocatalysis of alkanes (methane through octane) in the vapor phase. They found that the alkanes are oxidized to ketones, aldehydes, and CO_2 , and that steady-state product concentrations are reached within minutes [16]. More recently, Minabe et al. have studied the photo-oxidation of long-chain organics on TiO_2 thin film, and observed that only CO_2 and H_2O were produced in the gas phase [17]. They suggest that the initial reactants as well as all intermediates were continuously


attached to the TiO₂ surface; however, they offered no insight into how the organics were oriented on the surface, or on the nature of the intermediates. The authors prepared their samples by melting their organics, then spreading the liquid on the TiO₂ thin-film surface, whereas Teichner et al. introduced the organics in the gas phase over nonporous anatase particles. These differences in catalyst and sample introduction, as well as the long exposure time of Fujishima's physisorbed organics compared to the gas-phase organics in Teichner's experimental setup, likely account for Fujishima and coworkers inability to detect any intermediates.

In the first set of experiments, decane vapor was introduced to TiO₂ surfaces that had been pretreated by UV irradiation in vacuo, and surface coverage was compared to the nonirradiated case. It was known at the time that UV treatment makes TiO₂ surfaces superhydrophilic, and we believed that the UV pretreatment would affect the ability for decane to adsorb to the surface. Decane dosing was performed by opening a glass bulb containing decane, which was attached to a section of the gas manifold, for 2 minutes. The bulb was then closed, and that segment of the manifold was then opened to the sample chamber. The decane vapor was allowed to equilibrate with the sample for 10 minutes, and an initial FTIR spectrum was taken. The system was then opened to vacuum, and a series of scans were taken as the system was pumping down. Figure 4 shows the results of these experiments. Although initial decane concentrations were different ($t = 0$, while sample was sitting nonevacuated under decane vapor), after exposure to vacuum, both samples had near identical decane desorption profiles. Nearly all decane was lost from both the nonirradiated and irradiated surfaces during vacuum treatment, indicating that the decane was weakly bound, that is, physically adsorbed to the surface. These experiments provide support for the theory that hydrocarbon contaminants [13], not UV-induced defects [18] or UV-induced rupture of Ti–OH bonds [19], are responsible for surface hydrophilicity. The experiments suggest that the UV pretreated surface, once exposed to decane vapor, lost its super-hydrophilic character and behaved similarly to the nontreated surface in regards to the amount of decane adsorbed on the surface.


In the next series of experiments, the oxidation of decane on TiO₂ was studied. After dosing the sample with decane, the system was immediately exposed to 1 atm O₂, so as to prevent the decane from desorbing from the surface. The sample was then irradiated for 5–10-minute intervals, at which point the lamp was turned off and a spectrum was recorded. Total time spent undergoing irradiation was 1 hour. Figure 5 shows the resulting spectra over 2000–4000 cm^{−1}. As expected, both water (broad adsorption between 3000 and 3600 cm^{−1}) and CO₂ (2320 cm^{−1}) are produced, with a loss in hydrocarbon intensity (C–H stretches between 2800 and 3000 cm^{−1}). To further probe the reaction products, a series of difference spectra are used, as shown in Figure 6. After one minute of irradiation, water (but not CO₂) is seen to form, and peaks are seen in the 1350–1750 cm^{−1} region, which are indicative of C–O bonds. The initial formation of water indicates that hydrogen abstraction is the first step in decane oxidation [20]. As the oxidation

progressed, these C–O stretches eventually gave way to the C=O stretch at 1737 cm^{−1}, simultaneously accompanied by the formation of CO₂, as seen in the difference spectrum between 5 and 20 minutes of irradiation. At the end of the photoreaction, the system was exposed to vacuum, and some, but not all, of the reaction products were removed. Further oxidation in vacuo was used to remove the more strongly bound surface species.

Two possible mechanisms for the reaction are as follows. The active species for oxidation could be a surface-bound hydroxyl radical, which abstracts a hydrogen atom from a surface decane molecule, forming an alkyl radical. The alkyl radical could then react in any number of ways, such as attachment to a Ti–O–Ti group to form an alkoxy species, which would then undergo further oxidation to ketones and eventually CO₂:




Another possible mechanism involves superoxide formation, which leads to a free-radical-chain mechanism as outlined below:



On the basis of the FTIR data alone, neither mechanism can be proved nor disproved, although ketones are clearly an intermediate product. The spectra are especially complex between 1300 and 1700 cm^{−1}, likely due to peak overlap from ethers and ketones of various carbon-chain lengths, making absolute product assignment impossible.

3.3. Methanol adsorption and degradation on TiO₂ surfaces

Methanol was chosen as the next molecule to examine, due to the simplicity of possible photo-oxidation products (no long-chain carbon products) as well as the ability for methanol to chemisorb to the TiO₂ surface [6–8]. Samples were dosed with methanol vapor in a similar manner to decane, but unlike decane, the methanol species remained behind on the surface after complete evacuation of the sample chamber. Figure 7 shows the difference spectra before and after methanol and d₄-methanol adsorption onto the TiO₂ sample. Both samples show a loss of Ti–OH groups, as methanol molecules can displace surface OH groups during chemisorption as seen below:






FIGURE 4: Typical time series of decane desorption on TiO_2 in vacuo (a), and hydrocarbon peak intensity of decane absorbed to UV versus non-UV-treated TiO_2 (b).





FIGURE 5: DRIFT spectra taken during the course of 1-hour UV oxidation of decane on TiO_2 under 1 atm O_2 . Arrows indicate increase in surface-bound water and CO_2 vapor, and a decrease in hydrocarbon intensity.

For d4-methanol, CD_3 stretches are seen at 2072 and 2226 cm^{-1} , and the methanol OD stretch is seen as a broad peak centered at 2470 cm^{-1} . An OD stretch corresponding to Ti-OD is also seen at 2716 cm^{-1} , indicating scrambling of surface OH groups with methanol [3].

Figure 8 shows a series of difference spectra taken during the course of methanol oxidation under 1 atm O_2 . Within the first 5 minutes, both water and CO_2 are seen to form. There is a decrease in CH_3 stretches at 2916 and 2816 cm^{-1} , and a new peak assigned to a CH_2 stretch at 2862 cm^{-1} . There are also 2 new peaks at 1583 and 1361 cm^{-1} , which are assigned to the asymmetrical and symmetrical stretching bands of

carboxylate anion, respectively [21]. These products were also seen in the case of d4-methanol (Figure 9). To further validate that formic acid is indeed the intermediate species identified in the difference spectra, a drop of formic acid was placed directly on a fresh TiO_2 surface, and the resulting DRIFT spectrum is shown in Figure 10. Carboxylate peaks are observed in the same location as the peaks from the difference spectra, confirming the assignment.

After 15 more minutes of irradiation, there is a decrease in the carboxylate species, and an increase in CO_2 occurs. Upon evacuation, surface water and CO_2 are lost, but an increase is seen in carboxylate, indicating that it is a surface-bound species which now has increased signal strength, possibly due to readsorption of gas-phase carboxylic acid molecules once surface water was removed. A possible mechanism for the reaction, which is consistent with the spectral evidence presented above, is as follows. The initiating step is hydrogen abstraction, either by direct hole transfer or superoxide. A hydroperoxy species is formed, which rearranges to a surface-bound formic acid, which can then be released as CO_2 :






FIGURE 6: Time series DRIFT difference spectra following course of decane oxidation.

4. CONCLUSIONS

Only when TiO_2 is irradiated in the presence of a hole scavenger, even at very low surficial concentrations, electrons are trapped at Ti(III)-OH sites, and free electrons are also

generated. Upon heating, the hole scavengers are desorbed and with the consequent reinjection of previously trapped holes. This leads to a decrease in detectable Ti(III)-OH centers. Decane adsorption experiments lend support to the theory that removal of hydrocarbon contaminants is



FIGURE 7: DRIFT spectra showing surface coverage of methanol and methanol-d₄.

FIGURE 8: Time series DRIFT difference spectra following course of methanol oxidation.




FIGURE 9: Initial products of d4-methanol oxidation.




FIGURE 10: Formic acid absorbed on TiO_2 .

responsible for the appearance of super-hydrophilic TiO_2 surfaces. While the oxidation of decane did not lead to any definitive product assignments, the oxidation of methanol led to identification of surface-bound formic acid.

ACKNOWLEDGMENTS

We are grateful to the Hydrogen Energy Research & Development Center and 21st Century Frontier Research and Development Program of the Ministry of Science and Technology of Korea for research support. Supplementary support was generously provided by the Northrop-Grumman Corporation. Special issue dedicated to the second international conference on semiconductor photochemistry.

REFERENCES

- [1] M. R. Hoffmann, S. T. Martin, W. Choi, and D. W. Bahnemann, "Environmental applications of semiconductor photocatalysis," *Chemical Reviews*, vol. 95, no. 1, pp. 69–96, 1995.
- [2] T. L. Thompson and J. T. Yates Jr., "Surface science studies of the photoactivation of TiO_2 —new photochemical processes," *Chemical Reviews*, vol. 106, no. 10, pp. 4428–4453, 2006.
- [3] S. H. Szczepankiewicz, A. J. Colussi, and M. R. Hoffmann, "Infrared spectra of photoinduced species on hydroxylated titania surfaces," *Journal of Physical Chemistry B*, vol. 104, no. 42, pp. 9842–9850, 2000.
- [4] S. H. Szczepankiewicz, J. A. Moss, and M. R. Hoffmann, "Electron traps and the stark effect on hydroxylated titania photocatalysts," *Journal of Physical Chemistry B*, vol. 106, no. 31, pp. 7654–7658, 2002.
- [5] S. H. Szczepankiewicz, J. A. Moss, and M. R. Hoffmann, "Slow surface charge trapping kinetics on irradiated TiO_2 ," *Journal of Physical Chemistry B*, vol. 106, no. 11, pp. 2922–2927, 2002.
- [6] V. S. Lusvardi, M. A. Barteau, and W. E. Farneth, "The effects of bulk titania crystal-structure on the adsorption and reaction of aliphatic-alcohols," *Journal of Catalysis*, vol. 153, no. 1, pp. 41–53, 1995.
- [7] G. A. M. Hussein, N. Sheppard, M. I. Zaki, and R. B. Fahim, "Infrared spectroscopic studies of the reactions of alcohols over group IVB metal oxide catalysts—part 3: ethanol over TiO_2 , ZrO_2 and HfO_2 , and general conclusions from parts 1 to 3," *Journal of the Chemical Society, Faraday Transactions*, vol. 87, no. 16, pp. 2661–2668, 1991.
- [8] E. Farfan-Arribas and R. J. Madix, "Role of defects in the adsorption of aliphatic alcohols on the $\text{TiO}_2(110)$ surface," *Journal of Physical Chemistry B*, vol. 106, no. 41, pp. 10680–10692, 2002.
- [9] S. R. Morrison and T. Freund, "Chemical role of holes and electrons in ZnO photocatalysis," *Journal of Chemical Physics*, vol. 47, no. 4, pp. 1543–1551, 1967.
- [10] M. Miyake, H. Yoneyama, and H. Tamura, "Two step oxidation reactions of alcohols on an illuminated rutile electrode," *Chemistry Letters*, vol. 5, no. 6, pp. 635–640, 1976.
- [11] B. Kraeutler and A. J. Bard, "Heterogeneous photocatalytic decomposition of saturated carboxylic acids on TiO_2 powder. Decarboxylative route to alkanes," *Journal of the American Chemical Society*, vol. 100, no. 19, pp. 5985–5992, 1978.
- [12] T. Ohno, S. Izumi, K. Fujihara, Y. Masaki, and M. Matsumura, "Vanishing of current-doubling effect in photooxidation of 2-propanol on TiO_2 in solutions containing Fe(III) ions," *Journal of Physical Chemistry B*, vol. 104, no. 29, pp. 6801–6803, 2000.
- [13] T. Zubko, D. Stahl, T. L. Thompson, D. Panayotov, O. Diwald, and J. T. Yates Jr., "Ultraviolet light-induced hydrophilicity effect on $\text{TiO}_2(110)(1 \times 1)$. Dominant role of the photooxidation of adsorbed hydrocarbons causing wetting by water droplets," *Journal of Physical Chemistry B*, vol. 109, no. 32, pp. 15454–15462, 2005.
- [14] A. Y. Nosaka, T. Fujiwara, H. Yagi, H. Akutsu, and Y. Nosaka, "Photocatalytic reaction sites at the TiO_2 surface as studied by solid-state ^1H NMR spectroscopy," *Langmuir*, vol. 19, no. 6, pp. 1935–1937, 2003.
- [15] I. Rosenberg, J. R. Brock, and A. Heller, "Collection optics of TiO_2 photocatalyst on hollow glass microbeads floating on oil slicks," *Journal of Physical Chemistry*, vol. 96, no. 8, pp. 3423–3428, 1992.

- [16] N. Djeghri, M. Formenti, F. Juillet, and S. J. Teichner, "Photointeraction on the surface of titanium dioxide between oxygen and alkanes," *Faraday Discussions of the Chemical Society*, vol. 58, pp. 185–193, 1974.
- [17] T. Minabe, D. A. Tryk, P. Sawunyama, Y. Kikuchi, K. Hashimoto, and A. Fujishima, "TiO₂-mediated photodegradation of liquid and solid organic compounds," *Journal of Photochemistry and Photobiology A*, vol. 137, no. 1, pp. 53–62, 2000.
- [18] R. Wang, K. Hashimoto, A. Fujishima, et al., "Light-induced amphiphilic surfaces," *Nature*, vol. 388, no. 6641, pp. 431–432, 1997.
- [19] N. Sakai, A. Fujishima, T. Watanabe, and K. Hashimoto, "Quantitative evaluation of the photoinduced hydrophilic conversion properties of TiO₂ thin film surfaces by the reciprocal of contact angle," *Journal of Physical Chemistry B*, vol. 107, no. 4, pp. 1028–1035, 2003.
- [20] R. Nakamura and S. Sato, "Oxygen species active for photooxidation of *n*-decane over TiO₂ surfaces," *Journal of Physical Chemistry B*, vol. 106, no. 23, pp. 5893–5896, 2002.
- [21] R. Silverstein and F. Webster, *Spectrometric Identification of Organic Compounds*, John Wiley & Sons, New York, NY, USA, 6th edition, 1998.