SHREE GANESH CORRUGATORS - QC LABORATORY

Test Report No. SGC/QC/0926/114 Date: 24-09-2026
Sample: 3 Ply RSC 380x280x220, 150/120/150 GSM, BF 18

Parameter	Spec	Result
Bursting strength (kg/cm2)	>= 5.0	5.6
BCT (kgf)	>= 180	212
ECT (kN/m)	>= 4.2	4.7
Moisture (%)	<= 9	7.8

Instrument calibration valid till 31-Mar-2027. Tested by: R. Saini (QC In-charge)