

## SPECIFICATION SHEET

# 600NE NON-WOVEN GEOTEXTILE

600NE is manufactured using polypropylene fibers that are formed into a dimensionally stable network, which allows the fibers to maintain their relative position. 600NE resists ultraviolet deterioration, rotting, and biological degradation and is inert to commonly encountered soil chemicals.

PROPERTY	TEST METHOD	MARV ENGLISH	MARV METRIC
Weight	ASTM D5261	6.0 oz/yd <sup>2</sup>	204 g/m <sup>2</sup>
Thickness	ASTM D5199	85 mils	2.16 mm
Tensile Strength (Grab)	ASTM D4632	160 x 160 lbs	711.7 x 711.7 N
Elongation (Grab)	ASTM D4632	50% x 50%	50% x 50%
Trapezoidal Tear Strength	ASTM D4533	65 x 65 lbs	289 x 289 N
CBR Puncture	ASTM D6241	450 lbs	2,001.7 N
UV Resistance (500 hrs)	ASTM D4355	70%	70%
Apparent Opening Size*	ASTM D4751	70 US Std. Sieve	0.212 mm
Permittivity	ASTM D4491	1.63 sec <sup>-1</sup>	1.63 sec <sup>-1</sup>
Permeability	ASTM D4491	.30 cm/sec	.30 cm/sec
Water Flow Rate	ASTM D4491	125 gpm/ft <sup>2</sup>	5,080 lpm/m <sup>2</sup>

\*Maximum Average Roll Value

PROPERTY	TEST METHOD	TYPICAL ENGLISH	TYPICAL METRIC
Roll Dimensions	Measured	15 ft x 300 ft	4.6 x 91.5 m
Roll Area	Measured	500 yd <sup>2</sup>	418 m <sup>2</sup>

The information provided is for reference purposes only and is not intended as a warranty or guarantee whether implied or inferred. This document should not be construed as engineering advice. Always consult the project engineer for project specific requirements. The property values listed above are subject to change without notice. BW Geotextiles assumes no liability in connection with the use of this information and product.

1239 Notre Dame Drive, Box 178  
Petersburg, ON N0B 2H0  
Phone: (519)778-1953 Toll Free: 1-844-778-1953  
[www.bwgeotextiles.com](http://www.bwgeotextiles.com)

02/11/2020