

SPECIFICATION SHEET

800N NON-WOVEN GEOTEXTILE

800N is manufactured using polypropylene fibers that are formed into a dimensionally stable network, which allows the fibers to maintain their relative position. 800N resists ultraviolet deterioration, rotting, and biological degradation and is inert to commonly encountered soil chemicals.

PROPERTY	TEST METHOD	MARV ENGLISH	MARV METRIC
Tensile Strength (Grab)	ASTM D4632	205 x 205 lbs	912 x 912 N
Elongation (Grab)	ASTM D4632	50% x 50%	50% x 50%
Trapezoidal Tear Strength	ASTM D4533	80 x 80 lbs	356 x 356 N
CBR Puncture	ASTM D6241	525 lbs	2,336 N
UV Resistance (500 hrs)	ASTM D4355	70%	70%
Apparent Opening Size*	ASTM D4751	80 US Std. Sieve	0.18 mm
Filtration Opening Size	CAN/CGSB-148.1 N10-94		0.064mm
Permittivity	ASTM D4491	1.3 sec ⁻¹	1.3 sec ⁻¹
Water Flow Rate	ASTM D4491	90 gpm/ft ²	3,667 lpm/m ²

*Maximum Average Roll Value

PROPERTY	TEST METHOD	TYPICAL ENGLISH	TYPICAL METRIC
Roll Dimensions	Measured	12.5 ft x 360 ft	3.81 x 109.8 m
		15 ft x 300 ft	4.6 x 91.5 m
Roll Area	Measured	500 yd ²	418 m ²

The information provided is for reference purposes only and is not intended as a warranty or guarantee whether implied or inferred. This document should not be construed as engineering advice. Always consult the project engineer for project specific requirements. The property values listed above are subject to change without notice. BW Geotextiles assumes no liability in connection with the use of this information and product.

1239 Notre Dame Drive, Box 178
Petersburg, ON N0B 2H0
Phone: (519)778-1953 Toll Free: 1-844-778-1953
www.bwgeotextiles.com

02/11/2020