

SPECIFICATION SHEET

MIRAGRID_® 2XT GEOGRID

Miragrid® 2XT biaxial geogrid is composed of high molecular weight, high tenacity polyester multifilament yarns are woven in tension and finished with a PVC coating. Miragrid® 2XT biaxial geogrid is inert to biological degradation and resistant to naturally encountered chemicals, alkalis, and acids.

Miragrid® 2XT geogrid is used as soil reinforcement in MSE structures such as; segmental retaining walls, precast modular block walls, wire faced walls, geosynthetic wrapped faced walls and steepened slopes. Miragrid® 2XT is also used in MSE stabilized platforms for voids bridging, embankments on soft soils, landfill veneer stability, reducing differential settlement and for foundation seismic stability.

Machanical Proportios	Toot Mothod	Test Method Unit	Value	
Mechanical Properties	rest Method		MD	CD
Tensile Strength @ Ultimate (MARV¹)	ASTM D6637 (Method B)	lbs/ft (kN/m)	2000 (29.2	2000 (29.2)
Creep Rupture Strength ²	ASTM D5262/D6992	lbs/ft (kN/m)	1379 (20.1)	
Long Term Design Strength ³		lbs/ft (kN/m)	1194	(17.4)

¹ Minimum Average Roll Values (MARV) shown above are based on QC Testing per a defined lot not to exceed 12 months. Testing Frequency follows ASTM D4354, Table 1.

 $^{^3}$ Long Term Design Strength for sand, silt, clay. RF_{CR} = 1.45; RF_{ID} = 1.05; RF_D = 1.1 (Installation damage reduction factor for other soils available upon request)

Physical Properties	Unit	Roll Characteristic
Mass/Unit Area (ASTM D5261)	oz/yd² (g/m²)	7.1 (241)
Roll Dimensions (width x length)	ft (m)	4 x 50 (1.2 x 15)
		6 x 150 (1.8 x 46)
		12 x 150 (3.6 x 46)
Roll Area	yd² (m²)	22 (18)
		100 (84)
		200 (167)
Estimated Roll Weight	lbs (kg)	25 (11)
		50 (23)
		109 (49)

The information provided is for reference purposes only and is not intended as a warranty or guarantee whether implied or inferred. This document should not be construed as engineering advice. Always consult the project engineer for project specific requirements. The property values listed above are subject to change without notice. BW Geotextiles assumes no liability in connection with the use of this information and product.

1239 Notre Dame Drive, Box 178
Petersburg, ON NOB 2H0
Phone: (519)778-1953 Toll Free: 1-844-778-1953
www.bwgeotextiles.com

² 75-year design life based on NTPEP Report REGEO-2011-01-001 and REGEO-2015-01-002.