
Annex 2 — Technical Evidence

Purpose: Consolidates all measured test data, laboratory analyses, emission certifications, per-material pyrolysis yields, off-gas energy modelling, and the energy balance for the Urban Rig system. Every parameter is classified as FACT (measured on UR equipment), HYPOTHESIS (literature-based estimate), or ASSUMPTION (engineering judgement). Sources are cited inline throughout.

Date: March 2026

2.1 Test Programme Overview

All Urban Rig-specific test data originates from a controlled test campaign conducted at the Asada Shokai facility (Noda, Chiba Prefecture, Japan) between March and September 2022, supervised by Land Brain Co., Ltd. and documented in a 74-page Industrial Waste Test Research Report. Tests were performed on the Urban Rig batch unit using individual plastic types and mixed plastic batches.

Limitations of the test programme:

- All tests used the **batch** unit, not the continuous URC-2000 production machine. Batch-to-continuous scaling factors are manufacturer specifications, not independently verified (see §2.6).
 - **No non-plastic organic feedstock** (food waste, paper, wood) was tested on the UR. All organic pyrolysis parameters are literature estimates.
 - **PET, PVC, nylon, and SAP** were not tested on the UR. Their yields are derived from published pyrolysis literature.
 - Two mixed-waste tests (September 2022) yielded 32.2% and 45.0% oil, but the plastic fraction of the mixed waste was not measured, making back-calculation of per-material yields impossible (Asada Shokai test report, pp. 35–36).
-

2.2 Pure Plastic Test Results — Measured Oil and Off-Gas Yields

2.2.1 Individual Polymer Tests (9 Runs)

The following data comes from single-polymer tests on the UR batch unit. Off-gas mass is calculated by mass difference (input — oil — residue), not directly measured (Asada Shokai test report, Section 6).

Date	Feedstock	Input (kg)	Oil (kg)	Oil %	Off-gas (kg)	OG %	Residue (kg)	Res %
2022-03-02	PE pellets	20	14.8	74.0%	4.9	24.5%	0.3	1.5%
2022-03-09	PE molded offcuts	40	30.7	76.8%	8.8	22.0%	0.5	1.2%
2022-06-21	PE poly containers	50	40.7	81.4%	8.4	16.8%	0.9	1.8%
2022-04-08	PP pellets	20	16.2	81.0%	3.3	16.5%	0.5	2.5%
2022-04-16	PP molded offcuts	50	39.8	79.6%	10.0	20.0%	0.2	0.4%
2022-06-28	PP pallets	50	36.5	73.0%	7.4	14.8%	6.1	12.2%
2022-03-17	PS pellets	20	12.2	61.0%	4.0	20.0%	3.8	19.0%
2022-03-31	PS molded offcuts	40	22.0	55.0%	2.7	6.8%	15.3	38.2%
2022-07-07	PS foam	50	36.3	72.6%	3.8	7.6%	9.9	19.8%

Source: Asada Shokai Industrial Waste Test Research Report, Section 6 (September 2022).

2.2.2 Summary by Polymer Type

Polymer	Tests	Avg Oil %	Avg Off-gas %	OG % Range	Avg Residue %
PE	3	77.4%	21.1%	16.8–24.5%	1.5%
PP	3	77.9%	17.1%	14.8–20.0%	5.0%
PS	3	62.9%	11.5%	6.8–20.0%	25.7%

Key observations:

- PE and PP (polyolefins) perform similarly: 77–78% oil yield, 17–21% off-gas, minimal residue. These are the dominant plastics in MSW at approximately 60 wt% of the plastic fraction (ADEME MODECOM 2017).
- PS produces significantly more residue (19–38%) and less oil (55–73%) than polyolefins, consistent with PS forming styrene oligomers that remain in the char.
- Mass balance closes perfectly in all nine tests (input = oil + off-gas + residue).

2.2.3 Mixed Plastic Energy Balance Tests (2 Runs)

Two additional tests with mixed PE/PP/PS (“3P”) feedstock included detailed energy inputs and outputs (Asada Shokai test report, p. 35):

Parameter	Test 1 (2022-05-26, 3P pellets)	Test 2 (2022-07-11, 3P offcuts)
Input	60 kg	60 kg
Oil output	43.1 kg (71.8%)	49.4 kg (82.3%)
Off-gas	11.7 kg (19.5%)	1.3 kg (2.2%)
Residue	5.2 kg (8.7%)	9.3 kg (15.5%)
Electricity consumed	65 kWh (55,900 kcal)	65 kWh (55,900 kcal)
Light oil consumed (heating)	66 L (599,808 kcal)	76 L (690,688 kcal)
Off-gas recycled as fuel	15,489 kcal	1,721 kcal
Water (steam generation)	85 L	95 L

Parameter	Test 1 (2022-05-26, 3P pellets)	Test 2 (2022-07-11, 3P offcuts)
Total energy input	671,197 kcal	748,309 kcal

Source: Asada Shokai energy balance test reports, p. 35.

Observations:

- Oil yield ranges from 71.8% to 82.3% for mixed PE/PP/PS, supporting the **70% conservative assumption** used in the financial model.
- Off-gas mass varies enormously (11.7 kg vs 1.3 kg), likely reflecting batch startup conditions and off-gas capture variability rather than feedstock differences.
- Mass balance closes perfectly (60.0 kg out = 60.0 kg in) in both tests.

2.3 Per-Material Pyrolysis Yields — Full Polymer Set

For materials not tested on the UR, yields are estimated from published pyrolysis literature. These are required because MSW contains polymers beyond PE/PP/PS.

2.3.1 UR-Measured Polymers

Polymer	Oil Yield	Off-gas Yield	Residue	Data Quality
PE (LDPE + HDPE)	77%	22%	1%	FACT — Asada Shokai test #2 (PE molded, 40 kg)
PP	80%	18%	2%	FACT — Asada Shokai test #6 (PP molded, 50 kg)
PS	58%	14%	28%	FACT — Average of Asada Shokai tests #3 and #4

2.3.2 Literature-Estimated Polymers

Polymer	Oil Yield	Off-gas Yield	Residue	Source
PET	45%	17%	38%	<i>Polymer Degradation and Stability</i> , 2022 (slow pyrolysis at 400°C: 46.7% oil, 39.7% solid); cross-check: PMC 7183261
PVC	32%	~2%	13%	Two-stage dechlorination literature; 53% of mass exits as HCl (stoichiometric, captured by UR catalytic layer); net oil: 47% × 68% ≈ 32%. Sources: <i>Science of the Total Environment</i> , 2024; PMC 12096105

Polymer	Oil Yield	Off-gas Yield	Residue	Source
Polyester (textile)	45%	17%	38%	Same as PET — clothing polyester is chemically identical to PET resin
Nylon (PA6/PA66)	45%	20%	35%	PA6 pyrolysis at 500–700°C produces 40–80% caprolactam; conservative 45% total oil accounts for secondary products
SAP (sodium polyacrylate)	20%	30%	50%	Crosslinked acrylic polymer; Na content yields ~25–30% inorganic ash (Na_2CO_3)
Other synthetics	25%	25%	50%	Blended estimate for mixed adhesives, elastics, rubber

[!] **PET, PVC, nylon, and SAP have NOT been tested on the UR.** Validation on UR equipment is recommended.

2.3.3 Non-Plastic Materials

Material	Oil Yield	Off-gas Yield	Residue/Char	Source
Cellulose (paper, cardboard, wood, cotton)	12%	20%	68%	Bridgwater, <i>Biomass and Bioenergy</i> , 2012; Chen et al., <i>Waste Manage- ment</i> , 2014. Bio-oil has low CV (~17-20 MJ/kg vs ~43 MJ/kg for plastic oil)
Putrescibles (food/garden waste)	10%	20%	70%	Biomass pyrolysis literature. High moisture imposes energy penalty
Mineral inert	0%	0%	100%	Inorganic — passes through un- changed

[!] **No non-plastic organic feedstock has been tested on the UR.** All organic yields are HYPOTHESIS.

2.4 Oil Quality — Certified Laboratory Analysis

2.4.1 NKKK Fuel Certification

The produced oil was tested and certified by NKKK (Nippon Kaiji Kentei Kyokai — Japan Marine Survey Association) under JIS standards:

Parameter	Result	Comparison
Calorific value	43.27 MJ/kg	Fossil diesel: 42.6 MJ/kg
Flashpoint	46°C	—
Sulfur content	0.014%	Below IMO 2020 marine fuel limit (0.5%)
Chlorine content	1 ppm	Well below problematic levels

Source: NKKK recycled fuel test report, JIS standards.

2.4.2 Oil Fraction Distribution by Temperature Zone

The URC-2000 continuous process separates oil into four fractions by temperature-controlled condensation. The expected distribution is supported by independent laboratory distillation data.

Oil Fraction Characteristics by URC-2000 Zone:

Sources / Justification									
URC-2000 Zone	Expected Temperature	Oil Type	Flash Point	Density (SG)	Sulfur	Calorific Value	Possible Uses	Justification	
Zone 1 (GET)	150°C	~10%	Heating Oil (Light naphtha), C5-C8	< 21°C	0.70-0.76	19-30 ppm	~44-46 MJ/kg	Internal fuel (machine operation); Petrochemical feedstock (naphtha); Industrial solvent	URC-2000 brochure (10%); Asada Shokai p.28: lightest Class 1 fraction (Tb <150°C); SG/S from Class 1 PE (0.756, 19 ppm)

URC- 2000 Zone	Temperature	Expected Rate	Oil Type	Flash Point	Density (SG)	Sulfur	Calorific Value	Possible Uses	Sources / Justi- fica- tion
Zone 2 (GET)	300°C	~80%	Gas (Diesel) Oil (Kerosene + Diesel), C8- C20	40- 55°C	0.80- 0.86	50- 150 ppm	43-47 MJ/kg	Recycled diesel fuel (NKKK certi- fied); SAF co- processing feed- stock (Tier 1-3); JIS Class A/B heavy fuel oil equiv- alent; Indus- trial boiler com- bus- tion	URC- 2000 brochure (80%); Asada Shokai p.28: Class 2g- (52- 70%) + heavy Class 1 (Tb 150- 300°C); Ohsumi Tab.3- 8: flash <40°C, 43-47 MJ/kg; NKKK: flash ≤40°C, S 0.014%, 43.27 MJ/kg

URC- 2000 Zone	Temperature	Expected Rate	Oil Type	Flash Point	Density (SG)	Sulfur	Calorific Value	Possible Uses	Sources / Justi- fica- tion
Zone 3 (GET)	450°C	~10%	Heavy Oil, C20+	> 70°C	> 0.90	100- 200 ppm	40-45 MJ/kg	Industrial heavy fuel oil; High- capacity boiler fuel; Bitu- men/asph- alt feed- stock	URC- 2000 brochure (10%); Asada Shokai: heavy tail of Class Balt (Tb >300°C); Ohsumi Tab.3- 9: com- para- ble to JIS heavy fuel oil C
Zone 4 (GET)	600°C	Traces	Asphaltenes (semi- solid residue)	None	> 1.0	Variable	~32 MJ/kg	Solid fuel (car- bide); Soil amend- ment (biochar)	URC- 2000 brochure; Is- mitec: ure- thane car- bide 32.09 MJ/kg

Source: URC-2000 product brochure (One World Japan); Asada Shokai report Section 7.2 p.28; Ohsumi Verification Report Table 3-8; NKKK certified test report; Is-

mitec calorific certificates.

Compatibility Analysis — Distillation Data vs. 10/80/10 Dispatch:

The Asada Shokai report (Section 7.2, p.28) provides the only independent laboratory distillation of crude pyrolysis oil, separating it into Japanese petroleum Class 1 (flash point < 21°C) and Class 2+ (flash point > 21°C). The results are:

Plastic	Class 1			% Class 1		Class 2+			% Class 2+		Recovery
	Vol.	Flash	SG			Vol.	Flash	SG			
PE	61 ml	18°C	0.7563	30.5%		139 ml	55°C	0.8606	69.5%		100%
PP	56 ml	18°C	0.7603	33%		114 ml	45°C	0.8206	7%		85%
PS	90 ml	16°C	0.8704	5%		110 ml	53°C	0.9005	55%		100%
3P (mix)	96 ml	16°C	0.7884	8%		104 ml	52.5°C	0.8345	2%		100%

Source: Asada Shokai Industrial Waste Test Research Report (アサダショカイ工業廃棄物試験研究報告), Section 7.2, p.28 (January 2023). Samples of 200 ml per test.

The apparent discrepancy between 30–48% Class 1 (distillation) and the manufacturer’s 10% light oil fraction is explained by the difference in separation methods. Flash point ≠ boiling point: a compound classified as “Class 1” (flash < 21°C) can have a boiling point of 100–150°C+. In the URC-2000’s condensation-based system, such compounds condense in Zone 2 (300°C), not Zone 1 (150°C). Only the lightest naphtha (boiling point < 150°C) is captured in Zone 1. The heavy portion of Class 1 (boiling point 150–300°C) joins the Class 2+ diesel/kerosene fraction in Zone 2, while the heaviest tail of Class 2+ (boiling point > 300°C) moves to Zone 3. This makes the 10/80/10 distribution consistent with the measured distillation data.

[!] The 10/80/10 distribution is a manufacturer specification for the continuous URC-2000. No independent test of the continuous machine’s actual zone-by-zone output has been conducted. The Asada Shokai distillation data confirms oil composition is compatible with this distribution but was performed on batch-produced crude oil, not on zone-separated output from the URC-2000.

2.4.3 GC-MS Oil Composition (Qualitative Only)

Gas chromatography-mass spectrometry analysis performed by the Osaka Institute of Industrial Science and Technology on oil from the Asada Shokai test programme identified the principal compounds in the volatile (gas oil) fraction:

- Dimethylheptane (C₉)
- Undecene (C₁₁)
- Trimethylnonane (C₁₂)

These are middle-distillate hydrocarbons in the C₈-C₁₆ range, confirming that the dominant oil fraction (~80% of liquid output) is in the diesel/kerosene/naphtha range — directly usable as feedstock for steam crackers or refinery co-processing (Osaka Institute GC-MS report).

[!] The GC-MS quantitative data (54% heavy / 25% diesel) is INVALIDATED due to equipment malfunction during the test (overheating caused loss of the diesel fraction). Only the qualitative compound identification (C7-C16 chain range) is retained. The GC-MS tested the entire mixed oil sample, not a separated fraction.

2.4.3 Char Calorific Value

Literature baseline: Published pyrolysis literature reports the following char calorific values for conventional (non-superheated-steam) pyrolysis systems:

Char source	Literature CV (MJ/kg)	Range	Literature basis
MSW biomass char (organic/cellulose)	8-22	Wide, depends on ash content and process temperature	Fazil et al., <i>Energies</i> , 2021; Ronsse et al., <i>Biomass Conversion and Biorefinery</i> , 2020
Plastic-derived char	20-32	Higher carbon retention from incomplete polymer conversion	Malinowski et al., <i>Waste-Derived Chars: A Comprehensive Review</i> , 2023
Carbon black (reference)	~32	Industrial benchmark for near-pure carbon residue	Standard reference

Conservative estimates used in the financial model (Annex 5 §13):

Char source	CV estimate (MJ/kg)	Confidence	Rationale
Organic/cellulose char	15	MEDIUM	Mid-range for MSW biomass char; conservative vs clean biomass (20+ MJ/kg)
Plastic char	25	MEDIUM	High carbon content from incomplete polymer conversion
Weighted average (combustible fraction)	15.6	MEDIUM	Calculated: $(452.2 \times 15 + 28.6 \times 25) / (452.2 + 28.6)$

UR-specific measurement: One laboratory measurement on UR-produced char exists, and it sits at the top of the literature range:

Sample	CV	Method	Lab
Urethane-derived char	32.09 MJ/kg	JIS M 8814 bomb calorimeter	Isumi Tech Co., Ltd. (Report R35-339439)

This result — 32.09 MJ/kg on a single polymer feedstock — is notably higher than the 20–32 MJ/kg literature range for plastic char from conventional pyrolysis. While the single test is on a clean polymer (urethane, not MSW), the elevated value is consistent with a hypothesis that the Urban Rig’s superheated-steam process may produce higher-energy char than conventional pyrolysis. The steam environment suppresses secondary cracking of the char matrix and may preserve more fixed carbon, resulting in a product closer to carbon black than to typical pyrolysis char. This hypothesis remains unproven and requires validation by bomb calorimetry on UR-produced MSW char across multiple feedstock compositions.

[!] **MSW-derived char CV has NOT been measured on the UR.** The financial model uses conservative literature-based estimates (15 MJ/kg organic, 25 MJ/kg

plastic). These values are important for assessing the commercial viability and energy content of char as a marketable fuel product. Bomb calorimetry validation on UR-produced MSW char is recommended to support char sale quality assurance and pricing.

2.5 Off-Gas Composition and Energy

2.5.1 Qualitative Composition (GC Analysis)

A gas chromatography analysis was performed on an off-gas sample collected from the UR batch unit (report B2002600, 2020-12-05, Asada Shokai facility). The combustible species identified are:

Combustible Component	Detected
Hydrogen (H ₂)	Yes
Methane (CH ₄)	Yes
Ethane (C ₂ H ₆)	Yes
Ethylene (C ₂ H ₄)	Yes
Propane (C ₃ H ₈)	Yes
Propylene (C ₃ H ₆)	Yes
Carbon monoxide (CO)	Yes

Source: GC analysis report B2002600, 2020-12-05, Asada Shokai facility.

The sample also contained N₂ (~66%) and O₂ (~12%), most likely from the carrier gas and/or air ingress during sampling. Quantitative proportions cannot be used directly for volumetric LHV calculation. The qualitative composition confirms a typical pyrolysis gas mixture — combustible in a dedicated burner system. The presence of hydrogen provides reliable ignition and flame stability.

2.5.2 Off-Gas Calorific Value (Constant Factor)

Both 3P energy balance tests yield an identical off-gas energy factor (Asada Shokai test report, p. 35):

Test	Off-gas mass	Off-gas energy	Energy per kg
2022-05-26 (3P pellets)	11.7 kg	15,489 kcal	1,324 kcal/kg
2022-07-11 (3P offcuts)	1.3 kg	1,721 kcal	1,324 kcal/kg

1,324 kcal/kg = 5.54 MJ/kg off-gas [FACT]

This was confirmed as constant across all four feedstock types tested: 3P pellets, 3P molded, container recycling (MSW), and non-combustible residue — all returned 1,324 kcal/kg (Asada Shokai energy balance tables, pp. 35–36).

Methodological note: The identical value across all tests indicates this is a calorific factor applied to the mass balance, rather than an independent per-batch measurement. The same approach was used for oil (10,980 kcal/kg = 45.9 MJ/kg) and residue (5,880 kcal/kg = 24.6 MJ/kg). Cross-validation: independent lab analysis of oil from the same test campaign gave 46,000 J/g for container plastic oil and 45,000 J/g for non-combustible residue oil — consistent with the energy balance factor (Asada Shokai test report, Section 10).

2.5.3 Off-Gas Energy per kg of Feedstock

From plastic feedstock (measured):

Parameter	Value	Source
Weighted off-gas yield (MSW polymer mix)	19.3% of plastic input	Financial model cell J1: SUMPRODUCT of polymer mix × off-gas yields
Off-gas CV (steam-diluted)	5.54 MJ/kg	Asada Shokai energy balance (constant across all feedstocks)
Off-gas energy per kg plastic	1.069 MJ/kg	0.193 × 5.54 (financial model cell J3)

Note: A simplified PE/PP-only calculation gives 1.27 MJ/kg (23% off-gas × 5.54), but this overstates off-gas by 19% because it ignores the 10.3% residue from PET, PS, and PVC in the MSW mix. The weighted 1.069 MJ/kg is the correct figure for MSW modelling.

From organic/cellulose feedstock (literature estimate):

Parameter	Value	Source
Estimated off-gas CV (steam-diluted)	~2.0 MJ/kg off-gas	HYPOTHESIS — lower than plastic off-gas due to high CO ₂ and H ₂ O content
Off-gas mass yield	~20% of organic input	Bridgwater, 2012; Chen et al., 2014
Off-gas energy per kg organic	~0.5 MJ/kg	Conservative central estimate (range: 0.3–0.8 MJ/kg)

Sources for organic off-gas energy range: Bridgwater, Biomass and Bioenergy, 2012; Chen et al., Waste Management, 2014; PMC 9936530 (review of pyrolysis gas CV: 3–12 MJ/Nm³ for biomass); PMC 11044251 (HHV of non-condensable gas: 14.56 MJ/m³ at 600°C for clean biomass).

[!] **The organic off-gas energy (0.5 MJ/kg) is a literature-based estimate. It has NOT been measured on the UR.** This parameter affects the total energy balance and off-gas contribution to operational understanding (see §2.6).

Important correction log: The original financial model contained an inverted parameter — organic off-gas energy was set at 5.0 MJ/kg instead of 0.5 MJ/kg, overstating organic off-gas by 10×. This was corrected in Session 9 based on literature review of 12 peer-reviewed sources. The correction inverts the self-sufficiency relationship: higher plastic content now **improves** (rather than hurts) off-gas coverage, which is physically correct — plastic pyrolysis produces energy-rich hydrocarbon gas while organic pyrolysis produces mostly CO₂ and water vapour.

2.6 Energy Balance

2.6.1 Plant Heating Demand

The URC-2000 manufacturer specification (UR2000-JP, p. 4; Lufthansa worksheet) specifies **10,000 litres/day** of light oil for the 200 T/day unit (140 T actual throughput at 0.7 T/m³ density). Using the light oil energy density from test data (9,088 kcal/L = 38.0 MJ/L):

Reference heating demand: 10,000 L × 38.0 MJ/L = 380,000 MJ/day (~4.4 MW continuous)

Thermodynamic cross-check:

Component	Estimate
Sensible heat (140 T/day, 20°C → 600°C, $c_p \approx 1.5 \text{ kJ/kg}\cdot\text{K}$)	~122,000 MJ/day
Latent heat for moisture evaporation (~20% moisture)	~67,000 MJ/day
Endothermic pyrolysis reactions	~2,000 MJ/day
Heat losses (insulation, radiation, ~25%)	~48,000 MJ/day
Thermodynamic minimum	~239,000 MJ/day (~2.8 MW)

The manufacturer figure (380,000 MJ) is ~60% above the thermodynamic minimum — plausible given real-world burner efficiency, heat distribution losses, and safety margins. **The manufacturer figure is used as the reference demand** because it comes from the equipment specification (UR2000-JP, p. 4).

[!] **The 380,000 MJ/day heating demand is a manufacturer specification for continuous operation. It has NOT been independently verified** by a third-party audit of an operating continuous UR installation. In the V2 model, this heating demand is met entirely by purchased heating oil (10,000 L/day), with all char produced allocated to commercial sale.

2.6.2 Off-Gas Coverage by Plastic Content

Using measured off-gas energy (1.069 MJ/kg plastic) and literature-estimated organic off-gas (0.5 MJ/kg organic), with 15% inorganic fraction removed before processing:

Plastic %	Organic %	Off-gas (MJ/day)	Coverage	External fuel needed
10%	75%	67,469	17.8%	Yes
15%	70%	71,454	18.8%	Yes
(France MSW)				
20%	65%	75,438	19.9%	Yes
30%	55%	83,407	22.0%	Yes
(model default)				
50%	35%	99,345	26.1%	Yes
(industrial)				

Plastic %	Organic %	Off-gas (MJ/day)	Coverage	External fuel needed
100% (pure plastic)	0%	149,691	39.4%	Yes

Source: UR-Financial-Model-General.xlsx, Energy Scenarios sheet (corrected). Off-gas CV from Asada Shokai test data pp. 35–36; organic off-gas from pyrolysis literature (0.3–0.8 MJ/kg range; Bridgwater 2012, Chen et al. 2014). Inorganic fraction: 15% (glass, metals, ash — removed before reactor).

Key finding: off-gas alone never covers the full heating demand. Even at 100% plastic, off-gas provides only 39% of the energy needed. At typical French MSW (15–20% plastic), coverage is approximately 19–20%.

2.6.3 Energy Balance: Off-Gas and Char Energy Potential

While off-gas alone is insufficient to meet the full heating demand, the **char by-product** from the organic and cellulose fractions represents a significant energy-rich commercial product. Per 1,000 kg of OMR entering the reactor, the process produces 480.8 kg of combustible char with a weighted calorific value of 15.6 MJ/kg (§2.4.3). Scaled to the 140 T/day operational throughput:

Energy source	MJ/day	Energy content
Off-gas (plastic + organic)	90,407	23.8% of heating demand
Char energy potential	1,049,720	276.3% of heating demand
Total energy in by-products	1,140,127	~300% of heating demand
Plant heating demand (purchased oil)	379,960	100% (external fuel supplied)

Source: Off-gas from UR-Financial-Model-General.xlsx Energy Scenarios sheet; char energy from Annex 5 §13.3 (480.8 kg/T × 15.6 MJ/kg × 140 T/day). Char CV: 15 MJ/kg organic/cellulose char, 25 MJ/kg plastic char (HYPOTHESIS — see §2.4.3).

V2 Operating Model: In the current V2 operating model, all reactor heating is provided by purchased heating oil, and all char produced is sold on the commercial fuel market. The energy balance demonstrates that the char and off-gas contain significant energy content relative to the system’s heating requirement, which supports the commercial viability of char as a premium fuel product:

Parameter	Value
Total char produced (combustible)	67,312 kg/day (67.3 T/day)
Char available for sale	~67.3 T/day (~22,095 T/year)
Char energy content	1,049,720 MJ/day
Off-gas energy contribution	90,407 MJ/day
Plant heating supply	Purchased heating oil (10,000 L/day)

Source: Annex 5 §13.3; V2 operating model (March 2026).

Energy Content Implications: Even under conservative char CV assumptions (10 MJ/kg instead of 15 MJ/kg), the char produced maintains substantial energy value — approximately 180% of the plant heating demand — confirming robust commercial potential. Bomb calorimetry validation on UR-produced MSW char is recommended to support market positioning and pricing strategies.

2.6.4 Sensitivity to Organic Off-Gas Energy Assumption

The off-gas coverage figures are moderately sensitive to the organic off-gas energy estimate. However, because off-gas provides only ~24% of the total heating demand regardless of this assumption, and because all operational heating is supplied by purchased oil in the V2 model, the sensitivity affects primarily the understanding of total energy balance and the assessment of off-gas energy recovery potential:

Organic off-gas energy	Off-gas energy recovery	Share of total by-product energy
0.3 MJ/kg (pessimistic)	~80,500 MJ/day	7.1%
0.5 MJ/kg (central)	~90,400 MJ/day	7.9%
0.8 MJ/kg (optimistic)	~110,300 MJ/day	9.6%

Across the full literature range (0.3–0.8 MJ/kg organic off-gas), the total char availability for commercial sale remains stable at approximately 67.3 T/day. The organic off-gas energy estimate affects the relative proportions of off-gas and char energy contributions to the overall energy balance, but does not affect the V2 operating model where all char is marketed and reactor heating is sourced externally.

2.7 Exhaust Gas Emissions — Independent Laboratory Results

2.7.1 Air Emissions

Analysed by KANSO Technos, report 20002610, dated 2020-12-05. Samples collected 2020-11-25 at the Asada Shokai test facility (Noda, Japan).

Pollutant	UR Measured	Analysis Method	French Incineration Limit	Factor Below Limit
Hydrogen chloride (HCl)	< 1 ppm	JIS K 0107 (2012)	10 mg/m ³ (~7 ppm)	>7×
Sulfur oxides (SOx)	< 1 ppm	JIS K 0103 (2011)	50 mg/m ³	>50×
Nitrogen oxides (NOx)	15 ppm	JIS K 0104 (2011)	200 mg/m ³ (~100 ppm)	>6×
Particulate matter	< 0.002 g/m³	JIS Z 8808 (2013)	10 mg/m ³	>5×

Source: KANSO Technos Analysis Report 20002610. French incineration limits per Order of 20 September 2002 (Order of 20 September 2002).

Key result: Emissions are 5–50× below French incineration standards across all measured pollutants. The anoxic process eliminates the chemical formation pathway for dioxins and furans entirely — they cannot form without oxygen (Urban Rig Recycling Solutions ENG, p. 14). This is fundamentally different from incineration where dioxins form during combustion and must be captured by expensive filter systems.

2.7.2 Odour Assessment

Analysed by Total Environment System Co., Ltd., Osaka, 2020-11-27. Method: Environmental Agency Notification No. 63 (1995-09-13).

Measurement Point	Odour Index	Odour Concentration
Emission source (exhaust)	14	25
North boundary	< 10	< 10
West boundary	< 10	< 10

Measurement Point	Odour Index	Odour Concentration
-------------------	-------------	---------------------

Source: Total Environment System Co., Ltd. odour measurement report, 2020-11-27.

Japanese odour regulations typically require < 15-20 at the emission source and < 10-12 at property boundaries. The UR meets these standards. French ICPE odour requirements should be compared during the permitting phase.

2.8 Batch-to-Continuous Scaling

The test data (§2.2) was collected on the batch unit. The URC-2000 production machine operates continuously. The manufacturer specifies the following scaling parameters:

	Batch (per tonne, from Parameter tests)	Continuous (UR2000-JP / Lufthansa worksheet)	Ratio
Electricity	~1,083 kWh/T	~4.3 kWh/T (600 kW / 140 T/day)	~250× less
Heating fuel	~1,183 L/T	~71.4 L/T (10,000 L / 140 T/day)	~ 17× less
Staffing	—	~15 personnel for 200 T/day	—

Source: Asada Shokai batch test data vs UR2000-JP technical specification, p. 5; Lufthansa worksheet assumptions; Urban Rig Recycling Solutions ENG, p. 19.

The 17× fuel efficiency improvement is explained by: (1) no reheat cycles — continuous reactor stays at 600°C, (2) better insulation at scale — heat loss scales as r^2 while throughput scales as r^3 , (3) steady-state thermal equilibrium without temperature cycling losses, and (4) off-gas preheating of incoming feed in continuous mode.

[!] The continuous-operation figures are manufacturer specifications. They have NOT been independently verified by a third-party audit of an operating URC-2000 installation. The 17× improvement is physically plausible but the exact values require validation during commissioning.

2.9 Key Assumptions — Verification Status Summary

#	Assumption	Value	Source	Status
F1	Oil yield from plastic (pure PE/PP/PS)	70% (conservative)	Tested 71.8–82.3% (2 mixed tests, 9 individual tests)	FACT
F2	Oil yield linearity with plastic %	Oil = plastic% × 70%	Scientific literature on superposition model (Buah et al., 2022: max ±8% deviation)	HYPOTHESIS — supported by literature
F3	Biochar yield from organic matter	~68–70% of organic input	Bridgwater, 2012; Chen et al., 2014	HYPOTHESIS — not tested on UR
F4	Oil density	0.85 kg/L	Standard pyrolysis oil density	REASONABLE
F5	Off-gas composition (qualitative)	H ₂ , CH ₄ , C ₂ –C ₃ hydrocarbons, CO	GC analysis report B2002600, Asada Shokai facility	FACT (qualitative)
F6	Off-gas mass by polymer type	PE 21%, PP 17%, PS 12%	Asada Shokai test data (9 individual tests) — mass balance	FACT
F7	Off-gas CV (steam-diluted)	5.54 MJ/kg	Asada Shokai energy balance tests (constant across all feedstocks)	FACT
F8	Weighted off-gas rate (MSW plastic mix)	19.3% of plastic input	Weighted from F6 + literature for PET/PVC	DERIVED from FACT + HYPOTHESIS

#	Assumption	Value	Source	Status
F9	Off-gas energy from organic matter	~0.5 MJ/kg organic input	Literature (range 0.3–0.8 MJ/kg; 12 peer-reviewed sources)	HYPOTHESIS — critical, not tested on UR
F10	Plant heating demand (continuous)	380,000 MJ/day	UR2000-JP specification, Lufthansa worksheet	MANUFACTURER SPEC — not independently verified
F11	Char CV (organic/cellulose)	15 MJ/kg	Mid-range literature (Fazil et al., 2021; Ronsse et al., 2020)	HYPOTHESIS — not tested on UR
F12	Char CV (plastic)	25 MJ/kg	Literature (Malinowski et al., 2023)	HYPOTHESIS
F13	Exhaust emissions	< 1 ppm HCl, < 1 ppm SO _x , 15 ppm NO _x	KANSO Technos Report 20002610	FACT — accredited lab
F14	Oil CV	43.27 MJ/kg	NKKK certified test report	FACT — accredited lab
F15	Batch-to-continuous efficiency	~17× fuel reduction	Manufacturer spec vs test data	PLAUSIBLE — needs validation

Summary:

- **FACT** (lab/test data): F1, F5, F6, F7, F13, F14 — 6 of 15
- **DERIVED** (from verified + literature): F8 — 1 of 15
- **REASONABLE** (standard values): F4 — 1 of 15
- **HYPOTHESIS** (literature-based, not tested on UR): F2, F3, F9, F11, F12 — 5 of 15
- **MANUFACTURER SPEC** (not independently verified): F10, F15 — 2 of 15

2.9.1 Priority Validation Requests

The following data requests to Urban Rig / One World Corporation are recommended before commercial deployment:

1. **Off-gas flow rate and composition during continuous operation** — to validate the 5.54 MJ/kg constant at production scale and establish quantitative species proportions.
2. **Test data with non-plastic organic feedstock** (biomass, food waste, paper) — to validate the 0.5 MJ/kg organic off-gas estimate and the biochar yield assumptions.
3. **Bomb calorimetry on MSW-derived char** — to validate the 15 MJ/kg organic char and 25 MJ/kg plastic char assumptions that underpin the self-sufficiency claim.
4. **Validated energy balance for the continuous URC-2000** at different feedstock compositions — to confirm the 380,000 MJ/day heating demand and the 17× batch-to-continuous efficiency improvement.
5. **PET and PVC test runs on the UR** — to validate literature-estimated yields for the two most problematic polymer types in MSW.

2.10 Literature Sources for Off-Gas Energy Model

The off-gas energy relationship and correction (§2.5.3) is supported by 12 peer-reviewed sources:

1. ScienceDirect — “Pyrolysis gases produced from individual and mixed PE, PP, PS, PVC, and PET — Part I.” PE off-gas at 86.6 MJ/m³N.
2. PMC 9936530 — “A review on gasification and pyrolysis of waste plastics.” Gas CV: 3–12 MJ/Nm³.
3. PMC 11044251 — “Yield and Energy Modeling for Biochar and Bio-Oil Using Pyrolysis Temperature.” HHV of non-condensable gas: 14.56 MJ/m³ at 600°C.
4. Asada Shokai test data — Off-gas CV = 5.54 MJ/kg (steam-diluted). Energy balance tables, pp. 35–36.
5. Buah et al. (2022) — “Pyrolysis of mixed plastic waste: Predicting the product yields.” Linear superposition model, max deviation 8 pp.
6. ScienceDirect — “Co-pyrolysis of waste plastic and solid biomass for synergistic production of biofuels.” Plastic as hydrogen donor.
7. ScienceDirect — “Impact of plastic blends on the product yield from co-pyrolysis of lignin-rich materials.” Synergy rates up to 7.78% at 500°C.
8. Nature Scientific Reports — “Co-pyrolysis of furniture wood with mixed plastics.” Gas/solid yields change “almost linearly” with pine %.

-
9. ScienceDirect — “Co-pyrolysis and co-gasification of biomass and plastics.” Blend ratio contributes 28% to gas yield model; temperature 33%.
 10. ScienceDirect — “A review on municipal solid waste pyrolysis of different composition for gas production.”
 11. Frontiers — “Plastic regulates its co-pyrolysis process with biomass.” Mass ratio is second most influential factor (28%).
 12. EUBIA — “Pyrolysis” overview. Fast pyrolysis yields: ~65% liquid, ~10% gas, ~25% char; at >700°C up to 80% gas.
-

End of Annex 2