





F_{transfer} : one shape, four rates — a gapped relaxation to a UNIQUE attractor



Only F_{pole} 's rate is the seam eigenvalue $(2/3)^6$; the other three share the shape with external rates (v303).