


Centre-Injection Nanoparticle Transport

Block heatmaps — 6 h run, 23 Aug 2026 (0.4% agarose, non-BSA)


One page per coating (PEG, COOH). Rows: large-magnet arm (mean of L1-L3), small-magnet arm (mean of S1-S3), and the no-magnet control. Columns step through the 6 h run. Each cell is the 10x10 mm agarose block from above; the x-axis spans the whole block with 0 mm at the left edge and the magnet side at the right, so the centre injection gap appears as the bright band near 5 mm. Colour is NP darkness above each frame's own gel floor (camera exposure cancels); one shared scale (0-55 L*). The outer ~0.8 mm is trimmed because the gel pulls away from the holder late in the run and that seam would read as nanoparticles.

Transport is ordered large magnet > small magnet > control for both coatings, rising monotonically all run; controls stay put. Repeats 1-2 were photographed on 23 Aug and repeat 3 plus both controls on 25-26 Aug, so each magnet row averages across two sessions.

23 Aug · 0.4% agarose · non-BSA · PEG · centre injection



23 Aug · 0.4% agarose · non-BSA · COOH · centre injection



23 Aug validation — warped block photo vs heatmap

