# coatings and linings =

high performance

# PCS-2250 HYDRO-TECH WATER REDUCIBLE PIPE ENAMEL ASPHALT MODIFIED

**DESCRIPTION:** An asphalt modified water-reducible enamel for interior or exterior use, has good color and gloss retention, and the ability to be applied either direct to metal or to previously-painted surfaces.

**ADVANTAGES: PCS-2250** is extremely fast drying for a water reducible enamel, exhibiting very good early water resistance. It is V.O.C. compliant and has no flash point, which reduces fire hazards and may lower insurance costs.

**USES: PCS-2250** is used to coat machinery, implements, sanitation equipment, pipe, pipelines, shipping containers, structural steel and as a general maintenance finish. **Not** recommended for interior pipe linings. Consult **Permite** for recommendations.

**SURFACE PREPARATION:** Remove all loose rust, loose paint, oil, grease or other interference materials prior to painting.

**MIXING:** Stir thoroughly before use.

**THINNING: PCS-2250** will appear heavy bodied in comparison with solvent based paints, especially in colder temperatures. However, do not thin unless necessary to achieve atomization and then do so sparingly--no more than ½ pint of water per gallon.

**CLEAN-UP:** Warm soapy water.

**CAUTIONS:** PCS-2250 is not flammable. Components of this product may be skin irritants and/or skin sensitizers. Rubber gloves should be worn to minimize skin contact. Avoid breathing vapors of material. **IF SWALLOWED, DO NOT INDUCE VOMITING.** Call a physician immediately. For eye contact, flush with water.

See material safety data sheet for full precautions prior to use.

**PCS-2250** is intended for industrial use only.

**VOC:** As supplied:

Excluding water: 2.6 (±0.20) lbs./gallon Including water: 1.0 (±0.20) lbs./gallon

**COLORS:** Black

**VOLUME SOLIDS:**  $27\% \pm 3$ 

#### THEORETICAL COVERAGE:

430 sq. ft / mil / gal. (unreduced)

**THINNING:** None required for brush or roll; or airless spray

**GLOSS:** 90° +

## **SUGGESTED FILM THICKNESS:**

1.0-1.5 mils DFT over primer 2.0-2.5 mils DFT direct to metal

**APPLICATION:** Roll, brush, or spray

## **APPLICATION TEMPERATURE:**

40° F to 120° F

DRY TIME: At 77° F, 50% relative

humidity: Dust free: 20 minutes

To handle: 1-3 hours Recoat: 10-15 minutes

#### **SERVICE TEMPERATURE:**

140° F for continuous service 180° F intermittent

**PACKAGING:** 5-gallon pails, 55-gallon drums, and totes

**SHELF LIFE:** 3-6 months in unopened containers when stored between 40° F min. and 100° F max.