


FIG. 1. Melting points and melting curves of SiO_2 from this work and the literature. We fitted Simon-Glatzel melting equations using $T_{\text{melting}}(P) = T_0 \times (1 + \frac{P-P_0}{a})^b$ to the melting points from the Z method and two-phase calculations, which gave the following parameters: $T_0 = 6.018$, $P_0 = -202.338$, $a = 4.736 \times 10^{-4}$, and $b = 0.5126$ (two-phase calculations) and $T_0 = 6.462$, $P_0 = -256.011$, $a = 6.474 \times 10^{-4}$, and $b = 0.5141$ (Z method calculations). For the two-phase calculations the data points used in the fitting were the mean values of the lowest liquid and highest solid phases at a given temperature. All data points from the two-phase calculations are also reported in Table S1 in the SM. The inset shows the steepness of the melting curves from the two-phase coexistence calculations.