

**DATA SHEET FOR FR-LSH WIRES AS PER IS 694
(1 Sq.mm to 4 Sq.mm)**

Sr No.	Description	Unit	1C x 1 SQMM	1C x 1.5 SQMM	1C x 2.5 SQMM	1C x 4 SQMM
1	Description		Y	Y	Y	Y
2	Type of cable		FR-LSH PVC Insulated Unsheathed	FR-LSH PVC Insulated Unsheathed	FR-LSH PVC Insulated Unsheathed	FR-LSH PVC Insulated Unsheathed
3	Reference design Standards		IS 694/2010 With upto date amendment	IS 694/2010 With upto date amendment	IS 694/2010 With upto date amendment	IS 694/2010 With upto date amendment
4	Conductor size	mm ²	1	1.5	2.5	4
5	Rated Voltage	Volts	1100	1100	1100	1100
6	No of Core	Nos	1	1	1	1
7	Conductor					
	a Material		Annealed Plain Copper Conductor	Annealed Plain Copper Conductor	Annealed Plain Copper Conductor	Annealed Plain Copper Conductor
	b Reference Standards		IS 8130/2013 Class -5	IS 8130/2013 Class -5	IS 8130/2013 Class -5	IS 8130/2013 Class -5
	c Shape of conductor		Bunched Circular	Bunched Circular	Bunched Circular	Bunched Circular
	d Conductor d.c.Resistance Corrected to 20°C	Ohm/Km	19.5	13.3	7.98	4.95
	e AC Resistance at 85°C for Information only	Ohm/Km	23.4	15.96	9.576	5.94
	f Cuurent Rating in normal operation condition	Ampere	14	16	22	29
8	Insulation					
	a Reference Standards		IS 5831/1984	IS 5831/1984	IS 5831/1984	IS 5831/1984
	b Material composition		PVC Type-D With FR-LSH properties	PVC Type-D With FR-LSH properties	PVC Type-D With FR-LSH properties	PVC Type-D With FR-LSH properties
	c Thickness (Nominal) as per IS	mm	0.6	0.6	0.7	0.8
	d Core identification		As per customer requirment	As per customer requirment	As per customer requirment	As per customer requirment
	e The insulation will withstand conductor operating temp.	oC	70°C	70°C	70°C	70°C
9	Overall dimeter of cable (Maximum)	mm	3.0	3.4	4.1	4.8
10	Test for FRLS Properties :-					
	a Oxygen Index @ ambient temp. as per ASTM-2863	%	Not Less than 29	Not Less than 29	Not Less than 29	Not Less than 29
	b Smoke density rating As per ASTM-2843	%	Shall not be more than 60%	Shall not be more than 60%	Shall not be more than 60%	Shall not be more than 60%
	c Acid gas generation As per IEC 754-I	%	Shall not be more than 20% by weight	Shall not be more than 20% by weight	Shall not be more than 20% by weight	Shall not be more than 20% by weight
11	PACKING:					
	a Material		Rolls	Rolls	Rolls	Rolls
	b Length of cable per roll Sizes 25 sq.mm and above may be supplied in drums of 1000 Meter ± 5%	Meter	90/100/180/270 Meter in Rolls	90/100/180/270 Meter in Rolls	90/100/180/270 Meter in Rolls	90/100/180 Meter in Rolls
	c Order qty tolerance		± 2 Rolls or ± 5%	± 2 Rolls or ± 5%	± 2 Rolls or ± 5%	± 2 Rolls or ± 5%
12	Marking on Cable					
	a By Printing		RALLISON 1100V NO OF CORE X SIZE, "FR-LSH"	RALLISON 1100V NO OF CORE X SIZE, "FR-LSH"	RALLISON 1100V NO OF CORE X SIZE, "FR-LSH"	RALLISON 1100V NO OF CORE X SIZE, "FR-LSH"

Note: 5 % of Ordered quantity may be supplied in Assorted Non-Standard length but shall not be less than 50 Metres

Note: In case of any dispute/typographical error interpretation of the IS specification shall prevail.