



Torsion test: thin-walled tube, soda-lime glass
 $\sigma_{ss}^{DP} = 44.4$ MPa — cf. Kamarei et al. (2026) Fig. 8



(c) AT1 failure analysis

	Sharp	Our model	AT1 (fitted)
σ_{ss} (MPa)	44.4	44.4	25.9
Ratio to exact	1.00	1.00	0.58
Crack angle	45°	45°	0° (wrong)
Nucleation	Correct	Correct	Wrong stress