

## ANNEXURE III

IIITK/04/03/C/K1/21-22

09.12.2021

### TECHNICAL SPECIFICATION FOR STAINLESS STEEL

The Alloy shall conform to SS: 304

#### The Mechanical properties for 304 SS steel alloys – ( 8-75 mm thick)

| Grade                  | 304      | 304 L    |
|------------------------|----------|----------|
| Tensile Strength (MPa) | 520-720  | 500-700  |
| Proof Stress (MPa)     | 210 Min  | 200 Min  |
| Elongation AS          | 45 Min % | 45 Min % |

#### Physical properties for 304 stainless steel alloys

| Property               | Value                         |
|------------------------|-------------------------------|
| Density                | 8.00 g/cm <sup>3</sup>        |
| Melting Point          | 1450 degree C                 |
| Electrical resistivity | 0.72 X 10 <sup>-6</sup> Ohm m |
| Thermal Conductivity   | 16.2 W/m.k                    |
| Thermal Expansion      | 17.2 X 10 <sup>-6</sup> /K    |

#### Specifications in general

- " One Year Guarantee against manufacturing defects, if any.
- " All equipment's top fabricated with 18 S.W.G. 304 Grade sheet.
- " All Sinks Made with 20 SWG SS 304 Grade Sheet.
- " Side covers with 22 S.W.G S.S sheet. Unless otherwise specified.
- " Under shelves using 20G SWG SS 304 Grade Sheet.
- " All Leg Using 18 SWG SS 304 Grade sheet
- " All S.S legs would be provided with height adjustable nylon boots.

If any discrepancies noticed while physical testing by the Engineer –in charge, The item may get tested as per the discretion by the authority .The test shall be carried out free of cost by the contractor and the testing standards shall follow as per the relevant IS code.

