



บริษัท ปิโตรนาส อินเตอร์เนชันแนล มาร์เก็ตติ้ง (ประเทศไทย) จำกัด
2 อาคารจัสมิน ซิตี ชั้น 26 ซอยประสานมิตร (สุขุมวิท 23) ถนน สุขุมวิท แขวงคลองเตยเหนือ
เขตวัฒนา กรุงเทพฯ 10110
เบอร์โทรศัพท์ 02-663-5881-5

Certificate of analysis

No. : QO-24009150

Purchase No.		Reported date : 20/03/2024
Tank number : N6		Tested date : 19/03/2024
Product/Material name : PETRONAS GEAR MEP 460 (209 Lts.)		Received date : 19/03/2024
Batch No. : FL-2412038		

No.	Test item	Test method	Specification	Result	Unit
1	*Appearance	Visual	Bright & Clear	Bright & Clear	-
2	Density @15C	ASTM D4052-15	0.8700 - 0.9500	0.9038	g/cm3
3	Density @30C	ASTM D4052-15	Report	0.8944	g/cm3
4	Kinematic Viscosity @40C	ASTM D445-15	423.20 - 496.80	458.40	mm2/s
5	Kinematic Viscosity @100C	ASTM D445-15	Report	30.84	mm2/s
6	*Viscosity Index	ASTM D2270-10e1	Report	97	-
7	*Demulsibility @82C ml/ml/ml (min)	ASTM D1401-12e1	45 Max	15	Minutes
8	*Foaming : Seq.I @24C, Tendency	ASTM D892-13	25 Max	0	Milliliter
9	*Foaming : Seq.I @24C, Stability	ASTM D892-13	0 Max	0	Milliliter