



บริษัท ปิโตรนาส อินเตอร์ เนชันแนล มาร์เก็ตติ้ง (ประเทศไทย) จำกัด
2 อาคารจัสมิน ซิตี้ ห้องเลขที่ 20A-01 ชั้น 26 ซอยประสานมิตร (สุขุมวิท 23)
ถนน สุขุมวิท แขวงคลองเตยเหนือ เขตวัฒนา กรุงเทพฯ 10110
เบอร์ โทรศัพท์ 02-663-5881-5

CERTIFICATE OF ANALYSIS

Sample Name	: HYDRAULIC AW 46	Report Number	: ALR-COA-2511-11816
Source	: B-018A	Sampling Date/Time	: 22-Nov-2025 14:12
Sample ID	: ALR-2511007891	Sampling By	: LDDL OPERATOR
Batch Number	: 2511221403	Received Date/Time	: 22-Nov-2025 14:17
Vessel/Truck	: -	Sample Tested Date	: 22-Nov-2025 15:40
Sample Type	: Composite	Reported Date	: 23-Nov-2025 00:52

Properties	Test Method	Unit	Specification	Result
Appearance	Visual	-	Bright & Clear	Bright & Clear
ASTM Color	ASTM D 1500	-	Report	L0.5
Density @15 degree C	ASTM D 4052	g/cm3	Report	0.8702
Density @ 30 degree C	ASTM D 4052	g/cm3	Report	0.8607
Kinematic Viscosity @ 40 degree C	ASTM D 445	cSt.	43 - 49	45.92
Kinematic Viscosity @ 100 degree C	ASTM D 445	cSt.	Report	6.823
Viscosity Index	ASTM D 2270	-	95 min.	103
Foaming Characteristic (Sequence I)	ASTM D 892	mL/mL	150/0 max.	Nil/0
Foaming Characteristic (Sequence II)	ASTM D 892	mL/mL	75/0 max.	Nil/0
Foaming Characteristic (Sequence III)	ASTM D 892	mL/mL	150/0 max.	Nil/0
Flash Point (COC)	ASTM D 92	degree C	210 min.	234
Water Content	ASTM D 95	%vol.	Nil	Nil