




G238HAN02.0 Engineering Change Request

GDBU

12th JAN.Y23

AUO Display Plus Engineering Change Request

➤ Engineering Change item

Item	Reflector
As is	TCJ18N
To Be	EST188P

Reflector vendor announced the EOL of current reflector and the material can be supplied only till 2023/E. ADP suggest to change reflector from TorayTCJ18N to EST188P.

➤ Material Comparison

	As is	To be
Thickness(mm)	0.233	0.228
Front side optics	100%	←
Rear side optics (sensor hole)	100%	135%
Friction test	PASS	←
Stress test (500g & 1000g)	PASS	←

AUO Display Plus Engineering Change Request

➤ Optics

Optical Measurement Report												
Originator	chongfeng			Model/PCS		G238HAN02.0/5pcs			Date	2023/1/8		
Test Condition	Lum.,CR,Chromaticity,Uniformity,Gary Scale,V-T,View Angle,RT											
Test System	Detector	Inverter			DC Voltage					Warm up time		
FPM-520-2	SR-UL1R	NA			24V					30 min		
【Test Reason】												
G238HAN02.0 Optics 5pcs												
【Judgement】												
PASS												
Test Items	unit	PSS			23.5°C	23.5°C	23.5°C	23.5°C	23.5°C	-4σ	mean	+4σ
					2023/1/8 9:08	2023/1/8 9:24	2023/1/8 9:53	2023/1/8 10:23	2023/1/8 10:51			
		min	typ	max	V2B4U15GBZZS01	V2B4TY7BEZZS01	V2B4TY7SBZZS01	V2B4TK1SHZZS01	V2B4TY7UGZZS01			
Center Brightness	cd/m ²	240	300		237.1	304.4	299.6	310.5	302.3	266.230	300.8	335.330
Darkness (L0)					0.21	0.22	0.21	0.23	0.23	0.181	0.22	0.258
Contrast Ratio(CR)	---	700	1000		1348.5	1415.2	1423.3	1368.4	1299.7	1168.186	1371.0	1573.836
Chromaticity												
	Wx	0.255	0.235	0.315	0.291	0.295	0.296	0.298	0.295	0.285	0.295	0.305
	Wy	0.272	0.302	0.332	0.308	0.316	0.317	0.320	0.315	0.297	0.315	0.333
	Rx	0.597	0.627	0.657	0.630	0.630	0.631	0.631	0.630	0.628	0.630	0.633
	Ry	0.300	0.330	0.360	0.330	0.331	0.331	0.331	0.331	0.329	0.331	0.333
	Gx	0.268	0.298	0.328	0.301	0.301	0.302	0.302	0.302	0.299	0.301	0.304
	Gy	0.563	0.593	0.623	0.607	0.608	0.608	0.610	0.609	0.605	0.608	0.612
	Bx	0.124	0.154	0.184	0.154	0.154	0.154	0.154	0.154	0.153	0.154	0.155
	By	0.027	0.057	0.087	0.047	0.049	0.049	0.049	0.047	0.044	0.048	0.052
	NTSC	%	72		71.2	71.1	71.3	71.3	71.2	70.981	71.214	71.448
	CCT	---			8291	7780	7682	7534	7799	6676.779	7817.022	8957.264
Uniformity												
L255	ZoneA	9 points		1.250	1.131	1.129	1.137	1.088	1.088	1.017	1.114	1.212
L255	ZoneB	8 points		1.695	1.312	1.293	1.347	1.317	1.296	1.227	1.313	1.398

EC plan



- Current Plan: EC sample will be shipped on 2/B, ADP looks forward to getting customer agreement by the end of 05/2023 and running the EC phase-in.



Tap Into The Possibilities