# CAPRIKOT T-12

**Bituminous Cold Applied Clay Type Emulsion**

## DESCRIPTION:

**Caprickot T-12** is water based bituminous emulsions made from selected grades of bitumen with fibrous fillers. **Caprikot T-12** set within 48 hours and remain plastic on insulation material and take care of vibrations generated from pipes & equipment.

The dried films of **Caprikot T-12** has improved rheological properties. **Caprikot T-12** is tough non-flowing, resilient and strongly adhere to almost all types of surface.

## CHARACTERISTICS:

### Caprikot T–12

**Colour :**
Brown to Chocolate

**Consistency :**
Brushable/Trowel able

**Drying Time**
(Touch) 8 Hrs.
(Through) 48 Hrs.

**Coverage:**
10 kg / Sq. M for 6 mm thickness.

**Dry Film thickness:**
6 mm in 2 coats

**Specific Gravity:**
1.15

**Service Temperature:**
(-) 25°C to 130°C

## APPLICATION:

**Caprikot T-12** is recommended for protecting various types of thermal insulations to maintain their thermal efficiency.

**Caprikot T-12** give a coatings, which when set is joint-less and impervious to moisture. It also possesses plastic characteristics to resist cracking due to vibrations, temperature fluctuations.

### Advantages:

- Excellent vapour barriers.
- Retains thermal efficiency during all weather conditions.
- Economical and effective insulation material.
- Solvent free and hence eco-friendly and non-toxic.

**NOTE:** The properties and parameter closely resembles to Fos**r 90-07/ 90-10. The properties may change depending on specific requirement.

# CAPRIKOT T-14

**Bituminous Cold Applied Clay Type Emulsion**

## DESCRIPTION:

**Caprickot T-14** is water based bituminous emulsions made from selected grades of bitumen with fibrous fillers. **Caprikot T-14** set within 48 hours and remain plastic on insulation material and take care of vibrations generated from pipes & equipment.

The dried films of **Caprikot T-14** have improved rheological properties. **Caprikot T-14** is tough non- flowing, resilient and strongly adhere to almost all types of surface.

## CHARACTERISTICS:

**Colour:**
Brown to Chocolate

**Consistency:**
Brush able/Trowel able

**Drying Time**

| | |
|---|---|
| (Touch) | 8 Hrs. |
| (Through) | 48 Hrs. |

**Average Non Volatile:**
62% ± 2 by weight

**Coverage:**
10-12 kg / Sq. M for 6 mm thickness.

**Dry Film thickness:**
6 mm in 2 coats

**Specific Gravity:**
1.25 ± 0.05 kg/l

**Service Temperature:**
(-)23°C to 180°C

**Water Vapour Permeance:**
≥ 1 perms @ 1.6 mm DFT

**SURFACE BURNING CHARACTERISTICS (ASTM E 84-2022) – dry material**

| | |
|---|---|
| Flame Spread: | 05 |
| Smoke Developed: | 50 |

## APPLICATION:

**Caprikot T-14** is recommended for protecting various types of thermal insulations to maintain their thermal efficiency.

**Caprikot T-14** gives a coatings, which when set is joint-less and impervious to moisture. It also possesses plastic characteristics to resist cracking due to vibrations, temperaturefluctuations.

**Advantages:**

- Excellent vapour barriers.
- Retains thermal efficiency duringall weather conditions.
- Economical and effective insulationmaterial.
- Solvent free and hence eco-friendlyand non-toxic.