Thiagarajar Mills (P) Ltd., Kappalur.

USTER® HVI 1000

System Testing - Individual Tests

Lot ID	SRI KUMARAN FIBRE MILLS 3	Catalog	
Operator		HVI SW Version	3.6.0.107
Print Date	30-Sep-24	Serial Number	1311272
Print Time	12:43:19PM	Test Mode	4
Short/Weak Reference	Upland	Long/Strong Reference	Pima

Bale ID	SCI	Grade	Mst [%]	Mic	Mat [mat1]	SL2 [mm] (MC)	UR [%] (MC)	SF [%]	Str [g/tex] (MC)	Elg [%]	Rd	+b	CGrd Upland	TrCnt	TrAr [%]	TrID TrGrd	Amt
KEP-150BALES/1	161		8.3	4.84	0.88	29.62	51.1	8.3	23.4	5.2	79.1	9.8	11-4	7	0.08	1	545
KEP-150BALES/2	158		8.1	4.63	0.87	29.27	51.1	8.4	22.0	5.4	79.0	9.2	21-1	13	0.21	2	591
KEP-150BALES/3	144		8.2	4.84	0.88	29.91	49.4	8.7	22.7	5.5	78.2	9.2	21-4	14	0.34	3	574
KEP-150BALES/4	146		8.0	4.66	0.87	29.25	49.4	8.6	23.1	5.4	79.0	9.1	21-1	13	0.25	2	504
n	4																
Average	152		8.1	4.74	0.88	29.51	50.3	8.5	22.8	5.4	78.8	9.3	21-1	12	0.22	2	554
Std.Dev.	8		0.1	0.11	0.00	0.31	1.0	0.2	0.6	0.1	0.4	0.3		3	0.11		38.1
CV%	5.5		1.4	2.3	0.4	1.1	1.9	2.3	2.6	2.1	0.5	3.7		27.2	49.1		6.9
Q99% +/-	25		0.3	0.32	0.01	0.91	2.8	0.6	1.7	0.3	1.1	1.0		9	0.32		111.2
Min	144		8.0	4.63	0.87	29.25	49.4	8.3	22.0	5.2	78.2	9.1		7	0.08		504
Max	161		8.3	4.84	0.88	29.91	51.1	8.7	23.4	5.5	79.1	9.8		14	0.34		591

Thiagarajar Mills (P) Ltd., Kappalur.

System Testing - Individual Tests

USTER® HVI 1000

Lot ID	SRI KUMARAN FIBRE	Catalog	
Operator		HVI SW Version	3.6.0.107
Print Date	15-Oct-24	Serial Number	1311272
Print Time	1:07:45PM	Test Mode	4
Short/Weak Reference	Upland	Long/Strong Reference	Pima

(2)

Bale ID	SCI	Grade	Mst [%]	Mic	Mat [mat1]	SL2 [mm] (MC)	UR [%] (MC)	SF [%]	Str [g/tex] (MC)	Elg [%]	Rd	+b	CGrd Upland	TrCnt	TrAr [%]	TrID TrGrd	Amt
SHIVA-110BALES/1	121		9.3	4.96	0.88	28.81	46.7	10.4	23.8	5.3	79.7	8.5	21-1	7	0.10	1	498
SHIVA-110BALES/2	141		9.2	4.94	0.88	30.45	49.0	9.0	22.8	5.6	80.1	8.5	21-1	3	0.05	1	668
SHIVA-110BALES/3	138		9.2	4.84	0.88	29.29	48.6	9.3	23.3	5.6	79.8	8.8	21-1	10	0.19	2	540
SHIVA-110BALES/4	165		9.2	4.98	0.88	30.14	52.3	8.0	21.2	6.0	80.6	8.7	21-1	12	0.21	2	654
n	4																
Average	141		9.2	4.93	0.88	29.68	49.1	9.2	22.8	5.6	80.1	8.6	21-1	8	0.14	1	590
Std.Dev.	18		0.1	0.06	0.00	0.76	2.3	1.0	1.1	0.3	0.4	0.1		4	0.08		84.0
CV%	12.7		0.8	1.3	0.3	2.5	4.7	10.9	5.0	4.8	0.5	1.5		48.9	54.9		14.2
Q99% +/-	52		0.2	0.18	0.01	2.21	6.8	2.9	3.3	0.8	1.1	0.4		11	0.22		245.2
Min	121		9.2	4.84	0.88	28.81	46.7	8.0	21.2	5.3	79.7	8.5		3	0.05		498
Max	165		9.3	4.98	0.88	30.45	52.3	10.4	23.8	6.0	80.6	8.8		12	0.21		668

Thiagarajar Mills (P) Ltd., Kappalur.

System Testing - Individual Tests

USTER® HVI 1000

Lot ID	SRI KUMARAN FIBRE MILLS2
Operator	CTL
Print Date	16-Oct-24
Print Time	2:55:00PM
Short/Weak Reference	Upland
Catalog	H
HVI SW Version	3.6.0.107
Serial Number	1311272
Test Mode	4
Long/Strong Reference	Pima

3

Bale ID	SCI	Grade	Mst [%]	Mic	Mat [mat1]	SL2 [mm]	UR (MC) [%]	SF (MC) [%]	Str [g/tex]	Elg [%]	Rd	+b	CGrd Upland	TrCnt	TrAr [%]	TrID TrGrd	Amt
GOGI/1	148		7.6	4.22	0.86	30.66	49.5	8.8	21.5	5.8	77.8	8.4	31-1	11	0.16	1	715
GOGI/2	134		7.5	4.14	0.86	30.53	47.1	9.3	23.7	5.8	78.0	8.6	31-1	12	0.21	2	589
GOGI/3	150		7.4	4.25	0.86	30.45	49.7	8.8	22.2	5.6	76.3	8.8	31-3	8	0.12	1	574
GOGI/4	154		7.5	4.18	0.86	30.34	49.5	8.7	23.7	5.4	77.7	8.3	31-1	14	0.22	2	648
n	4																
Average	146		7.5	4.20	0.86	30.50	49.0	8.9	22.8	5.7	77.5	8.5	31-1	11	0.18	2	632
Std.Dev.	9		0.1	0.05	0.00	0.13	1.3	0.3	1.1	0.2	0.8	0.2		3	0.05		64.2
CV%	6.0		0.7	1.2	0.2	0.4	2.6	3.2	4.9	3.3	1.0	2.8		22.2	28.2		10.2
Q99% +/-	26		0.2	0.14	0.01	0.39	3.7	0.8	3.2	0.8	2.3	0.7		7	0.14		167.4
Min	134		7.4	4.14	0.86	30.34	47.1	8.7	21.5	5.4	76.3	8.3		8	0.12		574
Max	154		7.6	4.25	0.86	30.66	49.7	9.3	23.7	5.8	78.0	8.8		14	0.22		715

Thiagarajar Mills (P) Ltd., Kappalur.

System Testing - Individual Tests

USTER® HVI 1000

Lot ID	SRI KUMARAN FIBRE MILLS1	Catalog	H
Operator	CTL	HVI SW Version	3.6.0.107
Print Date	16-Oct-24	Serial Number	1311272
Print Time	2:52:02PM	Test Mode	4
Short/Weak Reference	Upland	Long/Strong Reference	Pima

4

Bale ID	SCI	Grade	Mst [%]	Mic	Mat [mat1]	SL2 [mm] (MC)	UR [%] (MC)	SF [%]	Str [g/tex] (MC)	Elg [%]	Rd	+b	CGrd Upland	TrCnt	TrAr [%]	TrID TrGrd	Amt
NOOR/1	111		7.8	4.36	0.86	29.63	45.7	10.5	21.5	5.8	75.9	8.9	31-3	13	0.10	1	750
NOOR/2	149		7.2	4.40	0.87	30.11	49.6	8.8	23.0	5.7	75.6	8.6	31-2	15	0.21	2	631
NOOR/3	150		7.3	4.27	0.86	30.42	49.4	8.8	23.0	5.8	77.5	8.8	31-1	13	0.15	1	723
NOOR/4	132		7.2	4.46	0.87	29.84	47.7	9.3	23.0	5.7	75.8	9.0	31-3	17	0.48	4	628
n	4																
Average	135		7.4	4.37	0.86	30.00	48.1	9.4	22.6	5.7	76.2	8.8	31-3	15	0.24	2	683
Std.Dev.	18		0.3	0.08	0.00	0.34	1.8	0.8	0.7	0.1	0.9	0.2		2	0.17		62.8
CV%	13.7		3.6	1.8	0.3	1.1	3.8	8.7	3.3	1.0	1.2	2.0		13.2	72.1		9.2
Q99% +/-	54		0.8	0.23	0.01	1.00	5.3	2.4	2.2	0.2	2.6	0.5		6	0.49		183.3
Min	111		7.2	4.27	0.86	29.63	45.7	8.8	21.5	5.7	75.6	8.6		13	0.10		628
Max	150		7.8	4.46	0.87	30.42	49.6	10.5	23.0	5.8	77.5	9.0		17	0.48		750

Thiagarajar Mills (P) Ltd., Kappalur.

System Testing - Individual Tests

USTER® HVI 1000

Lot ID	SRI KUMARAN FIBRE MILLS 1
Operator	CTL
Print Date	10-Oct-24
Print Time	12:42:36PM
Short/Weak Reference	Upland
Catalog	H
HVI SW Version	3.6.0.107
Serial Number	1311272
Test Mode	4
Long/Strong Reference	Pima

5

Bale ID	SCI	Grade	Mst [%]	Mic	Mat [mat1]	SL2 [mm] (MC)	UR [%] (MC)	SF [%]	Str [g/tex] (MC)	Elg [%]	Rd	+b	CGrd Upland	TrCnt	TrAr [%]	TrID TrGrd	Amt
SVT 84BALES/LOT NO-1/1	152		7.2	3.85	0.86	28.01	50.0	9.3	21.5	4.8	81.1	8.5	21-1	3	0.05	1	681
SVT 84BALES/LOT NO-1/2	154		7.2	3.87	0.86	29.04	50.0	8.8	21.9	4.8	78.3	8.8	31-1	14	0.15	1	546
SVT 84BALES/LOT NO-1/3	170		7.2	3.58	0.85	28.90	51.2	8.8	22.7	5.0	80.0	8.0	31-1	15	0.15	1	642
SVT 84BALES/LOT NO-1/4	151		7.2	3.69	0.85	27.99	49.8	9.2	20.9	4.9	80.9	8.8	11-2	8	0.07	1	561
n	4																
Average	157		7.2	3.74	0.85	28.49	50.2	9.0	21.7	4.9	80.1	8.5	21-1	10	0.11	1	608
Std.Dev.	9		0.0	0.14	0.00	0.56	0.6	0.3	0.8	0.1	1.3	0.4		6	0.05		64.6
CV%	5.6		0.5	3.7	0.5	2.0	1.2	3.1	3.6	2.4	1.6	4.2		56.0	50.1		10.6
Q99% +/-	26		0.1	0.41	0.01	1.64	1.8	0.8	2.3	0.3	3.8	1.0		16	0.15		188.8
Min	151		7.2	3.58	0.85	27.99	49.8	8.8	20.9	4.8	78.3	8.0		3	0.05		546
Max	170		7.2	3.87	0.86	29.04	51.2	9.3	22.7	5.0	81.1	8.8		15	0.15		681

Thiagarajar Mills (P) Ltd., Kappalur.

System Testing - Individual Tests

USTER® HVI 1000

Lot ID	SRI KUMARAN FIBRE MILLS 2
Operator	
Print Date	30-Sep-24
Print Time	12:43:12PM
Short/Weak Reference	Upland

Catalog	
HVI SW Version	3.6.0.107
Serial Number	1311272
Test Mode	4
Long/Strong Reference	Pima

(6)

Bale ID	SCI	Grade	Mst [%]	Mic	Mat [mat1]	SL2 [mm] (MC)	UR [%] (MC)	SF [%]	Str [g/tex] (MC)	Elg [%]	Rd	+b	CGrd Upland	TrCnt	TrAr [%]	TrID TrGrd	Amt
RCC-140BALES/1	162		8.8	4.90	0.88	30.45	50.8	8.3	24.4	5.6	80.4	9.1	21-1	10	0.19	2	590
RCC-140BALES/2	149		8.7	4.90	0.88	29.82	49.9	9.0	23.6	5.9	77.6	9.2	21-4	22	0.22	2	640
RCC-140BALES/3	141		8.8	4.87	0.88	30.88	48.8	8.6	22.9	5.6	78.1	9.2	21-4	13	0.34	3	685
RCC-140BALES/4	141		8.5	4.82	0.88	29.84	48.4	9.4	24.6	5.5	79.9	8.7	21-1	16	0.34	3	517
n	4																
Average	148		8.7	4.87	0.88	30.25	49.5	8.8	23.9	5.7	79.0	9.1	21-1	15	0.27	3	608
Std.Dev.	10		0.2	0.04	0.00	0.51	1.1	0.5	0.7	0.2	1.4	0.3		5	0.08		72.0
CV%	6.7		1.8	0.8	0.1	1.7	2.2	5.3	3.1	3.0	1.7	2.9		33.6	29.0		11.8
Q99% +/-	29		0.5	0.12	0.00	1.49	3.1	1.4	2.2	0.5	4.0	0.8		15	0.23		210.3
Min	141		8.5	4.82	0.88	29.82	48.4	8.3	22.9	5.5	77.6	8.7		10	0.19		517
Max	162		8.8	4.90	0.88	30.88	50.8	9.4	24.6	5.9	80.4	9.2		22	0.34		685

Nagarajar Mills (P) Ltd., Kappalur.

System Testing - Individual Tests

USTER® HVI 1000

Lot ID	KUMARAN FIBRE MILLS
Operator	
Print Date	16-Sep-24
Print Time	12:33:44PM
Short/Weak Reference	Upland
Catalog	
HVI SW Version	3.6.0.107
Serial Number	1311272
Test Mode	4
Long/Strong Reference	Pima

Bale ID	SCI	Grade	Mst [%]	Mic	Mat [mat1]	SL2 [mm] (MC)	UR [%] (MC)	SF [%]	Str [g/tex] (MC)	Elg [%]	Rd	+b	CGrd Upland	TrCnt	TrAr [%]	TriD TrGrd	Amt
MRVL-LOT SAMPLE/1	138		7.3	5.02	0.89	28.93	49.1	8.8	22.7	5.0	80.0	8.2	21-2	13	0.14	1	490
MRVL-LOT SAMPLE/2	163		7.3	5.05	0.88	29.82	52.0	7.8	22.3	5.2	79.1	8.8	21-2	16	0.33	3	538
MRVL-LOT SAMPLE/3	159		7.3	4.98	0.88	29.10	51.9	8.2	21.8	5.4	77.6	8.7	31-1	6	0.35	3	598
MRVL-LOT SAMPLE/4	153		7.2	5.10	0.88	30.11	51.1	7.7	21.4	5.6	79.4	8.4	31-1	36	0.53	4	512
n	4																
Average	153		7.3	5.04	0.88	29.49	51.0	8.1	22.0	5.3	79.0	8.5	21-2	18	0.34	3	535
Std.Dev.	11		0.1	0.05	0.00	0.57	1.3	0.5	0.5	0.3	1.0	0.3		13	0.16		46.7
CV%	7.1		0.7	1.0	0.2	1.9	2.6	6.0	2.4	5.2	1.3	3.4		72.5	47.2		8.7
Q99% +/-	32		0.2	0.15	0.01	1.65	3.9	1.4	1.5	0.8	3.0	0.8		36	0.47		136.3
Min	138		7.2	4.98	0.88	28.93	49.1	7.7	21.4	5.0	77.6	8.2		6	0.14		490
Max	163		7.3	5.10	0.89	30.11	52.0	8.8	22.7	5.6	80.0	8.8		36	0.53		598

Lot ID SRI KUMARAN FIBRE MILLS 1
Operator CTL
Print Date 20-Sep-24
Print Time 1:47:35PM
Short/Weak Reference Upland

USTER® *HVI 1000*

Catalog H
HVI SW Version 3.6.0.107
Serial Number 1311272
Test Mode 4
Long/Strong Reference Pima

(8)

Bale ID	SCI	Grade	Mst [%]	Mic	Mat [mat1]	SL2 [mm]	UR (MC) [%]	SF [%]	Str [g/tex] (MC)	Elg [%]	Rd	+b	CGrd Upland	TrCnt	TrAr [%]	TrID TrGrd	Amt
VG COTTON-LOT SAMPLE/1	164		8.4	4.10	0.87	28.46	52.3	8.1	21.4	4.5	70.9	9.2	42-1	33	3.68	8	686
VG COTTON-LOT SAMPLE/2	172		7.7	4.22	0.87	28.68	51.8	8.4	25.6	4.6	70.9	9.2	42-1	33	3.79	8	567
VG COTTON-LOT SAMPLE/3	140		7.6	4.43	0.87	28.18	49.1	9.3	23.9	4.5	71.6	9.5	42-1	39	3.49	8	501
VG COTTON-LOT SAMPLE/4	149		7.7	4.08	0.87	28.48	49.6	9.1	23.3	4.4	73.6	9.7	32-1	18	0.28	3	510
n 4																	
Average	156		7.9	4.21	0.87	28.45	50.7	8.7	23.6	4.5	71.8	9.4	42-1	31	2.81	8	566
Std.Dev.	14		0.4	0.16	0.00	0.21	1.6	0.6	1.7	0.1	1.3	0.2		9	1.69		85.2
CV%	9.1		4.6	3.7	0.5	0.7	3.1	6.6	7.4	1.6	1.7	2.3		29.1	60.2		15.0
Q99% +/-	41		1.1	0.46	0.01	0.60	4.6	1.7	5.1	0.2	3.7	0.6		26	4.94		248.7
Min	140		7.6	4.08	0.87	28.18	49.1	8.1	21.4	4.4	70.9	9.2		18	0.28		501
Max	172		8.4	4.43	0.87	28.68	52.3	9.3	25.6	4.6	73.6	9.7		39	3.79		686

Thiagarajar Mills (P) Ltd., Kappalur.
System Testing - Individual Tests

USTER® HVI 1000

Lot ID SRI KUMARAN FIBRE 3
Operator
Print Date 13-Sep-24
Print Time 1:48:20PM
Short/Weak Reference Upland

Catalog
HVI SW Version 3.6.0.107
Serial Number 1311272
Test Mode 4
Long/Strong Reference Pima

9

Bale ID	SCI	Grade	Mst [%]	Mic	Mat [mat1]	SL2 [mm] (MC)	UR [%] (MC)	SF [%]	Str [g/tex] (MC)	Elg [%]	Rd	+b	CGrd Upland	TrCnt	TrAr [%]	TrID TrGrd	Amt
VPT-LOT SAMPLE-50BALES/1	120		7.2	4.19	0.87	28.56	46.8	10.6	21.9	4.9	73.9	10.5	32-1	8	0.10	1	578
VPT-LOT SAMPLE-50BALES/2	115		7.3	4.06	0.86	27.93	46.5	11.0	21.8	4.8	71.4	10.8	33-2	18	0.15	1	578
VPT-LOT SAMPLE-50BALES/3	91		7.3	4.18	0.87	28.01	43.3	12.0	22.8	4.4	73.5	10.8	22-2	15	0.45	4	522
VPT-LOT SAMPLE-50BALES/4	118		7.3	4.20	0.87	28.35	46.9	10.5	21.8	4.8	71.2	10.7	33-2	17	0.27	2	551
n 4																	
Average	111		7.3	4.16	0.87	28.21	45.9	11.0	22.1	4.7	72.5	10.7	32-1	15	0.24	2	557
Std.Dev.	13		0.0	0.07	0.00	0.29	1.7	0.7	0.5	0.2	1.4	0.1		5	0.16		26.7
CV%	12.1		0.5	1.6	0.3	1.0	3.8	6.4	2.2	4.6	1.9	1.2		31.1	64.2		4.8
Q99% +/-	39		0.1	0.20	0.01	0.86	5.0	2.1	1.4	0.6	4.1	0.4		13	0.45		78.1
Min	91		7.2	4.06	0.86	27.93	43.3	10.5	21.8	4.4	71.2	10.5		8	0.10		522
Max	120		7.3	4.20	0.87	28.56	46.9	12.0	22.8	4.9	73.9	10.8		18	0.45		578

Thiagarajar Mills (P) Ltd., Kappalur.

System Testing - Individual Tests

USTER® HVI 1000

Lot ID SRI KUMARAN FIBRE MILLS
Operator CTL
Print Date 18-Sep-24
Print Time 12:49:02PM Seed Cotton
Short/Weak Reference Upland

Catalog H
HVI SW Version 3.6.0.107
Serial Number 1311272
Test Mode 4
Long/Strong Reference Pima

10

Bale ID	SCI	Grade	Mst [%]	Mic	Mat [mat1]	SL2 [mm] (MC)	UR [%] (MC)	SF [%]	Str [g/tex] (MC)	Elg [%]	Rd	+b	CGrd Upland	TrCnt	TrAr [%]	TrID TrGrd	Amt
K.S.SEED COTTON/1	166		6.7	3.56	0.85	29.11	50.0	9.1	24.2	4.7	82.2	10.2	11-3	9	0.08	1	748
K.S.SEED COTTON/2	170		6.5	3.46	0.85	29.01	49.8	9.1	26.0	4.6	81.3	10.1	11-3	12	0.12	1	588
K.S.SEED COTTON/3	162		6.4	3.46	0.85	28.16	49.7	9.5	24.2	4.5	81.4	10.0	11-3	12	0.13	1	585
K.S.SEED COTTON/4	166		6.3	3.72	0.86	29.32	50.3	8.7	23.3	4.6	82.4	9.9	11-1	8	0.12	1	588
n 4																	
Average	166		6.5	3.55	0.85	28.90	50.0	9.1	24.4	4.6	81.8	10.0	11-1	10	0.11	1	627
Std.Dev.	3		0.2	0.12	0.00	0.51	0.3	0.4	1.1	0.1	0.6	0.1		2	0.02		80.5
CV%	2.0		2.9	3.4	0.3	1.8	0.6	3.8	4.5	1.9	0.7	1.2		20.1	19.7		12.8
Q99% +/-	10		0.6	0.36	0.01	1.48	0.8	1.0	3.2	0.3	1.6	0.3		6	0.06		235.1
Min	162		6.3	3.46	0.85	28.16	49.7	8.7	23.3	4.5	81.3	9.9		8	0.08		585
Max	170		6.7	3.72	0.86	29.32	50.3	9.5	26.0	4.7	82.4	10.2		12	0.13		748