

Office: 308, 3rd Floor, Lok Center, Marol Maroshi Road, Marol, Andheri (E), Mumbai-400059.



## **SPECIFICATIONS: POLY ETHYLENE GLYCOL 200**

CHARACTERSTIC	UNIT	QUANTITY(MT):AVERAGE VALUE
Hydroxyl Number as mgKOH/g	С	544.200
PH (5% Aq. Solution) at 25 Deg C	NOU	5.630
AVERAGE MW	WTP	206.200
Colour at 25 Deg C	Pt-Co	10.000
Residual EO	Wt ppm	0.580
1,4 Dioxane	Wt ppm	0.700
Water	Wt %	0.110
Acidity as mgKOH/g		0.140