SWADI®
a step ahead...

LockTile Pro EP - TA08

Floor & Wall Epoxy-based Tile Adhesive used for Ceramic, Vitrified, & Stones.

Conforms to IS 15477:2019 Standards as a Type 5T Adhesive.

Description

Epoxy-based, high-performance tile adhesive suitable for fixing large format tiles and heavy-duty applications. Ideal for vitrified, porcelain, ceramic, glass mosaic, and natural stone tiles on both interior and exterior walls and floors. Provides exceptional bond strength, chemical resistance, and water resistance, making it suitable for industrial, commercial, and high-moisture environments.

Standard Compliance

Confirms to **IS 15477: 2019 Type 5** "Specification for Adhesives for use with Ceramic, Mosaic and Stone Tiles"
Classified as per requirements for cementitious adhesives (C), Confirms to **EN 12004 - R2**, Reaction resin adhesives.

Where to Use

TA08 is a higher-grade epoxy adhesive designed for demanding tile and stone installations, including granites and marbles. It is specifically used for large-format tiles exceeding 4x4 feet. Ideal for residential, commercial, and industrial spaces, it works effectively on substrates like concrete, cement screeds, plastered surfaces, Metal floors and walls, Plywood, Tile on tile.

Advantages

- Superior bond and impact resistant
- Easy to clean when fresh
- Non-Sag formula for vertical applications
- Excellent grip & stability
- Can be applied to heights where cement base adhesives have limitations

Product Data

Classification of adhesive	Type 5T I As per IS 15477:2019
Appearance	After mix, Brown Colour
Pot life 27 ± 2°C IS 15477:2019	30 - 40 Minutes
Setting time IS 15477:2019	24 hours
Foot traffic	After 24 hours
Grouting	After 8h for wall & 24h for floor

Technical Data

Properties tested as per IS 15477: 2019 @ 27 ± 2°C

Characteristic	Min. requirement	Test result
Tensile adhesion strength, 28 d SC Dry condition	≥ 2.0 N/mm²	3.1 N/mm²
Shear adhesion strength, 28 d SC Dry condition	6.0 N/mm²	8.5 N/mm²
Open time	N.A.	25 minutes

Properties tested as per EN 12004 @ 24 ± 2°C

Characteristic	Min. requirement	Test result
Shear adhesion strength, 28 d SC Water immersion Heat ageing	≥ 2.0 N/mm² ≥ 2.0 N/mm²	9.1 N/mm² 8.9 N/mm²
Open time	≥ 0.5 N/mm² after not less than 20 min	4 N/mm²

Coverage

- 4 - 5 kg/m² at 3mm thickness
- 6 - 7 kg/m² at 5mm thickness

LockTile Pro EP - TA08

Coverage will vary depending on the surface condition, tile size, and application method. For optimal results, ensure the surface is smooth, level, and free from defects..

Surface Preperation

- The surface to be tiled should be sound and thoroughly cleaned.
- Surface should be free from oil, wax, grease, curing compound, moisture, efflorescence, etc.,

Mixing

- Ratio 1: 0.5: 4.5 (Resin: Hardener: Filler), Mix these three components thoroughly and apply with a notched trowel within the open time 25 minutes.
- Do not add water or any other solvents to thin the material.

Application

- Spread not more than the area which can be tiled within the open time of the adhesive.
- Spread adhesive to a thickness of approx. 3-6mm and comb with notched trowel.
- Back buttering is required for large-format tiles.
- Start placing tiles on the surface to be tiled, tap the tiles properly to ensure complete coverage of the backside of tiles and to eliminate the possibility of any air voids.
- Keep joints between two tiles using spacers.
- Start filling joints only after 24 hrs. with SWADI Epoxy/Cementitious tile grouts which will enhance adhesion to tile edges, increase water-resistance and improves flexibility.

Cleaning

Clean any excess epoxy adhesive from the tile surface and joints immediately using a damp cloth or wet sponge before it hardens . The hardened adhesive can be removed from tools mechanically.

Precautions

- Use protective gloves during entire application
- Do not add water or solvents to the mix.
- Do not overmix, and apply within open time.
- Use thinner if material stains are huge.
- Do not breathe fumes, wear necessary PPE kit.

Packaging

24 Kg Pack, which includes 4 Kg Resin, 2 Kg Hardener, and 18 Kg filler.

Shelf Life

12 months when stored in normal dry conditions, store in dry closed container for long life time.

Storage and Handling Guidelines

The product should be stored in a dry, well-ventilated area, away from moisture, direct sunlight, and children, and in compliance with national regulations. Ensure the packaging is tightly sealed to prevent contamination or moisture ingress, and store it within the recommended temperature range of 5°C to 35°C. Handle the product with care, avoiding direct contact with skin and eyes, and wear appropriate protective equipment such as gloves and masks to prevent inhalation of dust. Use the product as per the instructions provided on the packaging for best results.

Environmental, Health, and Safety Information

For comprehensive information regarding the safe transportation, handling, storage, and disposal of this chemical product, please refer to the accompanying Safety Data Sheet (SDS). The SDS contains detailed information about physical properties, environmental impacts, toxicological hazards, and other safety-related factors. It is crucial to read the current SDS before using any product.

Disclaimer

The information provided in this datasheet is based on our extensive experience and is given in good faith to assist you. However, we reserve the right to update this information at any time without prior notice due to our ongoing research and development efforts. While we guarantee the consistent quality of our products, we cannot be held responsible for any losses or damages that may arise from their use if site conditions or the execution of work are not properly managed. This data sheet becomes invalid upon the publication of a new edition, and please contact us for the latest version. Please note that we do not provide any warranties regarding the results of our products in specific applications, as the storage, handling, and application of materials are factors beyond our control.

While we guarantee the consistent quality of our products, we cannot be held responsible for any losses or damages that may arise from their use if site conditions or the execution of work are not properly managed. This data sheet becomes invalid upon the publication of a new edition, and please contact us for the latest version. Please note that we do not provide any warranties regarding the results of our products in specific applications, as the storage, handling, and application of materials are factors beyond our control.

Contact Information

For immediate orders or enquires, contact our **24/7 support team at +91 8792919513 or enquiry@swadigroup.co.in**. For additional support options and resources, please visit our website at swadigroup.co.in

SWADI MINERALS AND CHEMICALS
an ISO 9001:2015 & ISO 14001:2015 certified company
Sy.no 70/1, Vishwaneedam post, Gollarahatti
Magadi main road, Bengaluru – 560091
Tel: +91 8884492928
Email: enquiry@swadigroup.co.in
Website: swadigroup.co.in

Product Data Sheet
LockTile Pro EP - TA08
April 2024, Version 011.05.10900000000008

SWADI®
a step ahead...