PERFORMANCE
WATERPROOFING SYSTEMS

SWADI®
a step ahead...

AquaBlend 2K - Standard

Acrylic Polymer-Modified Cementitious Coating for General Waterproofing

Description

AquaBlend 2K - Standard is a two-component, cementitious waterproofing coating system formulated with a blend of high-grade cement, graded fillers, performance-enhancing additives, and an acrylic polymer dispersion. The system forms a durable and flexible coating with strong adhesion to concrete and masonry surfaces, making it suitable for underlay waterproofing, Roofs, and other horizontal substrates.

Standard Compliance

Complies with Standards ASTM D 638, ASTM C 1305, ASTM D 2369, ASTM D 412, ASTM E 96.

Where to Use

1) For underlay waterproofing of roof slabs, sunken slabs, basements, water tanks, sunshades, etc. 2) Terrace waterproofing. 3) Interior & Exterior.

Advantages

- Superior Chemical bonding.
- Higher abrasion resistance.
- Well optimized polymer - to - cement ratio for improved flexibility and adhesion.
- High flexural/tensile strength to control cracking.
- Resists extreme hydro-static pressure.
- Easy to apply & cost-effective.

Product Data

Chemical type	Part A: Acrylic polymer Part B: Blend of portland cement, mineral fillers and performance additives.
Appearance	Part A: Milky white Part B: Grey powder.
Mix ratio	1 : 4.4 (Part A liquid : Part B powder) by weight addition water as per mentioned in mixing instructions.
Mix density	Part A: ~1.06 gm/cc Part B: ~1.83 gm/cc Mix density (Part A + Part B + Water 15%): ~ 1.78 gm/cc
Solid content by weight ASTM D 2369	~80%
Application temperature	10°C ≤ T ≤ 40°C

Technical Data

Tensile strength ASTM D 638	~1.0 n/mm²
Crack bridging capacity ASTM C 1305	≥ 1.3 mm
Elongation at break ASTM D 412	~50%
Bond strength ASTM D 7234	≥ 1.0 mpa
Water permeability DIN 1048	No water penetration at 5 bar pressure for 48 hours
Resistance to water vapor transmission ASTM E 96	<5 g/m²/24 hrs.
Foot traffic ISO 13007	24 hours at 25°C
Coverage	1.5 kg / 1 sqm / 2 coats @ 0.8 to 1 mm thickness

Application Instructions

Surface Preparation

The object of the surface preparation is to achieve a clean sound surface with a good mechanical key. All substrates should be cleaned and free of dust, plaster, oil, paint, grease, corrosion deposits, and any other deleterious substances. Laitance should be removed by mechanical means. Smooth substrates must be mechanically roughened e.g., by scabbling, needle gun

AquaBlend 2K - Standard

Corroded reinforcing steel should be exposed around its full circumference and cleaned to remove all loose scale and corrosion deposits. It is always preferably to clean the steel to a bright condition. Use of emery cloth, grit or sand blasting is recommended.

Mixing

1. Mix the entire pack quantity at once to achieve optimal performance properties.
2. Add 15% water (1.125 liters) to the 7.5 kg kit.
3. Combine the powder and liquid components, and mix thoroughly until a smooth, uniform consistency is obtained.
4. For crack repair, use AquaBlend 2K Standard in dry-pack form to fill micro and macro cracks before applying the coating.

Application

1. Pre-saturate the surface with clean water before applying the mixed material to ensure better adhesion.
2. Apply the first coat evenly over the prepared surface.
3. Allow the first coat to dry for 6 to 7 hours before applying the second coat.
4. Apply the second coat in a direction perpendicular to the first coat to ensure full coverage.

Important Considerations for SWADI AquaBlend 2K - Standard application

• Ensure the surface is clean, free of dust, grease, and loose particles before starting. • Do not add excess water, as this can compromise the performance of the coating. • Apply the material in recommended thicknesses to achieve the desired waterproofing properties. • Protect the coated surface from direct rain or water for at least 24 to 48 hours after application. • Avoid application at temperatures below 10°C or above 40°C to ensure proper curing and adhesion. • Apply the second coat in a direction perpendicular to the first coat to ensure full coverage.

Cleaning

Tools and equipment should be washed with water immediately after use.

Shelf Life

2K Standard has a shelf life of 12 months if kept in a dry store in unopened condition.

Packaging

- Industrial pack: 27kg Kit - 22 Kg (Powder), 5 Kg (Acrylic polymer)
- Retail pack: 7.5 Kg Kit – 6.11 Kg (Powder), 1.38 Kg (Acrylic polymer)

Condition of Sale

Sold subject to the company's condition of sale which are available on request.

Storage and Handling Guidelines

The product should be stored as per national regulations in a cool, dry, and well-ventilated area, away from direct sunlight and extreme temperatures. Keep it out of reach of children. Ensure the container is tightly sealed when not in use. Handle with care to avoid contamination. Stir well before use and apply as per the recommended guidelines.

Environmental, Health, and Safety Information

For comprehensive information regarding the safe transportation, handling, storage, and disposal of this chemical product, please refer to the accompanying Safety Data Sheet (SDS). The SDS contains detailed information about physical properties, environmental impacts, toxicological hazards, and other safety-related factors. It is crucial to read the current SDS before using any product.

Disclaimer

The information provided in this datasheet is based on our extensive experience and is given in good faith to assist you. However, we reserve the right to update this information at any time without prior notice due to our ongoing research and development efforts. While we guarantee the consistent quality of our products, we cannot be held responsible for any losses or damages that may arise from their use if site conditions or the execution of work are not properly managed. This data sheet becomes invalid upon the publication of a new edition, and please contact us for the latest version. Please note that we do not provide any warranties regarding the results of our products in specific applications, as the storage, handling, and application of materials are factors beyond our control.

Contact Information

For immediate orders or enquires, contact our **24/7 support team at +91 8792919513 or enquiry@swadigroup.co.in.** For additional support options and resources, please visit our website at swadigroup.co.in

SWADI MINERALS AND CHEMICALS
an ISO 9001:2015 & ISO 14001:2015 certified company
Sy.no 70/1, Vishwaneedam post, Gollarahatti
Magadi main road, Bengaluru – 560091
Tel: +91 8884492928
Email: enquiry@swadigroup.co.in
Website: swadigroup.co.in

Product Data Sheet
AquaBlend 2K - Standard
October 2025, Version 011.05.11000000000040