PERFORMANCE
WATERPROOFING SYSTEMS

SWADI®
a step ahead...

AquaSecure 120

Crystalline Waterproofing Technology

Description

AquaSecure 120 is a unique chemical treatment for the waterproofing, protection, and repair of concrete. Aqua Secure consists of Portland cement, finely graded sand and active proprietary chemicals; it is applied as a cementitious slurry to the pre-saturated surface of existing above and below grade concrete structures. The active chemicals diffuse into the substrate and react with moisture and initiate the development of a non-soluble crystalline formation throughout the pores and capillary tracts of the concrete, as well as cracks, permanently sealing the concrete and preventing the penetration of water and other liquids from any direction, even under high hydrostatic pressure. Aqua Secure 120 is also mixed in a Dry-Pac form for sealing strips at construction joints, or for the repairing of leaking cracks, faulty construction joints and other defects.

Standard compliance

Complies with Standards ASTM C 348, ASTM D 7234, DIN 1048, ASTM C 1305, ASTM C 1202.

Where to Use

1.) For waterproofing of roof slabs, sunken slabs, basements, water tanks, sunshades etc. 2.) Repairing Hairline cracks. 3.) Interior & Exterior.

Advantages

- Simple to use - Single component, gauged as required.
- Higher abrasion resistance, good adhesion to building materials similar thermal characteristics to concrete
- High flexural / tensile strength to control cracking
- Resists extreme hydro-static pressure
- Easy to apply & cost-effective
- Penetrates concrete, seals capillaries and hairline cracks and remains waterproof even if surfaces are damaged.

Product Data

Appearance	Grey powder
Mix ratio	1: 0.45 (100 grams powder:45 ml water) by weight
Mix density	
Application temperature	

Technical Data

Flexural strength ASTM C 348	≥ 6 MPa at 28 days
Adhesion strength ASTM D 7234	>1.5MPa or concrete failure
Water permeability DIN 1048	No water penetration at 5 bar pressure
Crack sealing capability ASTM C 1305	Seals upto 0.2mm
Chloride ion penetration ASTM C 1202	<1000 coulombs

Mix Design

For Brush Application

Mix AquaSecure 120 powder with clean water to a creamy consistency in the following proportions: 0.65 - 0.8 kg/m2

100grams powder: 45 ml of water

Application Instructions

Surface Preparation

The object of the surface preparation is to achieve a clean sound surface with a good mechanical key. All substrates should be cleaned and free of dust, plaster, oil, paint, grease, corrosion deposits, and any other deleterious substances. Laitance should be removed by mechanical means. Smooth substrates must be mechanically roughened e.g., by scabbling, needle gun or grit blasting to provide an adequate key.

Corroded reinforcing steel should be exposed around its full circumference and cleaned to remove all loose scale and corrosion deposits. It is always preferably to clean the steel to a bright condition. Use of emery cloth, grit or sand blasting is recommended.

Mixing

1. Mix entire pack quantity at a time to achieve best properties.
2. Fill up the micro & macro cracks by AquaSecure 120 dry-pac form.
3. Pre-Saturate the floor before applying the mix.
4. Apply two coats in opposite directions, after the first coat let it dry for 4 to 5 hours and then proceed with second coat.

Important Considerations for SWADI AquaSecure 120 Application

• Ensure the surface is clean, free of dust, grease, and loose particles, and pre-wet the substrate before application. • Do not over-dilute the material with water, as this can affect its crystalline growth and waterproofing properties. • Apply the material evenly to the recommended thickness to allow optimal penetration into the substrate. • Protect the treated surface from direct rain, water, or heavy traffic for at least 48 hours to ensure proper curing. • Avoid application at temperatures below 5°C or above 40°C to maintain the effectiveness of the material. • Use the material only on concrete or masonry substrates suitable for crystalline technology.

Cleaning

Tools and equipment should be washed with water immediately after use.

Shelf Life

AquaSecure 120 has a shelf life of 12 months if kept in a dry store in unopened condition.

Packaging

AquaSecure 120 is available in 5 Kg and25 Kg bags.

Condition of Sale

Sold subject to the company's condition of sale which are available on request.

Storage and Handling Guidelines

The product should be stored in accordance with national regulations. It is essential to keep it in a cool, well-ventilated area, away from heat, direct sunlight, sparks, and children. Please note that the product contains flammable solvents, so handle it with care. To ensure proper curing, mix the resin and hardener according to the specified ratio. Once mixed, use the solution within its pot life to avoid premature hardening.

Health, and Safety Information

SWADI Roof Bond is considered on-hazardous in normal usage; however, avoid contact with eyes or skin. Wear suitable protective dust mask, gloves and safety glasses. In case of contact with eyes, rinse for several minutes under running water.

For further information, please consult the Material Safety Data Sheet (MSDS).

Disclaimer

The information provided in this datasheet is based on our extensive experience and is given in good faith to assist you. However, we reserve the right to update this information at any time without prior notice due to our ongoing research and development efforts. While we guarantee the consistent quality of our products, we cannot be held responsible for any losses or damages that may arise from their use if site conditions or the execution of work are not properly managed. This data sheet becomes invalid upon the publication of a new edition, and please contact us for the latest version. Please note that we do not provide any warranties regarding the results of our products in specific applications, as the storage, handling, and application of materials are factors beyond our control.

Contact Information

For immediate orders or enquires, contact our **24/7 support team at +91 8792919513 or enquiry@swadigroup.co.in**. For additional support options and resources, please visit our website at swadigroup.co.in

AquaSecure 120

SWADI MINERALS AND CHEMICALS
an ISO 9001:2015 & ISO 14001:2015 certified company
Sy.no 70/1, Vishwaneedam post, Gollarahatti
Magadi main road, Bengaluru – 560091
Tel: +91 8884492928
Email: enquiry@swadigroup.co.in
Website: swadigroup.co.in

Product Data Sheet
Aqua Blend 90
October 2025, Version 011.05.11000000000045

SWADI®
a step ahead...