PERFORMANCE
CONSTRUCTION CHEMICALS

SWADI®
a step ahead...

CEM-LINK 52

A High - Performance Epoxy Bonding Agent for Old & New Concrete

Description

Swadi® Cem-Link 52 is a high-performance epoxy bonding agent, designed to create a strong, lasting bond between fresh concrete and existing cured concrete. The Cem-Link 52 bonding agent has an extended pot life and a minimum cured bond strength of 50 MPa, values that are not achieved by traditional methods or regular bonding agents. The bonding agent can also be used for repairs, crack filling, and priming of concrete substrates at the time of repair.

Cem-Link 52 is formulated as a solvent free system, which consists resin (part a) and hardener (part b) and supplied as a two-component system which are pre-weighed and packed.

Where to Use

1.) For bonding fresh wet cementitious material to old & cured concrete surfaces. 2.) Residential constructions, high rise buildings, bridges etc., 3.) Used as a primer for repair mortars to concrete substrates.

Advantages

- Exceptional adhesion to both old and new concrete.
- Solvent free system – Which makes it suitable for both internal and external applications
- User-friendly formulation for convenient application
- Sets quickly for faster project completion.

Technical Data

Compressive strength ASTM C 109	50 mPa
Tensile strength ASTM C-307	20 mPa
Flexural strength ASTM C - 580	35 mPa
Pot life ASTM D 2471	35 – 45 minutes
Full cure	7 days
Max. overlay time	60 minutes @25°C
Type	Epoxy
Solvent type	Solvent-free
Appearance base	Transparent clear liquid
Appearance hardener	Brown colour
Mix ratio	2 Part base: 1 part hardener

Application Instructions

Surface Preparation

For existing/old concrete surfaces:

Thoroughly clean the surface to remove any dirt, dust, debris, or loose particles. Use a wire brush, pressure washer, or other suitable tools to ensure a clean substrate. Ensure the surface is completely dry before application.

For fresh concrete surfaces:

Ensure the concrete has reached sufficient strength before applying Cem-Link 52. Refer to the concrete manufacturer's recommendations for curing times. Remove any laitance or curing compounds from the surface using a suitable cleaning agent and water. Allow to dry completely.

General considerations:

- Surface profile: For optimal adhesion, the surface should have a suitable profile. A lightly roughened surface is generally preferred.
- Moisture content: Avoid applying Cem-Link 52 to damp or wet surfaces. Ensure the surface is dry before application.
- Temperature: The ambient temperature should be within the recommended range for the product. Extreme high temperatures can speed up the curing process, and extreme low temperatures can slow the curing process, which may also affect the performance of bonding agent. Prefer to work within the range of temperature 18°C to 34°C.

Cem-Link 52

Important Considerations for SWADI Cem-Link 52 Application

• Cem-Link 52 is temperature and moisture sensitive. • It should not be applied when temperatures are below 10°C or in extreme heat. • Low temperatures can slow down the curing process, while high temperatures can accelerate it. • users are advised to contact Swadi technical team support for specific guidance in challenging conditions.

Mixing

Measure the required amounts of Cem-Link 52 Part A and Part B. Ensure the components are at room temperature. Pour Part A into the mixing container and add Part B. Mix thoroughly using a mixing paddle or drill attachment. Periodically scrape the sides of the container to ensure even mixing and prevent any unmixed material. Mix the components for about two minutes until a uniform color is obtained.

Application

Cem-Link 52 should be applied immediately after mixing to ensure optimal performance. Apply it to the prepared surface using a brush or airless spray. For fresh concrete, apply the new material while Cem-Link 52 is still tacky. If necessary, a second coat must be applied on the same day. After application, immediately install any reinforcement or formwork.

Cleaning

Cem-Link 52 should be cleaned immediately from tools after application, use Swadi® Clean Epoxy solvent. If in case the hardened material can only be removed mechanically.

Shelf Life

12 months when stored unopened sealed pack and out of direct sunlight.

Coverage

Cem-Link 52 provides a theoretical coverage of 4-5 m^2/litre.

Condition of Sale

Sold subject to the Company's conditions of sale which are available on request.

Packaging

Cem-Link 52 is supplied in 3 kg pack which includes 2 kg Resin and 1 kg Hardener.

Storage and Handling Guidelines

The product should be stored in accordance with national regulations. It is essential to keep it in a cool, well-ventilated area, away from heat, direct sunlight, sparks, and children. Please note that the product contains flammable solvents, so handle it with care. To ensure proper curing, mix the resin and hardener according to the specified ratio. Once mixed, use the solution within its pot life to avoid premature hardening.

Health, and Safety Information

SWADI Cem-Link 52 is considered on-hazardous in normal usage; however, avoid contact with eyes or skin. Wear suitable protective dust mask, gloves and safety glasses. In case of contact with eyes, rinse for several minutes under running water.

For further information, please consult the Material Safety Data Sheet (MSDS).

Disclaimer

The information provided in this datasheet is based on our extensive experience and is given in good faith to assist you. However, we reserve the right to update this information at any time without prior notice due to our ongoing research and development efforts. While we guarantee the consistent quality of our products, we cannot be held responsible for any losses or damages that may arise from their use if site conditions or the execution of work are not properly managed. This data sheet becomes invalid upon the publication of a new edition, and please contact us for the latest version. Please note that we do not provide any warranties regarding the results of our products in specific applications, as the storage, handling, and application of materials are factors beyond our control.

Contact Information

For immediate orders or enquires, contact our **24/7 support team at +91 8792919513 or enquiry@swadigroup.co.in.** For additional support options and resources, please visit our website at swadigroup.co.in

Cem-Link 52

SWADI MINERALS AND CHEMICALS
an ISO 9001:2015 & ISO 14001:2015 certified company
Sy.no 70/1, Vishwaneedam post, Gollarahatti
Magadi main road, Bengaluru – 560091
Tel: +91 8884492928
Email: enquiry@swadigroup.co.in
Website: swadigroup.co.in

Product Data Sheet
Cem-Link 52
October 2025, Version 011.05.11000000000021

SWADI®
a step ahead...