PERFORMANCE
WATERPROOFING SYSTEMS

SWADI®
a step ahead...

# Coal Tar CT50

## High Performance Epoxy Base Coal Tar

### Description

Swadi Coal Tar Epoxy is a high-performance, two-component coating system. This solvent-free formulation offers excellent resistance to a wide range of chemicals, including acids, alkalis, salts, and organic solvents. Ideal for protecting metal and concrete surfaces in harsh environments, Swadi Coal Tar Epoxy is widely used in industries such as oil and gas, chemical processing, and infrastructure. Its robust formulation ensures long-lasting protection against corrosion and weathering, reducing maintenance costs and extending the lifespan of structures.

### Standard compliance

Complies with Standards ASTM D 2697, ASTM D 2369 81, ASTM D 2471, ASTM D 1640, ASTM D 7091, ASTM C 109, ASTM D 4541, DIN 1048

### Where to Use

**1.) Infrastructure:** Bridges, tunnels, and other concrete structures exposed to harsh environments. **2.) Chemical Processing:** Chemical plants, refineries, and petrochemical facilities. **3.) Marine Environments:** Piers, docks, and offshore platforms. **4.) Water Treatment:** Sewage treatment plants, water treatment facilities, and pipelines. **5.) Industrial Facilities:** Factories & warehouses.

### Advantages

- Superior corrosion protection
- Excellent chemical resistance
- Easy application
- High solid content
- Long-lasting durability
- Versatile substrate compatibility

### Product Data

| | |
|---|---|
| Type | Epoxy |
| Appearance / Colour | Part A: Resin – Off white<br>Part B: Hardener – Black<br>Parts A+B mixed: Black |
| Mixing ratio | 1: 1 (Resin: Hardener: Filler) by weight |
| Density (@ +20°C) | Part A: Resin: ~ 1.305 g/cc<br>Part B: Hardener: ~ 1.04 g/cc<br>Parts A+B mixed: ~ 1.17 g/cc |
| Solid content by volume ASTM D-2697 | ≥ 85 % |
| Volatile organic compound (VOC) content ASTM D-2369-81 | < 10 g/l |
| Pot life ASTM D 2471 | ~ 20 - 25 min |
| Drying time @25°C ASTM D 1640 | |
| Surface dry | ≥ 5 hrs |
| Hard dry | ≥ 12 hrs |
| Full cure | 7 days |
| Overcoat duration | Min. 12 hrs |
| Recommended DFT for 2 coats ASTM D 7091 | 300 microns |

### Technical Data

| | |
|---|---|
| Resistance to bacteria | No bacteria observed |
| Compressive strength ASTM C 109 | ≥ 45 MPa at 28 days |
| Pull off adhesion test ASTM D 4541 | ≥ 2 MPa for M20 grade concrete or concrete failure |
| Water permeability DIN 1048 | No water penetration at 5 bar pressure |
| Salt spray test (5% Nacl) | ~ 320 hrs passes |

# Coal Tar CT50

## Application Instructions

### Surface Preparation

**For existing/old concrete surfaces:**
Thoroughly clean the surface to remove any dirt, dust, debris, or loose particles. Use a wire brush, pressure washer, or other suitable tools to ensure a clean substrate. Ensure the surface is completely dry before application.

**For fresh concrete surfaces:**
Ensure the concrete has reached sufficient strength before applying Coal tar. Refer to the concrete manufacturer's recommendations for curing times. Remove any laitance or curing compounds from the surface using a suitable cleaning agent and water. Allow to dry completely.

**For steel surfaces:**
Clean the steel surface to remove rust scales, by wire brushing & scrapping. For best results, sand / grit blasting is recommended. Surfaces corroded with rust must be treated with rust removers & converters.

### General considerations:

- **Surface profile:** For optimal adhesion, the surface should have a suitable profile. A lightly roughened surface is generally preferred.
- **Moisture content:** For concrete maximum residual moisture content is below 5%, Ensure the surface is dry before application.
- **Temperature:** The ambient temperature should be within the recommended range for the product. Prefer to work within the range of temperature 18°C to 34°C.

### Mixing

First, put Part A (Resin) and Part B (Hardener) in a mixing bowl. Use an electric mixer to mix them together until they are fully combined. Scrape the sides of the can to make sure everything is mixed well.

### Application

1.) Apply the mixed material with a roller or brush at the recommended coverage rates.
2.) Apply 2 coats in a duration of 10 – 12 hrs.
3.) Allow to cure the coating for 7 days.

### Coverage

1 Kg will cover 3 Sqm for 2 coats.
**Note:** Surface texture and porosity can affect coverage rate.

### Cleaning

To clean your tools after applying Coal Tar CT50, it is recommended to use Swadi® CleanEpoxy solvent. This should be done immediately after application. If the Coal Tar CT50 has already hardened, it can only be removed by scraping it off.

### Packaging

Swadi Coal Tar CT50 comes in 9 Kg pack which includes 4.5 kg Resin and 4.5 Kg hardener.

### Shelf Life

12 months when stored unopened sealed pack and out of direct sunlight.

### Important Considerations for SWADI Coal Tar CT50 Application

• Do not dilute the material with any type of solvent • Provide adequate ventilation during application and curing to minimize exposure to fumes. • Do not use for potable water tanks. • Product does not comply with food grade regulations. • Wear appropriate personal protective equipment, including gloves, masks, and eye protection.

### Storage and Handling Guidelines

The product should be stored in accordance with national regulations. It is essential to keep it in a cool, well-ventilated area, away from heat, direct sunlight, sparks, and children. Please note that the product contains flammable solvents, so handle it with care. To ensure proper curing, mix the resin and hardener according to the specified ratio. Once mixed, use the solution within its pot life to avoid premature hardening.

### Health, and Safety Information

SWADI Coal Tar CT50 is considered on-hazardous in normal usage; however, avoid contact with eyes or skin. Wear suitable protective dust mask, gloves and safety glasses. In case of contact with eyes, rinse for several minutes under running water.

For further information, please consult the Material Safety Data Sheet (MSDS).

### Disclaimer

The information provided in this datasheet is based on our extensive experience and is given in good faith to assist you. However, we reserve the right to update this information at any time without prior notice due to our ongoing research and development efforts. While we guarantee the consistent quality of our products, we cannot be held responsible for any losses or damages that may arise from their use if site conditions or the execution of work are not properly managed. This data sheet becomes invalid upon the publication of a new edition, and please contact us for the latest version. Please note that we do not provide any warranties regarding the results of our products in specific applications, as the storage, handling, and application of materials are factors beyond our control.

## Contact Information

For immediate orders or enquires, contact our **24/7 support team at +91 8792919513 or enquiry@swadigroup.co.in**. For additional support options and resources, please visit our website at swadigroup.co.in

**SWADI MINERALS AND CHEMICALS**
an ISO 9001:2015 & ISO 14001:2015 certified company
Sy.no 70/1, Vishwaneedam post, Gollarahatti
Magadi main road, Bengaluru – 560091
Tel: +91 8884492928
Email: enquiry@swadigroup.co.in
Website: swadigroup.co.in

Product Data Sheet
Coal Tar CT50
October 2025, Version 011.05.11000000000042

SWADI®
*a step ahead...*