PERFORMANCE
FLOORING SYSTEMS

SWADI®
a step ahead...

EvoShine PU Crete

Heavy-Duty Polyurethane Flooring System

Description

Swadi PU Crete is a four - component polyurethane - concrete flooring system. This flowable system is applied at a thickness of 3 - 6 mm and forms a smooth surface. The thickness is determined by the service and cleaning temperatures and the severity of traffic expected. PU Crete is extremely tough and has many physical properties that exceed those of typical concrete. PU Crete is recommended for conditions requiring the maximum chemical resistance and where a smooth, even and easy to clean surface is required.

Advantages

1.) Eco - friendly.
3.) Can be applied to 10 day old concrete.
4.) Solvent free and low odour.
5.) Water based system with a high level of mechanical, chemical and water resistance.
6.) Low maintenance, hygineic and safe.
8.) Non - tainting, non - dusting, monolithic. (minimum joints); easy to maintain; microbiologically inert) seamless and easy to clean system.
9.) Excellent impact resistance at (3 - 6 mm) thickness. Can handle heavy traffics.
10.) Slip - resistant finish.

Technical Data

Pot life	20 minutes
Light traffic	24 hrs
Full traffic	48 hrs
Full chemical cure	7 days
Bond strength	> 1.5 N/mm²
Compressive strength	50 N/mm²
Flexural strength	18 N/mm²
Tensile strength	07 N/mm²
Hardness, shore D	80 - 90
Abrasion resistance	Classified 'Special Duty' under BS 8204 Part 2 : 2002(9)
Slip resistance	Classified 'Satisfactory' under BS 8204 Part 2: 2002(9), wet and dry
Impact resistance	Classified 'High Impact Resistance' under BS 8204: Part 1: 1999

Chemical Resistance

Swadi PU Crete is resistant to following chemicals tested for about 7+ days (Immersion Testing).

Dilute mineral acids, including hydrochloric (< 35%), phosphoric (< 50%), and sulfuric (< 30%).
Alkalis, including potassium hydroxide to a 50% concentration.
Some dilute organic acids such as acetic (25%), formic, citric, lactic and uric.
Fats, oils, and sugars.
Mineral oils, diesel fuel, kerosene, and gasoline.
Most organic solvents, including aliphatic and aromatic hydrocarbons and alcohol.

The results given above are achieved in laboratory tests. Actual results obtained on site may show minor variations from those quoted.

Application Instructions

Surface Preparation

- The concrete or screed substrate must be hard, sound and free of dust and other barrier materials such as paint, lime coatings, plaster, curing agents, laitance, adhesive residues etc. that will inhibit adhesion to the substrate.

EvoShine PU Crete

- Remove bond-inhibiting materials such as oils, grease, wax, fatty acids, and other contaminants. (This can be accomplished by the use of detergent scrubbing, low pressure water cleaning, steam cleaning, or chemical cleaning. Acids and alkalis cleaning. Acids and alkalis can be removed by neutralizing to form a water-soluble salt and then high - pressure water cleaning). Contaminated concrete surfaces should be mechanically prepared, either by grinding or contained shot blasting equipment or similar, and be vacuumed clean prior to applying SWADI PU Crete.
- Concrete defects such as voids, bug holes, excess porosity, and physical and chemical damage are usually filled or repaired prior to the installation of the Flooring system. (Materials such as slurries, mortars, and polymer concrete are used to level, smooth and patch concrete surfaces).

Priming

Use suitable primer depending on substrate condition to ensure maximum product performance. Preferably scratch coat of SWADI PU Crete is recommended.

Mixing

The contents of part A, part D pigment kit and part B of SWADI PU Crete must be first mixed together for 1 minute, using forced action, in a suitably sized mixing vessel. The contents of part C the powder component should then be introduced into the mixed resin and mixed together for a further 2 minutes to create one homogeneous mix.

Application

For flooring applications, the mixed material should be applied to the prepared and primed surface after 24 hours of priming, using a trowel to achieve the desired thickness. As soon as the product has been laid and as work progresses, the surface should be gently rolled with a spiked roller in order to provide an even surface appearance. Do not re - roll later.

Drying Time

The floor can be returned to full service in 12 – 24 hours at 30° C. Full cure at 28 days.

Coverage Estimates

Pack Size Coverage

Part A - Resin	2.52 Kg
Part B - Hardener	3.21 Kg
Part C - Filler	13 Kg
Part D - Pigment	0.5 Kg

Total kit weighs: 19.23 Kg which gives coverage of 12 Sqm / 1mm thickness

Note: These figures are theoretical, due to the wastages and the variety and nature of substrates practical coverage figures may be reduced.

Colours Available

German Grey RAL 7035	Traffic Grey RAL 7042	Dark Grey RAL 7043	Light Blue RAL 5012
Dark Blue RAL 5010	Yellow RAL 1032	RED RAL 3013	Green RAL 6029

Note: Due to variations in monitor calibration, the physical color the product may differ from the color depicted here

- SWADI PU Crete is a colored polyurethane concrete, colour uniformity cannot be completely guaranteed from batch to batch. Do not mix batches within a single area.
- The final color of SWADI PU Crete, on both interior and exterior application is prone to yellowing effect and may darken/lighten under UV light exposure. This yellowing effect is dependent upon the amount of UV exposure, both in terms of intensity and time, and is more noticeable with lighter colours. The performance of the product, however, will not be affected.

Precautions

- This product is for professional use only. The applicators and operators shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to company's technical documentation.

- Applicators and operators shall use appropriate personal protection equipment when using this product. This guideline is given based on the current knowledge of the product. Any suggested deviation to suit the site conditions shall be forwarded to the responsible company representative for approval before commencing the work.

Safety Features

- Store the container with the lid tightly closed in an upright position, in a cool, dry place.
- Keep out of reach of children and away from eatables.
- May be harmful if swallowed. In case of ingestion seek immediate medical attention.
- Wear eye protection during application. In case of contact with eyes, rinse immediately.
- With plenty of water and if required seek medical advice.
- As far as possible, direct contact of resin and hardener with the skin should be avoided as they might cause irritant on sensitive skins. It is advisable to wash off immediately in case of skin contact.
- Special barrier creams and cleansing creams are available commercially as additional safeguards. Please refer MSDS for detail safety instructions.

Storage Conditions

Store and transport in unopened containers in a clean, dry area at stable temperatures approximating 5°C to 30°C.

Conditions of Sale

Sold subject to the company's conditions of sale which are available on request.

Storage and Handling Guidelines

The product should be stored in accordance with national regulations. It is essential to keep it in a cool, well-ventilated area, away from heat, direct sunlight, sparks, and children. Please note that the product contains flammable solvents, so handle it with care. To ensure proper curing, mix the resin and hardener according to the specified ratio. Once mixed, use the solution within its pot life to avoid premature hardening.

Environmental, Health, and Safety Information

For comprehensive information regarding the safe transportation, handling, storage, and disposal of this chemical product, please refer to the accompanying Safety Data Sheet (SDS). The SDS contains detailed information about physical properties, environmental impacts, toxicological hazards, and other safety-related factors. It is crucial to read the current SDS before using any product.

Disclaimer

The information provided in this datasheet is based on our extensive experience and is given in good faith to assist you. However, we reserve the right to update this information at any time without prior notice due to our ongoing research and development efforts. While we guarantee the consistent quality of our products, we cannot be held responsible for any losses or damages that may arise from their use if site conditions or the execution of work are not properly managed. This data sheet becomes invalid upon the publication of a new edition, and please contact us for the latest version. Please note that we do not provide any warranties regarding the results of our products in specific applications, as the storage, handling, and application of materials are factors beyond our control.

Contact Information

For immediate orders or enquires, contact our **24/7 support team at +91 8792919513 or enquiry@swadigroup.co.in**. For additional support options and resources, please visit our website at swadigroup.co.in

SWADI MINERALS AND CHEMICALS
an ISO 9001:2015 & ISO 14001:2015 certified company
Sy.no 70/1, Vishwaneedam post, Gollarahatti
Magadi main road, Bengaluru – 560091
Tel: +91 8884492928
Email: enquiry@swadigroup.co.in
Website: swadigroup.co.in

Product Data Sheet
EvoShine PU Crete
October 2025, Version 011.05.11000000000059

SWADI®
a step ahead...