PERFORMANCE
FLOORING SYSTEMS

SWADI®
a step ahead...

EvoShine Primer EP11

High-Performance Penetrative Primer for Epoxy Flooring Systems

Description

Evoshine EP11 is a two-component epoxy flooring primer, that allows the primer to penetrate into the concrete substrate and seal it with a nonporous finish, resulting in a superior bond. The evoshine contains specially formulated resins and hardeners which are able to withstand all the surface abrasions. This is mainly used to provide a good surface finish on applied topcoats.

Standard Compliance

Complies with standards ASTM C 579, ASTM D882, ASTM D 4541.

Where to Use

Recommended for chemical, pharmaceutical, clean rooms, food processing areas, laboratories, demonstration and training rooms, electrical and electronics assembly plants, packing and storage areas, automobile showrooms, light and heavy vehicle manufacturing units for interior floors protected from the sun, and other interior concrete surfaces. Not for use on exterior surfaces.

Advantages

1.) Good chemical resistance.
2.) Good abrasion resistance.
3.) Free of solvents.
4.) High mechanical strength.
5.) Easy & fast application.
6.) Durability & seamless.
7.) Aesthetic: Available in several colours provides as hygienic surface.

Technical Data

Type	Epoxy / Amine
Mixing ratio(R:H)	1:1 (Pre - Weighed Kit)
Percentage of solids	80 %
Flash point	Non - Flammable
Pot life	30 minutes
Surface dry	8 hours
Tack free dry	12 hours
Hard dry	7 days
Compressive strength at 30 ºC, N/mm², 14 days As per ASTM C 579	40 - 45 N / mm²
Tensile strength at 30ºCN/mm²,14days As per ASTM D882	11 N / mm²
Pull of adhesion As per ASTM D 4541	Passes up to 2.21 mPa
Flexural strength	20-25 N / mm²
Coverage	55-60 sqft / kg / 2 Coats
Application method	Trowel & spick roller
Clean up	Thinner / Solvent
Shelf life	24 months

Application Instructions

Surface Preparation

The substrate must be dry, hard, sound, free of dust and the barrier materials such as paint, lime coatings, plaster, curing agents, wax, polish, laitance, etc. Use a suitable degreaser to remove polish, wax, grease, oil and similar contaminating substances.

Priming

Evoshine Primer seal the pores and prevent air bubbles from rising through the applied mortar. The primer also helps to maintain flow life and promote excellent adhesion to the substrate.

Mixing

Mix Part A (Resin) and Part B (Hardener) in a 1:1 ratio by weight in a clean mixing container. Ensure all material is removed from each can. Using a slow-speed electric stirrer (≤300 RPM) or a jetty blade mixer attached to an electric drill, mix continuously until a smooth, homogenous blend is achieved. Scrape the sides and bottom of the container multiple times during mixing to ensure uniformity. Do not mix by hand, and be careful not to introduce air bubbles, as they can affect the performance of the primer. Once mixed, the material should be applied immediately within the specified pot life to avoid premature curing.

EvoShine Primer EP11

Packaging

Evoshine Primer EP11 is available in 10 kg and 40 kg pack.

Storage and Shelf Life / Precautions / Disposal / Spillage

For further information please refer to the Material Safety Data Sheet.

Conditions of Sale

Sold subject to the company's conditions of sale which are available on request.

Storage and Handling Guidelines

The product should be stored in accordance with national regulations. It is essential to keep it in a cool, well-ventilated area, away from heat, direct sunlight, sparks, and children. Please note that the product contains flammable solvents, so handle it with care. To ensure proper curing, mix the resin and hardener according to the specified ratio. Once mixed, use the solution within its pot life to avoid premature hardening.

Environmental, Health, and Safety Information

For comprehensive information regarding the safe transportation, handling, storage, and disposal of this chemical product, please refer to the accompanying Safety Data Sheet (SDS). The SDS contains detailed information about physical properties, environmental impacts, toxicological hazards, and other safety-related factors. It is crucial to read the current SDS before using any product.

Disclaimer

The information provided in this datasheet is based on our extensive experience and is given in good faith to assist you. However, we reserve the right to update this information at any time without prior notice due to our ongoing research and development efforts. While we guarantee the consistent quality of our products, we cannot be held responsible for any losses or damages that may arise from their use if site conditions or the execution of work are not properly managed. This data sheet becomes invalid upon the publication of a new edition, and please contact us for the latest version. Please note that we do not provide any warranties regarding the results of our products in specific applications, as the storage, handling, and application of materials are factors beyond our control.

Contact Information

For immediate orders or enquires, contact our **24/7 support team at +91 8792919513 or enquiry@swadigroup.co.in**. For additional support options and resources, please visit our website at swadigroup.co.in