PERFORMANCE
FLOORING SYSTEMS

SWADI®
a step ahead...

EvoShine TopCoat R21

Epoxy Roller Coat Compound

Description

EvoShine TopCoat R21 is a high performance, hi - quality, and solvent - less epoxy floor roller coat for use in industrial and commercial environments. It produces a smooth, Semi-gloss finish with several advantages.

Standard Compliance

Complies with standards ASTM C 579, ASTM D 882, ASTM D 4541.

Where to Use

Recommended for chemical, pharmaceutical, clean room, food processing area, laboratories, demonstration & training rooms, electrical & electronics assembly plants, packing & storage area, automobile showroom, light & medium vehicle manufacturing units for interior floors protected from the sun and other interior concrete surfaces. Not for use on exterior surfaces. Epoxy Topcoat R21 is used as coloured floor toppings.

Properties

1.) Good chemical resistance.
2.) Good abrasion resistance.
3.) Free of solvents.
4.) High mechanical strength.
5.) Easy & fast application.
6.) Durability & seamless.
7.) Aesthetic: Available in several colors provides as hygienic surface.

Technical Data

Type	Epoxy / Amine
Mixing ratio(R:H)	A: B:C:D (Pre - Weighed Kit)
Percentage of solids	93 - 95 %
Flash point	Non - flammable
Pot life	30 - 35 minutes
Surface dry	8 hours
Tack free dry	24 hours
Hard dry	7 days
Coverage / kit - For 1 Coat @200 micons	~250 Sqfts
Packaging top coat kit	Resin - 4 kgs Hardener - 2 kgs Filler - 4 kgs
Compressive strength at 30º C, N/mm², 14 days As per ASTM C 579	~40 N/mm²
Tensile strength at 30º C N/mm²,14days As per ASTM D 882	~16 N/mm²
Pull of adhesion As per ASTM D 4541	Passes up to 2.0 mPa
Flexural strength	~20 N/mm²
Application method	Roller
Clean up	Thinner / solvent
Shelf life	12 months

Finish

Semi-gloss finish.

Application Instructions

Surface Preparation

The substrate must be dry, hard, sound, free of dust and the barrier materials such as paint, lime coatings, plaster, curing agents, wax, polish, laitance, etc. Use a suitable degreaser to remove polish, wax, grease, oil and similar contaminating substances.

Priming

EvoShine Primer EP11 primer seal the pores and prevent air bubbles from rising through the applied mortar. The primer also helps to maintain flow life and promote excellent adhesion to the substrate.

Mixing

Add the parts in sequence below, under continuous stirring by a very slow speed electric stirrer or jetty blade mixer fitted on an electric drill till the mixture is homogenous. DO NOT MIX BY HAND. Remove all material from each can. Scrap the sides of the

container several times to ensure complete mixing. Be careful to not introduce any air bubbles while mixing.

Application

Since the mix ratio is critical to the performance of the flooring system. Quantity to be mixed should be calculated beforehand based on the area to be covered and coating thickness desired. Actual coverage will depend on texture, porosity, slope of the substrate.

Pour the mixed EvoShine Topcoat R21 onto the surface as soon as possible (see pot life) and spread using a rubber squeegee. Use a high-quality roller to spread the coating evenly, Apply in thin coats to avoid uneven thickness and roller marks. Maintain a wet edge to prevent roller overlap marks.

Do not overwork the material. Topcoat R21 is designed for use without solvents, use of thinners is not recommended.

Storage and Shelf Life / Precautions / Disposal / Spillage

For further information please refer to the Material Safety Data Sheet.

Conditions of Sale

Sold subject to the company's conditions of sale which are available on request.

Storage and Handling Guidelines

The product should be stored in accordance with national regulations. It is essential to keep it in a cool, well-ventilated area, away from heat, direct sunlight, sparks, and children. Please note that the product contains flammable solvents, so handle it with Page 5 of 5 care. To ensure proper curing, mix the resin and hardener according to the specified ratio. Once mixed, use the solution within its pot life to avoid premature hardening.

Environmental, Health, and Safety Information

For comprehensive information regarding the safe transportation, handling, storage, and disposal of this chemical product, please refer to the accompanying Safety Data Sheet (SDS). The SDS contains detailed information about physical properties, environmental impacts, toxicological hazards, and other safety-related factors. It is crucial to read the current SDS before using any product.

Disclaimer

The information provided in this datasheet is based on our extensive experience and is given in good faith to assist you. However, we reserve the right to update this information at any time without prior notice due to our ongoing research and development efforts. While we guarantee the consistent quality of our products, we cannot be held responsible for any losses or damages that may arise from their use if site conditions or the execution of work are not properly managed. This data sheet becomes invalid upon the publication of a new edition, and please contact us for the latest version. Please note that we do not provide any warranties regarding the results of our products in specific applications, as the storage, handling, and application of materials are factors beyond our control.

Contact Information

For immediate orders or enquires, contact our **24/7 support team at +91 8792919513 or enquiry@swadigroup.co.in**. For additional support options and resources, please visit our website at swadigroup.co.in

SWADI MINERALS AND CHEMICALS
an ISO 9001:2015 & ISO 14001:2015 certified company
Sy.no 70/1, Vishwaneedam post, Gollarahatti
Magadi main road, Bengaluru – 560091
Tel: +91 8884492928
Email: enquiry@swadigroup.co.in
Website: swadigroup.co.in

Product Data Sheet
EvoShine TopCoat R21
October 2025, Version 011.05.11000000000058

SWADI®
a step ahead...