PERFORMANCE
FLOORING SYSTEMS

SWADI®
a step ahead...

Evoshine ESD 101

ESD Flooring | Static Dissipative

Description

Swadi ESD 101 is a multi-layered self-levelled epoxy system, which provides you with a highly durable, customizable, sustainable & attractive work space with chosen colour.

Brief

Swadi ESD 101 is designed to control the electrical resistance of the floor by inhibiting static electricity, thus preventing damage from random static discharge. To predict the ESD floor of ground charges, we measure its electrical resistance, that's the capacity of a flooring material to resist, or reduce, the flow of electricity.

To comply with all industrial standards, our electrical resistance measures fall within the ideal range (or) Safest electrical range which come between 1.0 × 105 to 1.0 × 108 Ω (ohms).

Standard Compliance

Complies with standards ASTM D 2471, IS 8374 & IEC 61340 - 4 - 5, IS 8374 & IEC 61340 - 4 - 5, ASTM D - 695, ASTM D - 790, ASTM D - 638, ASTM D - 4060, ASTM D - 1640.

Where to Use

1.) Electronics, plat panel, and medical device manufacturing. 2.) Cleanroom manufacturing. 3.) Computer and electronics handling, assembly or repair . 4.) PCB soldering or rework. 5.) Telecommunication installation areas.

Advantages

1.) Provides a safest electrical resistance.
2.) Highly durable & seamless flooring.
3.) Excellent chemical resistance.
4.) High mechanical strength.
5.) Free of solvents.
6.) Ready with a wide range of attractive colour choice.

Technical Data

Type	Epoxy
Flash point	Non - flammable
Pot life ASTM D 2471	30 minutes
Electrical range IS 8374 & IEC 61340 - 4 - 5	1.0×10^6 to 1.0×10^9 Ω (ohms).
Body voltage generation (BVG) IS 8374 & IEC 61340 - 4 - 5	<100 V
Compressive strength ASTM D - 695	≥40 N/mm²
Flexural strength ASTM D - 790	≥20 N/mm²
Tensile strength ASTM D - 638	≥15 N/mm²
Abrasion resistance ASTM D - 4060	70 mg loss
Surface dry ASTM D - 1640	8 hours
Coverage	10 Sqm / Kit @1 mm thickness
Shelf life	12 months
Packaging	14.2 kg kit (Resin - 4.45 kg Hardener - 2.25 kg Filler - 7.50 kg)

Design of Screed System

Product	Thickness
Swadi primer	200 microns
Swadi screed	2mm to 6mm thickness
Copper tape	Conductive grid of 12mm wide copper tape
Swadi antistatic primer	200 microns
Swadi topcoat	1mm to 6mm thickness

Design of Non - Screeding System

Product	Thickness
Swadi primer	200 microns
Copper tape	Conductive grid of 12mm wide copper tape
Swadi antistatic primer	200 microns
Swadi topcoat	1mm to 6mm thickness

Storage and Shelf life / Precautions / Disposal / Spillage

For further information please refer to the Material Safety Data Sheet.

Conditions of Sale

Sold subject to the company's conditions of sale which are available on request.

Storage and Handling Guidelines

The product should be stored in accordance with national regulations. It is essential to keep it in a cool, well-ventilated area, away from heat, direct sunlight, sparks, and children. Please note that the product contains flammable solvents, so handle it with Page 5 of 5 care. To ensure proper curing, mix the resin and hardener according to the specified ratio. Once mixed, use the solution within its pot life to avoid premature hardening.

Environmental, Health, and Safety Information

For comprehensive information regarding the safe transportation, handling, storage, and disposal of this chemical product, please refer to the accompanying Safety Data Sheet (SDS). The SDS contains detailed information about physical properties, environmental impacts, toxicological hazards, and other safety-related factors. It is crucial to read the current SDS before using any product.

Disclaimer

The information provided in this datasheet is based on our extensive experience and is given in good faith to assist you. However, we reserve the right to update this information at any time without prior notice due to our ongoing research and development efforts. While we guarantee the consistent quality of our products, we cannot be held responsible for any losses or damages that may arise from their use if site conditions or the execution of work are not properly managed. This data sheet becomes invalid upon the publication of a new edition, and please contact us for the latest version. Please note that we do not provide any warranties regarding the results of our products in specific applications, as the storage, handling, and application of materials are factors beyond our control.

Contact Information

For immediate orders or enquires, contact our **24/7 support team at +91 8792919513 or enquiry@swadigroup.co.in**. For additional support options and resources, please visit our website at swadigroup.co.in

SWADI MINERALS AND CHEMICALS
an ISO 9001:2015 & ISO 14001:2015 certified company
Sy.no 70/1, Vishwaneedam post, Gollarahatti
Magadi main road, Bengaluru – 560091
Tel: +91 8884492928
Email: enquiry@swadigroup.co.in
Website: swadigroup.co.in

Product Data Sheet
Evoshine ESD 101
October 2025, Version 011.05.11000000000060

SWADI®
a step ahead...