PERFORMANCE
WATERPROOFING SYSTEMS

SWADI®
a step ahead...

Hydro LOC 2K

Two-Component Flexible Crack-Resistant Coating System

Description

HydraLoc 2K is a two-component crack-bridging and waterproofing system for gypsum plaster and other brittle surfaces. The product is composed of two components: Part A, a hydrophobic putty with excellent flexibility and adhesion, and Part B, an acrylic polymer emulsion that imparts toughness, elasticity, and UV resistance. These two coatings together reduce the risk of reflective cracking from gypsum plaster substrates by forming a flexible, water-repellent coating.

Where to Use

- Reinforcement over hairline and minor cracks (≤2.0 mm).
- Crack-bridging system over gypsum plaster, POP, or smooth internal walls.
- As a preparatory layer before painting or decorative coatings.

Advantages

- Excellent crack resistance
- Flexible and elastic – absorbs minor movements
- Hydrophobic – resists moisture ingress
- Good adhesion to gypsum plaster
- Easy to apply with putty knife or trowel
- Low shrinkage, non-sag formulation

Product Data

Type	Epoxy
Appearance / Colour	Part A: White Powder Part B: Milky liquid Parts A+B mixed: White paste
Mixing ratio	Part A: 71.5 % Part B: 28.5% On total weight of kit
Water Absorption	< 5% (after 24 hrs immersion)
Pot life ASTM D 2471	~ 30 - 40 min
Drying time @25°C ASTM D 1640	
Surface dry	4 hrs
Hard dry	≥ 12 hrs
Full cure	7 days
Overcoat duration	Min. 12 hrs

Application Instructions

Crack Preparation

Firstly, Inspect the surface for cracks up to 2.0 mm wide. These cracks should be widened to approximately 1 to 2 inches in width and about 2 mm in depth using sandpaper or a scraping tool. This widening helps create a better anchoring profile for the product, ensuring improved bonding and long-term crack resistance, especially on brittle surfaces like gypsum plaster.

Crack Cleaning

After widening the cracks, thoroughly clean the surface using a moist sponge to remove all dust, debris, and loose plaster. This step is crucial to prevent adhesion failure. Ensure the surface remains slightly damp but not wet, as a slightly absorbent surface will promote better bonding of the primer and the repair material.

Primer Application

Apply a uniform coat of AquaBlend 90 adhesion primer to the prepared area using a brush or roller. Allow it to dry for 5 minutes. This primer enhances adhesion between the gypsum surface and the HydroLoc 2K mixture.

Mixing

In a clean container, combine 5 kg of HydroLoc Powder (Part A) with 2 kg of HydroLoc Polymer (Part B). Mix thoroughly using a spatula or a slow-speed mechanical stirrer until a smooth, lump-free consistency is achieved. Do not add water or any additional materials to the mix.

Hydro LOC 2K

Application:

Apply the mixed HydroLoc 2K like a wall putty using a putty knife or trowel. Press the material firmly into the cracks and spread it evenly, feathering the edges to blend smoothly with the surrounding plaster. If required, apply a second coat after the first has dried to the touch (typically after 4 to 5 hours).

Curing & Finishing:

Allow the applied surface to cure for a minimum of 24 hours without disturbance. Protect the area from direct sunlight, wind, or moisture during curing. Once fully cured, the surface can be sanded lightly to achieve a smooth finish before painting or applying a decorative coat.

Coverage

1 Kg will cover approximately 10 Sqfts for 2 coats at 2mm thickness

Note: Actual coverage may vary depending on the surface condition, roughness, and the width and depth of the cracks being treated. Areas with wider cracks or more surface irregularities will require more material, thereby reducing the overall coverage.

Tools Cleaning

To clean your tools after applying Hydro Loc 2K, it is recommended to use clean water. This should be done immediately after application.

Packaging

Swadi Hydro Loc 2K comes in 7 Kg pack which includes 5 kg Powder and 2 Kg Liquid Polymer.

Shelf Life

12 months when stored unopened sealed pack and out of direct sunlight.

Storage and Handling Guidelines

The product should be stored in accordance with national regulations. It is essential to keep it in a dry area, away from heat.

Health, and Safety Information

Swadi Hydro Loc 2K is considered non-hazardous in usage; however, avoid contact with eyes or skin. Wear suitable protective dust mask, gloves and safety glasses. In case of contact with eyes, rinse for several minutes under running water.

For further information, please consult the Material Safety Data Sheet (MSDS).

Disclaimer

The information provided in this datasheet is based on our extensive experience and is given in good faith to assist you. However, we reserve the right to update this information at any time without prior notice due to our ongoing research and development efforts. While we guarantee the consistent quality of our products, we cannot be held responsible for any losses or damages that may arise from their use if site conditions or the execution of work are not properly managed. This data sheet becomes invalid upon the publication of a new edition, and please contact us for the latest version. Please note that we do not provide any warranties regarding the results of our products in specific applications, as the storage, handling, and application of materials are factors beyond our control.

Contact Information

For immediate orders or enquires, contact our **24/7 support team at +91 8792919513 or enquiry@swadigroup.co.in**. For additional support options and resources, please visit our website at swadigroup.co.in

SWADI MINERALS AND CHEMICALS
an ISO 9001:2015 & ISO 14001:2015 certified company
Sy.no 70/1, Vishwaneedam post, Gollarahatti
Magadi main road, Bengaluru – 560091
Tel: +91 8884492928
Email: enquiry@swadigroup.co.in
Website: swadigroup.co.in

Product Data Sheet
HYDRO LOC 2K
October 2025, Version 011.05.11000000000036

SWADI®
a step ahead...