PERFORMANCE
CONSTRUCTION CHEMICALS

SWADI®
a step ahead...

Hydrophobic Coarse Wall Putty

A True water-resistant coarse putty, designed for exterior walls and areas exposed to water flow.

Description

Swadi Hydrophobic Coarse Wall Putty is a high-performance, strong polymer-modified cement-based putty specially designed to correct surface irregularities and to level moderate undulations on cement plaster, Mivan structure concrete, beams, columns, and precast surfaces. Formulated with carefully graded aggregates, and performance additives, it provides the best water resistivity, excellent adhesion, crack resistance, and good workability.

Swadi Hydrophobic Coarse Putty is available in both coarse and finer grades.

Where to Use

- All types of plastered and concrete walls.
- To level undulation on concrete surfaces.
- Aerated lightweight concrete blocks (AAC blocks).
- Hollow concrete blocks and masonry surfaces.
- Mainly used for Exterior wall surfaces, suggestable to use for both interior & exterior to protect walls for longer run.

Advantages

- Water-repellent and moisture-resistant formulation.
- Excellent efflorescence resistance.
- Strong adhesion to concrete and plaster surfaces.
- Can be applied at a thickness of 2 mm to 5 mm in one single coat.
- Excellent UV resistant and helps in reduction in cracking.

Technical Data

Form	White coarse powder
Compressive strength (N/mm²) @ 28 Days	~ 9.5 N/mm²
Setting time (minutes) Initial Final	 4 to 6 hours 12 to 24 hours
May slightly vary depending on temperature & humidity	
Pot life	2 to 3 hours (Temp 30°C, H 65%)
Dry for recoat	10 hours at 3 mm thick (temp 30°C, H 65%)
Tensile adhesion ASTM D4541	0.92 N/mm²
Bulk density	1.55 g/cc
Water absorption-Karsten tube on concrete slab (ml) after 28 days curing - @2 mm thick	After 4 hr 0.8
Recommended thickness	2mm to 5mm per single coat (min 2mm & max 5mm)

Coverage

- 3.1 to 3.2 kg / Sqm / 2mm thickness

Coveage might vary depends on surface porosity or texture & practical spreading rate

Application Instructions

Surface Preparation

- Ensure that the surface on which you apply putty is plastered or made with the cementitious material.
- Give separate treatments or remedial measure for dampness, efflorescence, fungus, leakages on your wall.
- Ensure that the surface is totally clean. It should be free from dust, loose particles, residual paints, grease, oil or any other contamination.
- Remove all loose or poorly adhering material from the surface by rubbing down with help of sandpaper or with wire brush or with putty blade and after that wipe it out.
- Wet the wall with sufficient quantity of clean water and allow them to dry before applying Hydrophobic coarse putty on wall. Ensure that surface is just wet. Over wetting results in accumulation of water on a surface should be avoided. This ensures higher bonding of strength, easy workability & higher coverage with the surface.

Hydrophobic Coarse Wallputty

Mixing

- Mix the Swadi Hydrophobic Coarse Wallputty with 35 to 40 % clean water slowly to make a paste.
- Prepare the mixing with Mechanical mixer for 10 - 15 minutes till a uniform paste is formed. This will help in easy application, obtaining more coverage and smooth shade.
- Only mix a required quantity which can be used within 2 - 3 hours of mixing with water.

Application

- After thoroughly mixing, apply the first coat of putty in a vertical “bottom to top” manner by using a putty blade/spatula/ trowel or any finishing tool. This would ensure minimum wastage.
- Apply at a thickness rate of 2mm to 5mm thickness in one single coat.
- Each coat must not be less than 2mm and greater than 5mm. apply second coat if required after proper drying time of minimum 12 hours for 1st coat.

Precautions

- Do not apply the material without pre - wetting the surface for the 1st coat.
- Ensure the material is mixed homogeneously with water and allowed to stand for 5-10 min before application.
- Do not sand the material vigorously with Emery Paper otherwise it will reduce the strength of the material.
- Do not apply the material to fill cracks.
- Though the material is non - toxic, care should be taken to avoid dust inhalation while mixing and handling.

Storage

Stored in a dry place for best results use it within 12 months from date of manufacture.

Condition of Sale

Sold subject to the Company's conditions of sale which are available on request.

Storage and Handling Guidelines

The product should be stored as per national regulations in a cool, dry, and well-ventilated area, away from direct sunlight and extreme temperatures. Keep it out of reach of children. Ensure the bag is tightly sealed when not in use. Handle with care to avoid contamination. Use as per the recommended guidelines.

Health, and Safety Information

Swadi Hydrophobic Coarse Wallputty is considered on-hazardous in normal usage; however, avoid contact with eyes or skin. Wear suitable protective dust mask, gloves and safety glasses. In case of contact with eyes, rinse for several minutes under running water.

For further information, please consult the Material Safety Data Sheet (MSDS).

Disclaimer

The information provided in this datasheet is based on our extensive experience and is given in good faith to assist you. However, we reserve the right to update this information at any time without prior notice due to our ongoing research and development efforts. While we guarantee the consistent quality of our products, we cannot be held responsible for any losses or damages that may arise from their use if site conditions or the execution of work are not properly managed. This data sheet becomes invalid upon the publication of a new edition, and please contact us for the latest version. Please note that we do not provide any warranties regarding the results of our products in specific applications, as the storage, handling, and application of materials are factors beyond our control.

Contact Information

For immediate orders or enquires, contact our **24/7 support team at +91 8792919513 or enquiry@swadigroup.co.in.** For additional support options and resources, please visit our website at swadigroup.co.in

SWADI MINERALS AND CHEMICALS
an ISO 9001:2015 & ISO 14001:2015 certified company
Sy.no 70/1, Vishwaneedam post, Gollarahatti
Magadi main road, Bengaluru – 560091
Tel: +91 8884492928
Email: enquiry@swadigroup.co.in
Website: swadigroup.co.in

Product Data Sheet
Hydrophobic Coarse Wallputty
October 2025, Version 011.05.10900000000019

SWADI®
a step ahead...