PERFORMANCE
WATERPROOFING SYSTEMS

SWADI®
a step ahead...

Inject 50+

High-performance epoxy injection grout for structural repairs

Description

Swadi® Inject 50+ is a high - performance epoxy - based injection grout designed for sealing cracks and voids in concrete and restoring structural integrity. This two - component, solvent - free system consists of a resin (Part A) and a hardener (Part B), pre - weighed and packed for ease of use. Inject 50+ provides superior bond strength and penetration, ensuring long -term durability and performance in demanding structural repair applications.

Standard Compliance

Complies with Standards ASTM D 2393, ASTM D 2697, ASTM D 2369 81, ASTM D 2471, ASTM D 1640, ASTM D 695, ASTM D 638, ASTM C 882, ASTM D 2566.

Where to Use

1.) Repair of fine cracks and voids in concrete and masonry structures. 2.) Bridges, dams, industrial floors, and high - rise buildings. 3.) Strengthening of structural elements like beams, slabs, and columns.

Advantages

- Exceptional penetration into fine cracks for effective sealing.
- High compressive, tensile, and bond strength for enhanced structural integrity.
- Solvent - free, non-shrink formulation ensures minimal shrinkage and long-term stability.
- Low viscosity allows deep penetration into cracks as narrow as 0.2 mm.
- Suitable for vertical, horizontal, and overhead crack injection.

Product Data

Type	Epoxy
Solvent type	Solvent free
Appearance / Colour	Part A - Resin: Transparent / Clear Part B - Hardener : Brown Mixed colour : Brown
Viscosity ASTM D 2393	120 +/- 10 seconds by ford cup B4
Mix ratio	1:1 (part A : part B)
Density of mix (Resin : Hardener - 1:1 ratio)	1.04 gm / cc
Solid content by volume ASTM D 2697	≥91 %
VOC content ASTM D 2369 81	< 10 g/l
Pot life ASTM D 2471	20 minutes
Drying time @ 25°C ASTM D 1640 Hard dry Final cure	 12 hours 7 days

Technical Data

Compressive strength ASTM D 695	55 MPa @ 1 day 80 MPa @ 7 days
Tensile strength ASTM D 638	20 MPa
Bond strength ASTM C 882	>5 MPa
Shrinkage ASTM D 2566	0 %

Application Instructions

Surface Preparation

1. Thoroughly clean the surface to remove any dirt, dust, debris, or loose particles.
2. Ensure the cracks are clean and free from contaminants, use compressed air to blow out debris.
3. For wider cracks, prepare suitable injection ports at intervals.

Mixing

Measure the required amounts of Inject 50+ (part A and part B). Ensure the components are at room temperature. Pour Part A into the mixing container and add Part B. Mix thoroughly using a mixing paddle or drill attachment. Periodically scrape the sides of the

container to ensure even mixing and prevent any unmixed material. Mix the components for about two minutes until a uniform color is obtained.

Application

1. Inject the mixed material into the cracks using a pressure injection equipment.
2. Start injection from the lowest port, gradually moving upwards to ensure complete filling of voids.
3. After the completion of material cure period, remove the injection ports and finish the surface as required.

Important Considerations for SWADI Inject 50+ application

• Inject 50+ is temperature and moisture sensitive. It should not be applied when temperatures are below 10°C or in extreme heat. • Avoid using the product in environments with high moisture of water ingress during application.

Cleaning

Inject 50+ should be cleaned immediately from tools after application, use Swadi® CleanEpoxy solvent. If in case the hardened material can only be removed mechanically.

Shelf Life

12 months when stored unopened sealed pack and out of direct sunlight.

Packaging

Inject 50+ is supplied in 6 Kg pack which includes 3 Kg Resin and 3 Kg Hardener.

Condition of Sale

Sold subject to the company's condition of sale which are available on request.

Storage and Handling Guidelines

The product should be stored as per national regulations in a cool, dry, and well-ventilated area, away from direct sunlight and extreme temperatures. Keep it out of reach of children. Ensure the container is tightly sealed when not in use. Handle with care to avoid contamination. Stir well before use and apply as per the recommended guidelines.

Environmental, Health, and Safety Information

For comprehensive information regarding the safe transportation, handling, storage, and disposal of this chemical product, please refer to the accompanying Safety Data Sheet (SDS). The SDS contains detailed information about physical properties, environmental impacts, toxicological hazards, and other safety-related factors. It is crucial to read the current SDS before using any product.

Disclaimer

The information provided in this datasheet is based on our extensive experience and is given in good faith to assist you. However, we reserve the right to update this information at any time without prior notice due to our ongoing research and development efforts. While we guarantee the consistent quality of our products, we cannot be held responsible for any losses or damages that may arise from their use if site conditions or the execution of work are not properly managed. This data sheet becomes invalid upon the publication of a new edition, and please contact us for the latest version. Please note that we do not provide any warranties regarding the results of our products in specific applications, as the storage, handling, and application of materials are factors beyond our control.

Contact Information

For immediate orders or enquires, contact our **24/7 support team at +91 8792919513 or enquiry@swadigroup.co.in**. For additional support options and resources, please visit our website at swadigroup.co.in

SWADI MINERALS AND CHEMICALS
an ISO 9001:2015 & ISO 14001:2015 certified company
Sy.no 70/1, Vishwaneedam post, Gollarahatti
Magadi main road, Bengaluru – 560091
Tel: +91 8884492928
Email: enquiry@swadigroup.co.in
Website: swadigroup.co.in

Product Data Sheet
Inject 50+
October 2025, Version 011.05.11000000000049

SWADI®
a step ahead...