PERFORMANCE
FLOORING SYSTEMS

SWADI®
a step ahead...

Seela Super 999

Two-component premium food grade epoxy waterproof coating

Description

Seela Super 999 is a Self-levelling underlayment polymer-modified cement that has superior flow characteristics, which flows with gravity to level uneven & rough surfaces. This provides an ultrasmooth and seamless finish to the floor. Super 999 comes with the latest modified technology which improves levelling, finishing, strength & durability.

Seela Super 999 is also known as Floating cement due to its ability to float and level the surface. The thickness of floor can be carried out from 3mm to 30mm which depends upon level and roughness of the surface.

The SS 999 powder is a single component ready-to use product, requiring a mix of water as per the powder: water ratio. As a result of the mixed viscosity, the product remains a homogeneous and a perfect integrational mix. Swadi offers premium quality self-levelling cement, which comes in two varieties based on floor requirements.

Where to Use

- Interior and exterior floor levelling and smoothing applications.
- Car parking areas and driveways.
- Resurfacing of uneven or high-traffic concrete floors.
- Used as an underlayment levelling cement floor before installation of vinyl, carpet, tiles, wooden, or epoxy/PU flooring systems.
- Warehouses, industrial spaces & production areas providing smooth & levelled floor finish.

Advantages

- Best self-levelling properties
- Can be applied on a Damp substrates
- Rapid hardening technology
- Can be layed upto thickness of 3 to 30mm
- Quick and easy to mix, can be pumped for larger areas

Technical Data

Consistency	Lumps free fine powder
Colour	Grey
Application temperature range	from 5°C to 45°C
Bulk density of powder	1.3 To 1.35 kg/l
Pot life	approx. 20 - 30 minutes
Initial Setting time	60 min at 3mm thick
Final setting time	8 hrs at 3 - 10mm thick
Set to light foot traffic	12 hours
Storage and shelf life	12 months - when stored in dry conditions
Overcoating	
Thinner application ≤6mm	24 Hrs
Thicker application 6mm to 10mm	48 Hrs
Thicker application 10mm to 30mm	72 Hrs

Flow Characteristics: (W/P) 22%, Test Temp: 30°C

Initial Flow (0 min)	340 mm
Flow after (10 min)	300 mm
Flow after (15 min)	280 mm
Compressive Strength	
After 28 days	25 - 30 N/mm²
Flexural Strength	
After 28 days	6 N/mm²
Coverage Estimates	
Pack size	25 Kg
Coverage	1.66 kg/m² per 1 mm of thickness

Seela Super 999

Application Instructions

Surface Preparation

The substrate must be clean, dry, hard, and free from dust, weak cementitious layers, curing compounds, paints, wax, grease, and other contaminants. New concrete should be cured for at least 14 days before application, while existing concrete has no time limit but must be properly prepared. The surface should have an open texture to ensure proper adhesion. If required, mechanical methods such as grinding, shot blasting, or scarification should be used for surface preparation. All loose particles must be removed using industrial vacuuming. Cracks, blowholes, and surface defects should be repaired with appropriate Swadi repair products.

Priming

Priming is essential for all surfaces to seal the substrate, prevent air release, and enhance adhesion of self-leveling compounds.

For porous or absorbent surfaces (e.g., cement screeds, RCC, and other absorbent substrates), pre-soak substrates with clean water, allow excess moisture to dry, and then apply Swadi SL Primer diluted 1:1 / 1:2 / 1:3 with water.

For highly porous or dry substrates, pre-soak with clean water, let the surface dry, and then apply undiluted SL Primer for better adhesion.

For non-porous or dense surfaces (e.g., vitrified tiles, mosaic, granite), use undiluted SL Primer to ensure strong bonding.

Mixing

In a clean mixing vessel, take 5 – 5.5 litres of clean water. Add the 25 kg Seela Super 999 powder to the rust-free bucket containing water and mix steadily and thoroughly until a slump-free, fluid consistency is obtained. The use of a mixing paddle with a 10 mm chuck ensures thorough mixing with maximum shear yet minimum air entrapment and heat build-up. For larger areas and higher thickness applications, use an electric rotor mixer and pump the mixed material directly to the site area for faster and uniform placement.

Application

Pour the mixed Swadi Self-Leveling Compound onto the prepared and primed substrate. Use a notched trowel or squeegee to spread the material evenly within its working time.

For air release, roll the surface with a spiked roller immediately after application. Spiked roller application is effective only for thicknesses ranging from 2mm to 6mm.

Ensure the working area is protected from direct sunlight and dry winds to prevent premature surface drying.

Application Instructions for Different Thicknesses

Swadi Self-Leveling Compound can be applied from 3mm to 30mm thick.

Guidelines for Different Thicknesses:
For thicknesses of 6mm to 15mm, incorporate up to 20% of the powder weight (Swadi Self-Leveling Compound) with 3mm clean, dry, coarse aggregate to improve stability.
Example: For a 25kg bag of Swadi Self-Leveling Compound, add 5 kg of coarse aggregates.

For applications exceeding 15mm up to 30mm, use 3–6mm clean, dry, fines-free, graded gravel in 25% of the total mix volume to enhance stability.
Example: For a 25kg bag of Swadi Self-Leveling Compound, add 6.25 kg of 3–6mm coarse aggregates.

Mix the self-leveling compound as per standard instructions and gradually add the aggregate without increasing the water content.

For further guidance, contact Swadi Technical Service Team.

Cleaning

Cleaning prior to setting, SEELA SUPER 999 can be cleaned and removed from tools and hands with water.

Packaging

25 kg bag.

Storage and Shelf Life / Precautions / Disposal / Spillage

For further information please refer to the Material Safety Data Sheet.

Conditions of Sale

Sold subject to the company's conditions of sale which are available on request.

Storage and Handling Guidelines

The product should be stored in accordance with national regulations. Store in a cool, dry, and well-ventilated area, away from direct sunlight, moisture, and extreme temperatures. Keep out of reach of children. To ensure optimal performance, mix the powder and liquid components as per the specified ratio. Once mixed, use the material within its working time to prevent premature setting.

Environmental, Health, and Safety Information

For comprehensive information regarding the safe transportation, handling, storage, and disposal of this chemical product, please refer to the accompanying Safety Data Sheet (SDS). The SDS contains detailed information about physical properties, environmental impacts, toxicological hazards, and other safety-related factors. It is crucial to read the current SDS before using any product.

Disclaimer

The information provided in this datasheet is based on our extensive experience and is given in good faith to assist you. However, we reserve the right to update this information at any time without prior notice due to our ongoing research and development efforts. While we guarantee the consistent quality of our products, we cannot be held responsible for any losses or damages that may arise from their use if site conditions or the execution of work are not properly managed.

This data sheet becomes invalid upon the publication of a new edition, and please contact us for the latest version. Please note that we do not provide any warranties regarding the results of our products in specific applications, as the storage, handling, and application of materials are factors beyond our control.

Contact Information

For immediate orders or enquires, contact our **24/7 support team at +91 8792919513 or enquiry@swadigroup.co.in**. For additional support options and resources, please visit our website at swadigroup.co.in

SWADI MINERALS AND CHEMICALS
an ISO 9001:2015 & ISO 14001:2015 certified company
Sy.no 70/1, Vishwaneedam post, Gollarahatti
Magadi main road, Bengaluru – 560091
Tel: +91 8884492928
Email: enquiry@swadigroup.co.in
Website: swadigroup.co.in

Product Data Sheet
Seela Super 999
October 2025, Version 011.05.11000000000051

SWADI®
a step ahead...