PERFORMANCE
CONSTRUCTION CHEMICALS

SWADI®
a step ahead...

SwadiFix TA03

Floor & Wall Tile Adhesive for Ceramic, Vitrified, & Stones
Conforms to IS 15477:2019 Standards as a Type 4T Adhesive

Description

Grey, cement-based high polymer fortified tile adhesive suitable for fixing tiles with less than 3% porosity, like vitrified, semi-vitrified tiles, and natural stones on both interior and exterior walls and floors.

Standard Compliance

Confirms to IS 15477: 2019 Type 4TS1
"Specification for Adhesives for use with Ceramic, Mosaic and Stone Tiles"
Classified as per requirements for cementitious adhesives (C), Confirms to EN 12004-2:2017, Adhesives for ceramic tiles, C2 TES1

Where to Use

TA03 is a higher-grade adhesive designed for demanding tile and stone installations, including granites and marbles. It is specifically used for large-format tiles exceeding 4x4 feet. Ideal for residential, commercial, and industrial spaces, it works effectively on concrete, cement screeds, and plastered surfaces.

Advantages

- Advanced polymer technology
- Micro-grain adhesion
- Fiber reinforced
- Excellent grip & stability
- No pre-soaking or curing required
- Easy to mix and apply

Product Data

Classification of adhesive	Type 4T | As per IS 15477:2019
Appearance	Grey powder
Mix density	1.8 g/cc
Pot life 27 ± 2°C IS 15477:2019	2- 2.5 hours
Setting time IS 15477:2019	24 hours
Foot traffic	After 24 hours
Grouting	After 8h for wall & 24h for floor

Technical Data

Properties tested as per IS 15477: 2019 @ 27 ± 2°C

Characteristic	Min. requirement	Test result
Tensile adhesion strength (as per Annex A, Clause 4.4)		
Dry condition	1.50 N/mm²	2 N/mm²
Wet condition	1.0 N/mm²	1.9 N/mm²
Shear adhesion strength (as per Annex B, Clause 4.5 & 4.6)		
Dry condition	1.50 N/mm²	1.95 N/mm²
Wet condition	1.0 N/mm²	1.71 N/mm²
Heat ageing condition	1.0 N/mm²	1.8 N/mm²
Open time (as per Annex C, Clause 4.7)	N.A.	30 minutes
Adjustability (as per Annex D, Clause 4.8)	N.A.	25 minutes
Slip (T) (as per Annex E)	<0.5 mm	No slip
Transverse deformation (as per Annex F)	S1 - ≥ 2.5mm and <5 mm	3mm

SwadiFix TA03

Properties tested as per EN 12004-2 : 2017 @ 24 ± 2°C

Characteristic	Min. requirement	Test result
Tensile adhesion strength (1d, Clause 8.3)		
Initial	≥ 1 N/mm²	2 N/mm²
Water immersion	≥ 1 N/mm²	1.8 N/mm²
Heat ageing	≥ 1 N/mm²	1.9 N/mm²
Freeze-thaw cycles	≥ 1 N/mm²	1.8 N/mm²
Open time: tensile adhesion strength (1e, Clause 8.1)	≥ 0.5 N/mm² after not less than 10 min	0.9 N/mm²
Slip (T) (1c, Clause 8.2)	≥ 0.5mm	No slip

Coverage

- 80 - 90 sqft / 30 kg bag at 3 mm thickness.
- 40 - 45 sqft / 30 kg bag at 6 mm thickness.

- 1 kg will cover 2.7 to 3.0 sqft at 3 mm thickness.
- 1 kg will cover 1.3 to 1.5 sqft at 6 mm thickness.

Coverage will vary depending on the surface condition, tile size, and application method. For optimal results, ensure the surface is smooth, level, and free from defects..

Surface Preperation

- The surface to be tiled should be sound and thoroughly cleaned.
- Surface should be free from wax, grease, polish etc.,

Mixing

- Ratio 1:4 (water: Adhesive) approx. 7.5ltr for 30kg Swadi Stone Bond Grey
- Use only clean water and mix them till the particular consistency occurred.

Application

- Spread not more than the area which can be tiled within the open time of the adhesive.
- Spread adhesive to a thickness of approx. 3-6mm and comb with notched trowel.
- Intermittently touch the adhesive paste on substrate by finger. If the adhesive sticks to fingers, then continue tiling and if not scrap off the adhesive and apply new coat.
- Start placing tiles on the surface to be tiled, tap the tiles properly to ensure complete coverage of the backside of tiles and to eliminate the possibility of any air voids.
- Keep joints between two tiles using spacers.
- Start filling joints only after 24 hrs. with SWADI Epoxy/Cementitious tile grouts which will enhance adhesion to tile edges, increase water-resistance and improves flexibility.

Cleaning

Clean any excess tile adhesive from the tile surface and joints immediately using a damp cloth or wet sponge before it hardens . The hardened adhesive can be removed from tools mechanically.

Precautions

- For laying tiles on floor, surface should be sufficiently hard & good condition.
- Always add powder to water & never add water to powder.
- Do not add excess water than recommended.
- Never add sand & cement at site.
- Apply only on suitable surface.
- Cement based adhesive, avoid contact with eyes and with the skin carefully by the use of gloves, eye protection. Wash contaminated skin thoroughly after handling.

Packaging

30kg bag

Shelf Life

12 months when stored in normal dry conditions, store in dry closed container for long life time.

Storage and Handling Guidelines

The product should be stored in a dry, well-ventilated area, away from moisture, direct sunlight, and children, and in compliance with national regulations. Ensure the packaging is tightly sealed to prevent contamination or moisture ingress, and store it within the recommended temperature range of 5°C to 35°C. Handle the product with care, avoiding direct contact with skin and eyes, and wear appropriate protective equipment such as gloves and masks to prevent inhalation of dust. Use the product as per the instructions provided on the packaging for best results.

Environmental, Health, and Safety Information

For comprehensive information regarding the safe transportation, handling, storage, and disposal of this chemical product, please refer to the accompanying Safety Data Sheet (SDS). The SDS contains detailed information about physical properties, environmental impacts, toxicological hazards, and other safety-related factors. It is crucial to read the current SDS before using any product.

Disclaimer

The information provided in this datasheet is based on our extensive experience and is given in good faith to assist you. However, we reserve the right to update this information at any time without prior notice due to our ongoing research and development efforts.

While we guarantee the consistent quality of our products, we cannot be held responsible for any losses or damages that may arise from their use if site conditions or the execution of work are not properly managed. This data sheet becomes invalid upon the publication of a new edition, and please contact us for the latest version. Please note that we do not provide any warranties regarding the results of our products in specific applications, as the storage, handling, and application of materials are factors beyond our control.

Contact Information

For immediate orders or enquires, contact our **24/7 support team at +91 8792919513 or enquiry@swadigroup.co.in.** For additional support options and resources, please visit our website at swadigroup.co.in

SWADI MINERALS AND CHEMICALS
an ISO 9001:2015 & ISO 14001:2015 certified company
Sy.no 70/1, Vishwaneedam post, Gollarahatti
Magadi main road, Bengaluru – 560091
Tel: +91 8884492928
Email: enquiry@swadigroup.co.in
Website: swadigroup.co.in

Product Data Sheet
SwadiFix TA03
October 2025, Version 011.05.11000000000003

SWADI®
a step ahead...