PERFORMANCE
CONSTRUCTION CHEMICALS

SWADI®
a step ahead...

AG02

Free Flow, High Early Strength, Non - Shrink, Cementitious Precision Grout & Chloride-Free

Description

SWADI - AG02 is supplied as a ready to use dry powder. The addition of controlled amount of clean water produces a free flowing, non-shrink grout for gap thickness up to 100mm. AG02 is a blend of Portland cement, graded fillers and chemical additives. The low water demand ensures high early strength. The grade fillers are designed to assist uniform mixing and produce a consistent grout.

Consistency in performance of grout is assured, as only recommended quantity of water is required to be added to the designed premix composition. The flowable and self-leveling properties ensure complete filling voids and perfect bearing. AG02 grout can be poured and compacted.

Standard Compliance

Complies with Standards IS 4031 (Part 6): 1988, IS 10158: 1982, IS 4031 (Part 5): 1988, IS 516, ASTM C 531.

Where to Use

SWADI AG02 grouts are ideally suited to withstand static and dynamic loads. Typical applications would be the grouting for anchor bolts, machine base plates, bearing plates, pre-cast wall panels, void filling requirements, bore packing, foundation bolts, Casting Cover blocks and also many other equipment foundations.

Advantages

- Free flow ensures high level of contact with load bearing area.
- Provides excellent dimensional stability under temperature variations.
- High strength ensures the durability of the hardened grout.
- Develops high early strength without the use of chlorides.
- Reducing water content accelerates strength development and high compressive values.
- Does not segregate even at high flow – while pumping.
- Versatile, can be applied in any consistency from dry pack to fluid just by varying water content.
- Mainly ease application and max field control, add water, mix and place.

Product Data

Color	Concrete grey
Application temperature range	From 5°C to 45°C
Density	2220 Kg/m³
Mix ratio (w/p)	150 ml/kg for pourable, 160 ml/kg for flowable
Mix ratio for aggregates	w/p- 0.17% Aggregate quantity – 0.40%, 10 kg @10mm sieved, well graded aggregates for 30kg bag. *use for >100mm thicker sections*
Set time	Initial- 1 to 2 hours Final – 48 hours
Expansion characteristics	0.2 – 4% expansion in the plastic state

Technical Data

Flow spread IS 5512 flow table test	≥ 220 mm

Compressive strength IS 4031(Part 6): 1988 Flowable (w/p-0.16%)	1 days: 20 - 30 MPa 7 days: 30 - 40 MPa 28 days: ≥60 MPa
Compressive strength with addition of aggregates (10mm) w/p - 0.17%	1 days: 20 - 30 MPa 7 days: 30 - 40 MPa 28days: ≥65 MPa
Tensile strength	3 N/mm² @28DAYS
Flexure strength	6.9 N/mm² @28 DAYS
Coefficient of thermal expansion	~10 × 10^{-6}/°C
Bleeding IS 9103:1999	0% bleeding
Chloride content IS 456:2000	<0.1%

Application Instructions

Surface Preparation

The Substrate surface must be free from oil, grease or any loosely adherent material. If the concrete surface is defective or has laitance, it must be cut back to a sound base. Bolt holes and fixing pockets must be blown clean of any dirt or debris.

Mixing

- For best results a mechanically powered grout mixer should be used. When quantities up to 50kg are used, a heavy-duty slow speed drill (400-500 rpm) fitted with a paddle is suitable.
- A larger quantity requires a heavy-duty mixer.
- The quantity of clean water required to be added to a 30kg bag to achieve the desired consistency (Pourable: 4.5 liters, Flowable: 4.8 liters).
- The selected water content should be accurately measured into the mixer; this will ensure that the grout has a smooth even consistency.
- When you observe dampness in grouting area use Swadi AG02 with Swadi TruBond 50 (SBR) with the mix ratio of (1kg AG02: 100ml water (0.1%): 60ml Swadi TruBond 50 (SBR) 0.06%).

Application

Mixed grout may be pumped or transported by buckets or wheelbarrows without any delay, place the grout within 20 minutes to earn great expansion benefits. Continuous grout flow is essential.

Curing

To achieve performance consistent with technical data, curing must be provided such as wet hessian cloth. Curing must commence immediately after placing and finishing.

Shelf Life

SWADI - AG02 has a shelf life of 12 months if kept in dry store in sealed bags, if exposed to rain or high temperatures shelf life may be reduced.

Health & Safety

For further information, please consult the Material Safety Data Sheet (MSDS).

Condition of Sale

Sold subjects to the company's condition of sale which are available on request.

Packaging

30 kg bag.

Storage and Handling Guidelines

The product should be stored in a dry, well-ventilated area, away from moisture, direct sunlight, and children, and in compliance with national regulations. Ensure the packaging is tightly sealed to prevent contamination or moisture ingress, and store it within the recommended temperature range of 5°C to 35°C. Handle the product with care, avoiding direct contact with skin and eyes, and wear appropriate protective equipment such as gloves and masks to prevent inhalation of dust. Use the product as per the instructions provided on the packaging for best results.

Environmental, Health, and Safety Information

For comprehensive information regarding the safe transportation, handling, storage, and disposal of this chemical product, please refer to the accompanying Safety Data Sheet (SDS). The SDS contains detailed information about physical properties, environmental impacts, toxicological hazards, and other safety-related factors. It is crucial to read the current SDS before using any product.

Disclaimer

The information provided in this datasheet is based on our extensive experience and is given in good faith to assist you. However, we reserve the right to update this information at any time without prior notice due to our ongoing research and development efforts.

While we guarantee the consistent quality of our products, we cannot be held responsible for any losses or damages that may arise from their use if site conditions or the execution of work are not properly managed. This data sheet becomes invalid upon the publication of a new edition, and please contact us for the latest version. Please note that we do not provide any warranties regarding the results of our products in specific applications, as the storage, handling, and application of materials are factors beyond our control.

Contact Information

For immediate orders or enquires, contact our **24/7 support team at +91 8792919513 or enquiry@swadigroup.co.in.** For additional support options and resources, please visit our website at swadigroup.co.in

SWADI MINERALS AND CHEMICALS
an ISO 9001:2015 & ISO 14001:2015 certified company
Sy.no 70/1, Vishwaneedam post, Gollarahatti
Magadi main road, Bengaluru – 560091
Tel: +91 8884492928
Email: enquiry@swadigroup.co.in
Website: swadigroup.co.in

Product Data Sheet
AG02
October 2025, Version 011.05.10900000000022

SWADI®
a step ahead...