PERFORMANCE
WATERPROOFING SYSTEMS

SWADI®
a step ahead...

# TruBond 50

## SBR Based Multipurpose Polymer for Waterproofing and Repair

### Description

TRUBOND 50 is a modified styrene-butadiene rubber emulsion, which substantially increases the quality & performance of cement slurries & mortars. It offers high durability, reduced shrinkage, and increased flexibility & bond strength. It is also used in conjunction with Portland cement for waterproof slurries or tight render basecoat.

### Where to Use

1.) For waterproofing of roof slabs, sunken slabs, basements, water tanks, sunshades etc. in combination with cement. 2.) Concrete repair: Spalled concrete, repairing floors, beams and pre - cast slabs, etc. 3.) For bonding new concrete to old concrete, plaster, stone / brick masonry. 4.) As a bonding agent for uses in repair and plastering. 5.) For making polymer mortar for repairs mortars etc.

### Advantages

- Simple to use - Single component, gauged as required.
- Higher abrasion resistance, good adhesion to building materials similar thermal characteristics to concrete.
- High flexural / tensile strength to control cracking.
- Compatible with all common hydraulic cements.
- Reduces the rate of aggressive chemical attack.
- Long life and watertight masonry jointing.
- Makes renders waterproof and gives durability & flexibility.

### Technical Data

| | |
|---|---|
| Cement sand ratio | 1:3 (50 kg cement : 150 kg sand) |
| Swadi TruBond 50 | (For 50 kg cement - 10 liters TruBond) |
| For waterproofing application | 1: 1.5 = SBR : Cement |
| Fresh wet density | 2000 - 2200 kg/m³ |
| pH | 8 |
| Solid content | 45% |

| Compressive strength | Days | Normal (kg/cm²) | TruBond 50 (kg/cm²) |
|---|---|---|---|
| | 28 days | 450 to 550 | 600 to 650 |
| Tensile strength | Days | Normal (kg/cm²) | TruBond 50 (kg/cm²) |
| | 28 days | 35.48 | 43.7 |
| Flexural strength | Days | Normal (kg/cm²) | TruBond 50 (kg/cm²) |
| | 28 days | 80.9 | 92.28 |
| Adhesion for bond coat | | >1.5 MPa or concrete failure | |

### Application Instructions

#### Surface Preparation

The object of the surface preparation is to achieve a clean sound surface with a good mechanical key. All substrates should be cleaned and free of dust, plaster, oil, paint, grease, corrosion deposits, and any other deleterious substances. Laitance should be removed by mechanical means. Smooth substrates must be mechanically roughened e.g., by scabbling, needle gun or grit blasting to provide an adequate key.

Corroded reinforcing steel should be exposed around its full circumference and cleaned to remove all loose scale and corrosion deposits. It is always preferably to clean the steel to a bright condition. Use of emery cloth, grit or sand blasting is recommended.

#### Mixing

- Use fresh, lump free cement, well graded sand/aggregates free of excessive fines.
- Mix sand and cement and coarse aggregate in Pan Type mixer for 1 -2 minutes. Hand mixing is only permissible when the total weight of the mix is less than 25 kg.
- Mix required quantity of Swadi TruBond 50 and water for 2 minutes in a separate container, to avoid excessive air entrapment.

- Finally, without delay, add the liquid mix slowly into the mixer containing the mixed powdered sand/coarse aggregate and cement until the required consistency is achieved.

### Mix Design

### For Repair Mortar

Mix 10 kgs of Swadi TruBond 50 : 50 kg of Cement: 150 kg of sieved sand : 10 kg of water.

### Application

- Repairing beams & pre - cast slabs.
- Repairing floors & spalled concrete.
- Repairing old substrates.
- Repair of corrosion damaged concrete.
- Bonding new concrete to old concrete, plaster, stone/brick masonry.
- As a bonding agent for uses in repair and plastering.
- For making polymer mortar for repairs mortars etc.

### For Floor Screeds

Mix 6 - 7 kgs of Swadi TruBond 50: 50 Kg of Cement : 75 kg of sand : 75 kg of coarse aggregate (6mm down) : 14 - 15 kgs of water. (1 polymer : 5 cement : 7.5 sand : 7.5 coarse aggregates : 1water).

### Application

For leveling of floor surface gives water and chemical resistance to screed.

### For Waterproofing Slurry

- Mix ratio - 1 : 1.5 = SBR : Cement
- After the first coat has dried, apply second coat at right angle to first follow by mortar/screed overlay. Average time gap between two coats is 3 to 4 hours. Consistency would be slurry.

### Use as a Polymer Additive for Cement / Sand Coverings and Renders

Mix 1 - part Swadi TruBond 50 with 3 parts water and use as the gauging mix (mixing water) with 1 : 3 or 1 : 4 (cement : sand) mix.

### Coverage

### Waterproofing Slurry

2 - 2.5 m² in two coats for mix of 1 kg Swadi TruBond 50 with 1.5 kg of cement (depends on porosity)

### Repair Mortar / Concrete Screed

10 kg of Swadi TruBond 50 per 50 kg of cement.

### Shelf Life

TruBond 50 has a shelf life of 12 months if kept in a dry store in unopened condition.

### Packaging

TruBond 50 is available in 1, 5 & 20 kg containers.

### Condition of Sale

Sold subject to the companies condition of sale which are available on request.

### Storage and Handling Guidelines

The product should be stored in accordance with national regulations. It is essential to keep it in a cool, well-ventilated area, away from heat, direct sunlight, sparks, and children.

### Health, and Safety Information

SWADI TruBond 50 is considered non-hazardous in normal usage; however, avoid contact with eyes or skin. Wear suitable protective dust mask, gloves and safety glasses. In case of contact with eyes, rinse for several minutes under running water.

For further information, please consult the Material Safety Data Sheet (MSDS).

### Disclaimer

The information provided in this datasheet is based on our extensive experience and is given in good faith to assist you. However, we reserve the right to update this information at any time without prior notice due to our ongoing research and development efforts. While we guarantee the consistent quality of our products, we cannot be held responsible for any losses or damages that may arise from their use if site conditions or the execution of work are not properly managed. This data sheet becomes invalid upon the publication of a new edition, and please contact us for the latest version.

Please note that we do not provide any warranties regarding the results of our products in specific applications, as the storage, handling, and application of materials are factors beyond our control.

## Contact Information

For immediate orders or enquires, contact our **24/7 support team at +91 8792919513 or enquiry@swadigroup.co.in.** For additional support options and resources, please visit our website at swadigroup.co.in

**SWADI MINERALS AND CHEMICALS**
an ISO 9001:2015 & ISO 14001:2015 certified company
Sy.no 70/1, Vishwaneedam post, Gollarahatti
Magadi main road, Bengaluru – 560091
Tel: +91 8884492928
Email: enquiry@swadigroup.co.in
Website: swadigroup.co.in

Product Data Sheet
TruBond 50
October 2025, Version 011.05.11000000000043