PERFORMANCE
WATERPROOFING SYSTEMS

SWADI®
a step ahead...

TruBond FG 100

Two-component premium food grade epoxy waterproof coating

Description

TruBond FG 100, the water-based epoxy impermeable shield. Two-component waterproof coating with modified water base hardener and graded fillers. It is a lead-free, non-toxic, anti-fungal, anti-corrosive, which has multiple attributes to make it an ideal choice for potable water tanks, water retaining structures, and concrete. Its advanced formulation ensures protection and compliance with stringent standards for safety and performance.

Standard Compliance

- Complies with Standards ASTM D 412, ASTM C 836, ASTM D 3960 & ASTM 2369.
- Complies to CFTRI & BS 6920 for potable water tank application, suitability of non-metallic products for use in contact with water intended for human consumption with regard to their effect on the quality of the water.

Where to Use

TruBond FG 100 is used to protect and prevent water leakage and penetration of moisture into the Concrete and other masonry surfaces. TruBond FG100 is ideal for: Tanks, Water retaining structures & concrete.

Benefits

- Easy to use & apply.
- Low VOC & lead free.
- Best formulated for safe & hygienic storage.
- Food-grade coating for water tanks etc.,
- Anti-corrosive & anti-fungal.

Technical Data

Appearance	Part A (White colored resin) Part B (Hardener)
Mix ratio	2:1 (Resin: Hardener)
Density @27°C	Approx. 1.5 g/cc
Pot life	30 minutes
Solid content ASTM 2369	80%
Recoating duration	12 – 16 Hrs
Initial hardness@25°C	24 hours @30°C
Full cure	7 days @30°C
Colors available	White

Typical cured membrane properties @28 days

VOC Content	<5 g/l
Tensile strength, N/mm2 (ASTM D 412)	>15 mPa
Shore Hardness (ASTM C 836)	70 - 80
Bond strength (ASTM C 836)	>1.5 mPa

Application Instructions

Surface Preparation

The object of the surface preparation is to achieve a clean sound surface with a good mechanical key. All substrates should be cleaned and free of dust, plaster, oil, paint, grease, corrosion deposits, and any other deleterious substances. Laitance should be removed by mechanical means. Smooth substrates must be mechanically roughened e.g., by scabbling, needle gun or grit blasting to provide an adequate key.

Corroded reinforcing steel should be exposed around its full circumference and cleaned to remove all loose scale and corrosion deposits. It is always preferably to clean the steel to a bright condition. Use of emery cloth, grit or sand blasting is recommended. New concrete slabs must be allowed to cure for at least 28 days.

For best results, ensure that the surface is fully cured and free from visible moisture before priming. It is essential that TruBond FG 100 is applied directly over solid concrete or plaster surfaces. Application over weak skim coats or damp substrates must be strictly avoided, as this may lead to delamination or peeling.

TruBond FG 100

Priming

Before applying TruBond FG 100, it is recommended to prime the surface using Evoshine Primer W11, a two-component, water-based epoxy primer. The primer should be mixed in the ratio of Resin (Part A): 3 parts to Hardener (Part B): 1 part by volume. Mix thoroughly using a slow-speed drill or paddle mixer until a uniform blend is achieved. The primer should then be applied evenly with a brush or roller to ensure complete surface penetration. The mixed primer has a pot life of approximately 30 minutes. After application, the primer must be allowed to cure for a minimum of 24 hours, or until it is fully dry and hard to the touch, before proceeding with the topcoat application.

Application Procedure

TruBond FG 100 is supplied as a two-component epoxy system comprising Part A (Resin) and Part B (Hardener). These should be mixed in the ratio of 2 parts Resin to 1 part Hardener by volume. Use a slow-speed mechanical stirrer (200–300 rpm) to mix both components for about 2 minutes, ensuring a homogeneous blend. Overmixing or mixing at high speed should be avoided as it may introduce air bubbles into the material. Once mixed, the product must be used within its pot life of 20 minutes.

Apply the coating in two uniform coats using a soft polyurethane (PU) roller. A brush may be used for corners, edges, or areas inaccessible to rollers. Ensure that the primer is completely dry and cured before applying the first coat of TruBond FG 100. Maintain a recoat interval of 8 to 12 hours between coats, depending on ambient temperature and humidity.

Freshly coated surfaces must be protected from dust, water, and other contaminants during curing. Full curing and water exposure resistance is typically achieved after 7 days under standard conditions.

Important Considerations for SWADI TruBond FG 100 Application

- Apply only after concrete or plaster has cured for at least 28 days.
- Do not apply below 50°C or above 40°C.
- Surface must be completely dry — no moisture or dampness.
- Do not apply over skim coats or weak substrates.
- Apply directly on sound concrete or plaster.
- Avoid water contact for 7 days after final coat for full curing.
- Ensure no dust, oil, or loose particles before
- priming.
- Do not dilute or alter mix ratio of components. Wear proper safety gear during application.

Coverage

Evoshine PrimerW11: 30 - 40 Sqfts/Kg
(Coverage might vary depending on the porosity of concrete substrate).
TruBond FG 100: 25 - 30 Sqfts/Kg/2 Coats

Shelf Life

TruBond FG 100 has a shelf life of 7 months if kept in a dry store in unopened condition.

Packaging

TruBond FG 100 is available in 6 Kg Pack.

Condition of Sale

Sold subject to the company's condition of sale which are available on request.

Cleaning

Tools and equipment should be washed with water immediately after use.

Storage and Handling Guidelines

The product should be stored as per national regulations in a cool, dry, and well-ventilated area, away from direct sunlight and extreme temperatures. Keep it out of reach of children. Ensure the container is tightly sealed when not in use. Handle with care to avoid contamination. Stir well before use and apply as per the recommended guidelines.

Environmental, Health, and Safety Information

For comprehensive information regarding the safe transportation, handling, storage, and disposal of this chemical product, please refer to the accompanying Safety Data Sheet (SDS). The SDS contains detailed information about physical properties, environmental impacts, toxicological hazards, and other safety-related factors. It is crucial to read the current SDS before using any product.

Disclaimer

The information provided in this datasheet is based on our extensive experience and is given in good faith to assist you. However, we reserve the right to update this information at any time without prior notice due to our ongoing research and development efforts. While we guarantee the consistent quality of our products, we cannot be held responsible for any losses or damages that may arise from their use if site conditions or the execution of work are not properly managed. This data sheet becomes invalid upon the publication of a new edition, and please contact us for the latest version. Please note that we do not provide any warranties regarding the results of our products in specific applications, as the storage, handling, and application of materials are factors beyond our control.

Contact Information

For immediate orders or enquires, contact our **24/7 support team at +91 8792919513 or enquiry@swadigroup.co.in**. For additional support options and resources, please visit our website at swadigroup.co.in

SWADI MINERALS AND CHEMICALS
an ISO 9001:2015 & ISO 14001:2015 certified company
Sy.no 70/1, Vishwaneedam post, Gollarahatti
Magadi main road, Bengaluru – 560091
Tel: +91 8884492928
Email: enquiry@swadigroup.co.in
Website: swadigroup.co.in

Product Data Sheet
TruBond FG 100
October 2025, Version 011.05.11000000000050

SWADI®
a step ahead...