PERFORMANCE
WATERPROOFING SYSTEMS

SWADI®
a step ahead...

# TruBond PU

## High Performance, Polyurethane Hybrid UV Stable, Water - Based Waterproofing Membrane

### Description

TruBond PU is a single-component, liquid applied, elastomeric polyurethane coating for waterproofing of concrete and masonry surfaces. TruBond PU provides excellent resistance to moisture, water, and salts penetration into concrete and masonry surfaces.

### Standard Compliance

TruBond PU conforms to ASTM C836-03 for high-performance, fluid-applied waterproofing membrane and meets ASTM D412, D7234, E96, D2369, G154, and D4060.

### Where to Use

1.TruBond PU is used to protect and prevent water leakage and penetration of moisture into the Concrete and other masonry surfaces. TruBond PU is ideal for:
2.Waterproofing RetainingWalls, Podiums, Sunken Slabs, Terraces & Swimmingpools.

### Advantages

- Liquid applied membrane, can be appliedwith roller, brush or spray.
- Non-toxic, Provides a seamless coating.
- Flexible, has crack bridging ability.
- High bond strength to a varietyof substrates and building materials.
- Resists positive water pressure.
- Resistant to chemicals.
- Excellent resistance to humidity and temperature.
- Excellent resistance to Chlorides and Alkali.
- Very high tensile strength.

### Product Data

| | |
|---|---|
| Appearance | Milky, White emulsion |
| Application temperature range | 10°C to 40°C |
| Viscosity @30°C (Brookfield RVF 4/20) | ~13000 – 15000 cps |
| pH | 8 |
| Density at 27°C | Approx. 1.17 g/cc |
| Solid content ASTM D 2369 | ~60% |
| Recoating | 3-5 hours at 20°C |
| Cure time at 25°C | 5-7 days |

### Technical Data

| | |
|---|---|
| Elongation at break ASTM D412 | 550% |
| Shore hardness ASTM C 836 | 70 - 80 |
| Crack bridging ASTM C 836 | Up to 1.5 mm |
| Tear resistance ASTM D 624 | 9 - 10 N |
| Moisture vapor permeability ASTM E 96 | ~7g/m²/24 hrs |
| UV resistance ASTM G 154 | No degradation, cracks or yellowing after 1000 hours |
| Abrasion resistance ASTM D 4060 | <100 mg loss CS-17 wheel, 1000 cycles |
| Pull of adhesion strength ASTM C 7234 | >2 mpa |

### Application Instructions

#### Surface Preparation

The object of the surface preparation is to achieve a clean sound surface with a good mechanical key. All substrates should be cleanedand free of dust, plaster,oil, paint, grease, corrosion deposits, and any other deleterious substances. Laitance should be removed by mechanical means. Smoothsubstrates must be mechanically roughened e.g., by scabbling, needle gun or grit blasting to provide an adequate key.

# TruBond PU

Corroded reinforcing steel should be exposed aroundits full circumference and cleaned to remove all loose scale and corrosiondeposits. It is always preferably to clean the steel to a bright condition. Use of emery cloth, grit or sand blasting is recommended.

## Fillet Preparation

Horizontal and verticalangle joints need to be prepared with 50x50mm concavefillet using SWADI AG06 FS(Non shrink grout) or concrete admixed with Trubond 50 SBR, 8-9 liters per 50Kg bag of cement. Fillet should be cured togain strength and completely dry before Primer application.

## Priming

Epoxy based Primer Evoshine Primer W11 a two-component primer is recommended before application of TruBond PU. Mix both the components of Primer and apply by brush on cleaned concrete. Pot life of the mixed primer is only 30 minutes. Allow the primer to dry for 4-5hours. Apply the water proofing coating TruBond PU when the Primer is tacky.

## Application Procedure

Prior to application, thoroughly mix the contents of the container using a slow speed stirrer at 300 rpm. Care should be taken to scrape the sides and bottom of the container with the mixer. Do not add solvent, thinners, water at any time.

After mixing, immediately apply TruBond PU over the tacky primer while ensuring a continuous coating of uniform thickness. A soft roller is recommended for such application. A brush may be used for touch-up and edging work or for areas unsuitable for roller application.

TruBond PU must be applied all along the angle fillets, corners, joints around the pipes, conduits etc. Apply TruBond PU on surrounding walls up to a height of minimum 300mm from FFL. Always apply in two coats in order to avoid pinholes. The second coat can be applied after the first coat has dried (12 – 16 hours)depending on the ambient and surface temperature.

## Protection with Screed

Prior to layingof protection screed,use a separation barrier of 160 gsm Geo Textile.Screed to be applied as per slope requirement. For vertical application 15 – 20mm plaster is recommended.

## Coverage

1.5 - 2kg/m² for 1mm thickness.

## Shelf Life

TruBond PU has a shelf life of 12 months if kept in a dry store in unopened condition.

## Packaging

TruBond PU is available in 20kg Pail.

## Important Considerations for SWADI TruBond PU Application

• Never apply to new concrete surfaces before they have been allowed to cure for a minimum of 28 days. • Do not apply if the temperature is in excess of 40°c or less than 5°c. • Do not apply on wet or damp surfaces. Before the application primer the surface must be in dry condition. • Do not apply if rain is expected in the proceeding 24 hours.

## Condition of Sale

Sold subject to the company's condition of sale which are available on request.

## Cleaning

Tools and equipment should be washed with water immediately after use.

## Storage and Handling Guidelines

The product should be stored as per national regulations in a cool, dry, and well-ventilated area, away from direct sunlight and extreme temperatures. Keep it out of reach of children. Ensure the container is tightly sealed when not in use. Handle with care to avoid contamination. Stir well before use and apply as per the recommended guidelines.

## Environmental, Health, and Safety Information

For comprehensive information regarding the safe transportation, handling, storage, and disposal of this chemical product, please refer to the accompanying Safety Data Sheet (SDS). The SDS contains detailed information about physical properties, environmental impacts, toxicological hazards, and other safety-related factors. It is crucial to read the current SDS before using any product.

## Disclaimer

The information provided in this datasheet is based on our extensive experience and is given in good faith to assist you. However, we reserve the right to update this information at any time without prior notice due to our ongoing research and development efforts. While we guarantee the consistent quality of our products, we cannot be held responsible for any losses or damages that may arise from their use if site conditions or the execution of work are not properly managed. This data sheet becomes invalid upon the publication of a new edition, and please contact us for the latest version. Please note that we do not provide any warranties regarding the results of our products in specific applications, as the storage, handling, and application of materials are factors beyond our control.

## Contact Information

For immediate orders or enquires, contact our **24/7 support team at +91 8792919513 or enquiry@swadigroup.co.in**. For additional support options and resources, please visit our website at swadigroup.co.in

**SWADI MINERALS AND CHEMICALS**
an ISO 9001:2015 & ISO 14001:2015 certified company
Sy.no 70/1, Vishwaneedam post, Gollarahatti
Magadi main road, Bengaluru – 560091
Tel: +91 8884492928
Email: enquiry@swadigroup.co.in
Website: swadigroup.co.in

Product Data Sheet
TruBond PU
October 2025, Version 011.05.11000000000047

SWADI®
*a step ahead...*