PERFORMANCE
CONSTRUCTION CHEMICALS

SWADI®
a step ahead...

Block Fix Adhesive - BFA06

A heavy-duty thin-bed block jointing adhesive used for AAC & lightweight blocks

Description

SWADI Block Fix Adhesive BFA06 is high quality dry mortar for fixing of concrete blocks, hollow bricks, fly ash bricks, AAC blocks, soil cement block, earthen terracotta blocks. It is premix of graded sand and cement specially designed with polymers which combine to give high strength and stability. This can be used at 3-6 mm thickness instead of conventional mortar which requires at 15-20 mm thick.

Where to Use

1.) Laying and jointing of fly ash bricks, cement blocks, hollow blocks, AAC blocks etc. 2.) Jointing of pre-stressed concrete slabs, panels. 3.) Parapet walls 4.) Jointing of cement window and door frames. 5.) Garden and boundary walls.

Advantages

- Economical and easy application.
- Crack resistance and non-shrink.
- Excellent durable & eco friendly.
- Excellent adhesion strength.
- Suitable for all types of blocks.
- Self curing mortar.
- Consistent mix quality.
- Thin bed Instead of conventional thick bed.

Technical Data

Binder	Portland Cement + Polymers
Colour	Grey
Water requirement	8 to 8.8 litres per 40 kg
Open & adjustable time	30 minutes
Working time (Pot life)	Approx. 120 min
Initial setting time	4 hours
Final setting time	12 hours
Tensile adhesion strength 28 days	≥1.00 Mpa
Compressive strength	≥9 Mpa
Flexural strength	≥2.50 Mpa
Storage & shelf life	12 months from date of manufacture, when stored in dry conditions

Application Instructions : For Interior and Exterior Thin Laying Mortar

Surface Preparation

Prepare the surfaces before the application by removing oil, bond inhibiting agents, dirt, dust and laitance. The cleaning can be carried out with suitable methods like by using wire brush, water jetting, mopping etc. Prewetting of substrate is essential with maximumsaturation. Wet the concrete blocks before applicationof BFA06 to avoid any abrupt absorption of water fromthe material.

Coverage

Thickness	Coverage for 40 kg bag
3 mm	95 Sqft
4 mm	75 Sqft
5 mm	60 Sqft
6 mm	50 Sqft

Mixing

- SWADI BFA06 requires 20% to 22% of water by the weight of BFA06. Approx. 8 to 8.8 liters for 40 kg bag.
- Use only clean water and mix them till the particular consistency occurred.

Application

Place the mixed mortar on the block work in thin layers of 3 to 6 mm (or as required by engineers at site) using trowel & place next layer of blocks on the mortar. Keep joints between blocks as required by the site engineers & fill the joints with the mixed mortar, using a trowel. Check the plumb of wall while laying blocks to keep the walls perfectly vertical to the plumb. 1. Concrete Blocks 2. Cement Mortar Blocks / Bricks 3. Concrete Hollow Blocks 4. Aerated Light weight Blocks 5. Cellular Concrete Blocks 6. Fly ash Bricks 7. AAC Blocks.

Block Fix Adhesive - BFA06

Cleaning

Clean tools and containers with water while mortar is fresh.

Precautions

Block Fix Adhesive - BFA06 is non-toxic. Use of gloves and goggles recommended. Any splashes to the skin or eyes should be washed off with clean water. In case of prolonged irritation, medical advice should be sought.

Health & Safety

For further information, please consult the Material Safety Data Sheet (MSDS).

Condition of Sale

Sold subject to the company's conditions of sale which are available on request.

Packaging

40 kg bag.

Shelf Life

12 months when stored in normal dry conditions, store in dry closed container for long life time.

Storage and Handling Guidelines

The product should be stored in a dry, well-ventilated area, away from moisture, direct sunlight, and children, and in compliance with national regulations. Ensure the packaging is tightly sealed to prevent contamination or moisture ingress, and store it within the recommended temperature range of 5°C to 35°C. Handle the product with care, avoiding direct contact with skin and eyes, and wear appropriate protective equipment such as gloves and masks to prevent inhalation of dust. Use the product as per the instructions provided on the packaging for best results.

Environmental, Health, and Safety Information

For comprehensive information regarding the safe transportation, handling, storage, and disposal of this chemical product, please refer to the accompanying Safety Data Sheet (SDS). The SDS contains detailed information about physical properties, environmental impacts, toxicological hazards, and other safety-related factors. It is crucial to read the current SDS before using any product.

Disclaimer

The information provided in this datasheet is based on our extensive experience and is given in good faith to assist you. However, we reserve the right to update this information at any time without prior notice due to our ongoing research and development efforts. While we guarantee the consistent quality of our products, we cannot be held responsible for any losses or damages that may arise from their use if site conditions or the execution of work are not properly managed. This data sheet becomes invalid upon the publication of a new edition, and please contact us for the latest version. Please note that we do not provide any warranties regarding the results of our products in specific applications, as the storage, handling, and application of materials are factors beyond our control.

Contact Information

For immediate orders or enquires, contact our **24/7 support team at +91 8792919513 or enquiry@swadigroup.co.in**. For additional support options and resources, please visit our website at swadigroup.co.in

SWADI MINERALS AND CHEMICALS
an ISO 9001:2015 & ISO 14001:2015 certified company
Sy.no 70/1, Vishwaneedam post, Gollarahatti
Magadi main road, Bengaluru – 560091
Tel: +91 8884492928
Email: enquiry@swadigroup.co.in
Website: swadigroup.co.in

Product Data Sheet
Block Fix Adhesive - BFA06
October 2025, Version 011.05.11000000000014

SWADI®
a step ahead...