PERFORMANCE
FLOORING SYSTEMS

SWADI®
a step ahead...

Concrete Densy 1K (S)

Sodium based densifier for concrete

Description

Swadi Concrete Densy 1K [S] is a ready-to-use, water-based sodium silicate concrete densifier. It penetrates into the concrete surface, reacts with calcium silicates in concrete. This reaction process increases concrete surface hardness, abrasion resistance, reduces dusting, and improves durability and gloss of concrete. It is suitable for new & old concrete surfaces.

Where to Use

1.) Industrial spaces
2.) Warehouses
3.) Heavy storage spaces
4.) Car parking areas and more.

Advantages

1.) Sodium-based densifying process gives dust-free, heavy wear-resistant concrete.
2.) Hardens and strengthens concrete surface
3.) Reduces dusting and makes cleaning easier
4.) Eco-friendly and zero VOC

Technical Data

Appearance	Liquid
Colour	Clear to hazy
pH	10 (Alkaline)
Density	1.3 kg/L
Chemical composition	Sodium Silicate
VOC content	<5 g/L
Application temparature	5°C to 40°C
Set to foot traffic	After 3 hours
Storage & shelf life	12 months - when stored in dry conditions

Coverage Estimates

Pack size	20 kg & 200 kg barrel
Coverage	Approx. 5-6 m²/kg per coat. Coverage will vary depending on surface profile, porosity and absorption. Apply until the substrate is fully saturated. Conduct a test area

Application Instructions

Surface Preparation

All dust, dirt, laitance, loose or friable materials must be removed by vacuum or brush. Substrates must be clean, dry and absorbent for better penetration.

If cleaning with water jetting is required, allow to dry it completely before application. If its a fresh concrete allow it cure properly for 28 days to attain its maximum strength. Concrete must have a minimum strength of 25 MPa and surface must be finished by power trowelling using Swadi Hardtop (Concrete floor hardener) to make dense and abrasion-resistant surface.

Mixing

Take required amount of Densy 1K (S) liquid and add clean water in 1:2 or 1:3 in ratios depends upon porosity of concrete densification.

Detailed Application Process

Step 1: Commence coarse grinding with metal-bonded diamond grits of 120, followed by 200 grade, using water as required. This process removes the worn-out top layer and exposes a firm, sound concrete surface.

Step 2: Buff the surface with PVC grits of 100 to smoothen and level the substrate. Use water if necessary depending on floor condition. Clean the surface thoroughly and allow it to dry.

Step 3: Pour the required quantity of Swadi Densy 1K (S) depending on the absorption capacity of the concrete.
Spread uniformly with an industrial-grade brush, using light sprinkling of water if dilution is required. Ensure proper penetration by working in to-and-fro motions.

Step 4: Remove any excess material and allow the surface to dry for 8–10 hours. Buff again with 200 grade PVC grit (wet process). Clean the surface thoroughly with an industrial brush to remove fine dust.

Step 5: Initiate progressive dry polishing using PVC grits in sequence: 400 → 800 → 1500 → 3000 to achieve the desired finish.

Step 6: Surface must be regularly cleaned with clean water and mopping for long lasting appearance.

Cleaning

Clean all tools with regular water.

Packaging

20 kg pack & 200 kg barrel.

Storage and Shelf Life / Precautions / Disposal / Spillage

For further information please refer to the Material Safety Data Sheet.

Conditions of Sale

Sold subject to the company's conditions of sale which are available on request.

Storage and Handling Guidelines

The product should be stored in accordance with national regulations. Store in a cool, dry, and well-ventilated area, away from direct sunlight, moisture, and extreme temperatures. Keep out of reach of children. Product is for industrial use only, handled by trained proffesionals.

Environmental, Health, and Safety Information

For comprehensive information regarding the safe transportation, handling, storage, and disposal of this chemical product, please refer to the accompanying Safety Data Sheet (SDS). The SDS contains detailed information about physical properties, environmental impacts, toxicological hazards, and other safety-related factors. It is crucial to read the current SDS before using any product.

Disclaimer

The information provided in this datasheet is based on our extensive experience and is given in good faith to assist you. However, we reserve the right to update this information at any time without prior notice due to our ongoing research and development efforts. While we guarantee the consistent quality of our products, we cannot be held responsible for any losses or damages that may arise from their use if site conditions or the execution of work are not properly managed. This data sheet becomes invalid upon the publication of a new edition, and please contact us for the latest version. Please note that we do not provide any warranties regarding the results of our products in specific applications, as the storage, handling, and application of materials are factors beyond our control.

Contact Information

For immediate orders or enquires, contact our **24/7 support team at +91 8792919513 or enquiry@swadigroup.co.in**. For additional support options and resources, please visit our website at swadigroup.co.in

SWADI MINERALS AND CHEMICALS
an ISO 9001:2015 & ISO 14001:2015 certified company
Sy.no 70/1, Vishwaneedam post, Gollarahatti
Magadi main road, Bengaluru – 560091
Tel: +91 8884492928
Email: enquiry@swadigroup.co.in
Website: swadigroup.co.in

Product Data Sheet
Concrete Densy 1K (S)
October 2025, Version 011.05.11000000000063

SWADI®
a step ahead...