PERFORMANCE
FLOORING SYSTEMS

SWADI®
a step ahead...

EvoShine Screed ES22

Self-Levelling Epoxy Underlay Screed

Description

EVOSHINE ES22 is a solvent-less epoxy-based self-leveling screed suitable for applying 1 mm to 5 mm self leveling underlay to cover surface imperfections and unevenness on concrete substrates. Its self-leveled three-component epoxy system provides a proper base for the application of self-leveling top coats. EVOSHINE ES22 consists of special resins and graded aggregates formulated to withstand chemical attack and impact shock.

Where to Use

Screed application is normally recommended for areas where medium-high load movement is envisaged. Heavy mechanical load and high abrasion resistance requirements of concrete and Masonry substrates are suggested with a built of 1-5 mm screed, before going in for floor coating finishes.

Advantages

1) Provides a flat and level surface.
2) Quick & easy to lay.
3) Excellent Adhesion.
4) High Compressive Strength.
5) Excellent impact resistance to heavy mechanical load.
6) High abrasion resistance.
7) Excellent bond to epoxy and PU top coats.

Product Data

Type	Epoxy-Phenalkamine
Appearance / Colour	Part A: Resin – Pale yellow / clear Part B: Hardener –Brown Part C: Filler – Off white Parts A+B+C mixed: Brown
Mixing ratio	1:0.5:3 (Resin: Hardener : Filler) by weight
Finish	Matt finish
Density (@ +20°C)	Part A: Resin: ~ 1.13 gm/cc Part B: Hardener: ~ 0.95 gm/cc Part C: Filler: ~ 1.79 gm/cc Parts A+B+C mixed: ~ 1.5 gm/cc
Solid content by volume (ASTM D-2697)(ASTM D 638)	≥ 92 %
Volatile organic compound (VOC) content (ASTM D-2369-81)	< 11.5 g/l
Pot life (ASTM D 2471)	~ 30 - 40 min
Drying time @25°C (ASTM D 1640)	
Surface dry	≥ 5 hrs
Tack free dry	≥ 8 hrs
Hard dry	≥ 24 hrs
Full cure	7 days
Recommended DFT (ASTM D 7091)	~ 1mm to 5mm

Technical Data

Tensile Strength @7 days (ASTM D 882)	~ 21.6 MPa
Modules of Elasticity @28 days (ASTM D 882)	~ 1366 MPa
Compressive Strength @28 days (ASTM C 579)	~ 60 MPa
Pull off adhesion test (ASTM D 4541)	≥ 2 MPa for M20 grade concrete or concrete failure

Salt spray test (5% Nacl)	~ 320 hrs passes

Application Data

Theoretical coverage	12 Sqm / 1 mm / 18 kg kit. 30 Sqm / 45 kg kit / 1 mm thickness. Note: Surface texture and porosity can affect coverage rate.
Application	By notched trowel & spike roller
Overcoat duration	Min. 12 hrs
Cleaning	Use only compatible thinner to kept equipment's clean, we recommend Swadi Clean epoxy thinner
Shelf life	12 months in the un-opened container

Application Instructions

Surface Preparation

For Existing/Old Concrete Surfaces

Thoroughly clean the surface to remove any dirt, dust, debris, or loose particles. Use a wire brush, pressure washer, or other suitable tools to ensure a clean substrate. Ensure the surface is completely dry before application.

For Fresh Concrete Surfaces:

Ensure the concrete has reached sufficient strength before applying Cem-Link 52. Refer to the concrete manufacturer's recommendations for curing times. Remove any laitance or curing compounds from the surface using a suitable cleaning agent and water. Allow to dry completely.

General Considerations:

Surface Profile

For optimal adhesion, the surface should have a suitable profile. A lightly roughened surface is generally preferred.

Moisture Content

For concrete maximum residual moisture content is below 5%, Ensure the surface is dry before application.

Temperature

The ambient temperature should be within the recommended range for the product. Prefer to work within the range of temperature 18°C to 34°C.

Packaging

Evoshine Screed ES22 is supplied in 18 kg pack, which contains 4 kg (Resin), 2 kg (Hardener), 12 kg (Graded Filler) & in 45 kg kit, which contains 10 kg (Resin), 5 kg (Hardener), 30 kg (Graded Filler).

Shelf Life

12 months when stored unopened sealed pack and out of direct sunlight.

Storage and Handling Guidelines

The product should be stored in accordance with national regulations. It is essential to keep it in a cool, well-ventilated area, away from heat, direct sunlight, sparks, and children. Please note that the product contains flammable solvents, so handle it with care. To ensure proper curing, mix the resin and hardener according to the specified ratio. Once mixed, use the solution within its pot life to avoid premature hardening.

Environmental, Health, and Safety Information

For comprehensive information regarding the safe transportation, handling, storage, and disposal of this chemical product, please refer to the accompanying Safety Data Sheet (SDS). The SDS contains detailed information about physical properties, environmental impacts, toxicological hazards, and other safety-related factors. It is crucial to read the current SDS before using any product.

Disclaimer

The information provided in this datasheet is based on our extensive experience and is given in good faith to assist you. However, we reserve the right to update this information at any time without prior notice due to our ongoing research and development efforts. While we guarantee the consistent quality of our products, we cannot be held responsible for any losses or damages that may arise from their use if site conditions or the execution of work are not properly managed. This data sheet becomes invalid upon the publication of a new edition, and please contact us for the latest version. Please note that we do not provide any warranties regarding the results of our products in specific applications, as the storage, handling, and application of materials are factors beyond our control.

Contact Information

For immediate orders or enquires, contact our **24/7 support team at +91 8792919513 or enquiry@swadigroup.co.in.** For additional support options and resources, please visit our website at swadigroup.co.in

SWADI MINERALS AND CHEMICALS
an ISO 9001:2015 & ISO 14001:2015 certified company
Sy.no 70/1, Vishwaneedam post, Gollarahatti
Magadi main road, Bengaluru – 560091
Tel: +91 8884492928
Email: enquiry@swadigroup.co.in
Website: swadigroup.co.in

Product Data Sheet
EvoShine Screed ES22
October 2025, Version 011.05.11000000000055

SWADI®
a step ahead...