

UNIVERSITÉ GRENOBLE ALPES



Numerical and experimental study of the
thermo-hydro-mechanical behavior of concrete
under severe accident conditions using a
poro-mechanical approach

Tan Kiet HONG

This thesis is submitted in partial fulfillment of the requirements for the Master's degree in the International Program "Geomechanics, Civil Engineering and Risks".

The work was carried out during the Master 2 internship at 3SR Laboratory.

Supervisors

Prof. Julien BAROTH, Université Grenoble Alpes

Prof. Stefano DAL PONT, Université Grenoble Alpes

Grenoble, June 2026

Acknowledgment

[REVIEW] This chapter is currently a draft version and will undergo further review and revision.

I would like to express my sincere gratitude to my amazing supervisors, Prof. Julien BAROTH and Prof. Stefano DAL PONT, for their guidance and valuable advice throughout this work.

I also thank the 3SR Laboratory for providing an excellent research environment and for the support I received during my internship.

Finally, I would like to thank my family for their constant encouragement, patience, and support throughout my studies and the completion of this thesis.

Abstract

[REVIEW] This chapter is currently a draft version and will undergo further review and revision.

This thesis investigates the thermo-hydro-mechanical behavior of concrete under severe accident conditions using a poro-mechanical approach.

The study combines numerical modeling and experimental validation to better understand the coupled physics involved.

Nomenclature

Finite Element notation

$[C]$	Capacity matrix
$[K]$	Global stiffness matrix
$\{F\}$	Nodal force vector
$\{R\}$	Residual vector
$\{U\}$	Nodal displacement vector

Hydraulic symbols

ϵ_{rd}	Desiccation shrinkage strain related to drying	[-]
ϵ_{re}	Endogenous shrinkage strain related to hydration	[-]

Mechanical symbols

σ	Cauchy stress tensor	[Pa]
ϵ	Total strain tensor	[-]
ϵ_e	Elastic strain tensor	[-]
ϵ_{th}	Thermal strain	[-]
$\mathbf{C}$	Fourth-order isotropic elasticity tensor defined by E and ν	[-]
D	Damage variable	[-]
E	Young's modulus	[Pa]
f_t	Tensile strength	[Pa]
G_f	Fracture energy	[J·m ⁻²]
L_e	Characteristic element length	[m]

Thermal symbols

λ	Thermal conductivity	$[\text{W}\cdot\text{m}^{-1}\cdot\text{K}^{-1}]$
ρ	Mass density	$[\text{kg}\cdot\text{m}^{-3}]$
σ	Stefan–Boltzmann constant	$[\text{W}\cdot\text{m}^{-2}\cdot\text{K}^{-4}]$
ε	Emissivity	$[-]$
c_p	Specific heat capacity	$[\text{J}\cdot\text{kg}^{-1}\cdot\text{K}^{-1}]$
h	Convective heat transfer coefficient	$[\text{W}\cdot\text{m}^{-2}\cdot\text{K}^{-1}]$
q''	Heat flux	$[\text{W}\cdot\text{m}^{-2}]$
T	Temperature	$[\text{K}]$

Contents

Acknowledgment	i
Abstract	ii
Nomenclature	iii
1 Introduction	1
1.1 Context and problem statement	1
1.1.1 Concrete behaviour under high temperature	1
1.1.2 Problem statement	2
1.1.3 Limitations of existing THM models	2
1.2 Objectives and scope of the thesis	2
1.3 Research enviroment and Computational tools	3
1.3.1 3SR Laboratory	3
1.3.2 Finite element code - Cast3M	3
1.3.3 Probabilistic analysis tool - Persalys	3
2 Theoretical and Numerical framework	5
2.1 Thermal behavior	5
2.1.1 Conduction, convection and radiation	5
2.1.2 Heat transfer	6
2.2 Hydric behavior	9

2.2.1	Types of water in concrete	9
2.2.2	Evaporation and dehydration	9
2.2.3	Moisture transport equation	10
2.2.4	Pore pressure build-up	14
2.3	Mechanical behavior	15
2.3.1	Linear elastic model	15
2.3.2	Mazars damage model	17
2.3.3	Mesh dependency and fracture energy regularization	19
2.4	Coupling mechanisms	21
2.4.1	Thermo-Hydric (TH) coupling mechanisms	21
2.4.2	Thermo-hydric input to the mechanical field	23
2.5	THM model and spalling	25
2.5.1	Full THM governing formulation	25
2.5.2	Spalling mechanisms	27
3	Numerical implementation	31
3.1	Discretization	31
3.1.1	Spatial discretization	31
3.1.2	Temporal discretization	32
3.1.3	Solution strategy	33
3.2	Model description and parameters	33
3.2.1	Geometry	33
3.2.2	Material properties	34
3.2.3	Boundary conditions and loadings	34
3.3	Implementation of the thermal model	34
3.3.1	Stationary linear thermal analysis	34
3.3.2	Transient linear and non-linear thermal analysis	34

3.4	Implementation of the hydric model	35
3.4.1	Drying	35
3.4.2	Shrinkage	35
3.5	Implementation of the mechanical model	35
3.5.1	Elastic linear mechanical model	35
3.5.2	Mazars model	35
3.6	Implementation of the TH coupled model	35
3.7	Implementation of the THM coupled model	35
3.8	Numerical results	35
4	Experimental data and Model validation	37
4.1	Experimental data	37
4.1.1	Experimental tests and material properties	37
4.1.2	Thermal, hydraulic and mechanic loadings	37
4.1.3	Measured data	37
4.2	Validation	38
4.2.1	Comparison between numerical and experimental results	38
4.2.2	Discussions on model performance	38
5	Probabilistic analysis of the THM model	39
5.1	Sources of uncertainty and concrete heterogeneity	39
5.1.1	Motivation for probabilistic assessment	39
5.1.2	Classification of uncertainties	40
5.1.3	Concrete heterogeneity and material variability	40
5.2	Stochastic finite element framework (Monte Carlo)	40
5.2.1	Random Field theory and Spatial variability	41
5.2.2	Transformation of Lognormal to Gaussian distributionn	42
5.2.3	Integration of spatial variability into the THM model	44

5.2.4	Monte Carlo simulation framework	44
5.3	Gaussian Quadrature framework	45
5.3.1	Principle of Gaussian Quadrature	45
5.3.2	Statistical moment estimation	45
5.3.3	PDF, CDF and reliability assessment	45
5.3.4	Computational efficiency	46
5.4	Sensitivity analysis	46
5.4.1	Characterization of input parameters	46
5.4.2	Sensitivity indicators and ranking methods	47
5.4.3	Identification of dominant parameters	47
5.5	Reliability analysis	48
5.5.1	Probability of failure and reliability index	48
5.5.2	Probability of failure from moment-based PDF	48
5.5.3	Probability of failure from Monte Carlo sampling	48
5.5.4	Effect of spatial heterogeneity on structural safety	48
6	Conclusions and Perspectives	49
6.1	Main findings	49
6.2	Model limitations and possible improvements	49
6.3	Perspectives for future research	49
	List of Figures	51
	List of Tables	52
	Bibliography	53

Chapter 1

Introduction

[REVIEW] This chapter is currently a draft version and will undergo further review and revision.

1.1 Context and problem statement

Concrete structures exposed to fire undergo a complex interplay of thermal, hydric, and mechanical phenomena that can lead to progressive degradation and, in the most severe cases, to *spalling* — the sudden detachment of concrete layers from the exposed surface. Several catastrophic tunnel fires have illustrated the severity of this phenomenon: the Channel Tunnel fire (1996), the Mont-Blanc tunnel fire (1999), and the St. Gotthard tunnel fire (2001) all caused extensive spalling-induced structural damage [3].

In nuclear containment structures, where concrete is exposed to extreme temperatures during severe accidents, the consequences of spalling are particularly critical as they may compromise structural integrity and containment function.

1.1.1 Concrete behaviour under high temperature

When concrete is subjected to rapid heating, several coupled physical processes develop simultaneously:

- **Thermal:** steep temperature gradients develop through the cross-section, driving differential thermal dilation and generating compressive stresses at the heated surface.
- **Hydric:** free and chemically bound water evaporate and migrate through the pore network; in low-permeability concretes such as high-performance concrete (HPC),

vapor cannot escape rapidly enough, leading to pore pressure build-up behind a quasi-saturated *moisture clog*.

- **Mechanical:** the combined action of thermal stresses and pore pressure loading on the solid skeleton can exceed the (temperature-degraded) tensile strength, initiating cracks parallel to the heated surface and potentially triggering explosive spalling.

Despite extensive experimental research, the mechanisms governing spalling remain incompletely understood and no general consensus has been reached [3].

1.1.2 Problem statement

Reliable prediction of spalling requires a consistent *thermo-hydro-mechanical* (THM) framework capable of capturing:

- the multi-physics coupling between thermal, hydric, and mechanical fields under high temperature;
- the temperature- and damage-dependent evolution of transport properties, whereby microcracking alters permeability and redistributes pore pressure;
- the inherent spatial variability of material parameters (permeability, porosity, tensile strength) and its influence on the onset and location of spalling.

1.1.3 Limitations of existing THM models

Current THM models present several limitations that this work aims to address:

- incomplete coupling between the damage state and transport properties, often neglecting the feedback of cracking on permeability;
- lack of consistent regularization for strain localization, leading to mesh-dependent solutions;
- limited probabilistic assessment of parameter uncertainty: existing models typically treat material properties as homogeneous deterministic values, neglecting the spatial variability of concrete properties.

1.2 Objectives and scope of the thesis

Main objectives of the thesis:

- Understanding and Developing a THM model
- Temperature- and damage-dependent evolution of stiffness and transport properties.
- Numerical implementation and numerical validation.
- Probabilistic sensitivity analysis: Evaluating parameter uncertainty and identifying the dominant physical parameters.

The scope of this work is limited to:

- Thermal boundaries limited by severe accident conditions.
- Continuum-scale THM modelling by Cast3M.
- Damage modelling including temperature-dependent stiffness and transport properties.
- Probabilistic sensitivity analysis at the material parameter level.

1.3 Research environment and Computational tools

1.3.1 3SR Laboratory

The host institution providing the scientific environment, experimental data, and expertise in structural mechanics and risk analysis.

1.3.2 Finite element code - Cast3M

Cast3M (or Castem) is an open-source finite-element code developed at CEA, which is used to implement advanced constitutive laws and custom multiphysics formulations.

Compared with COMSOL Multiphysics, Cast3m typically offers greater transparency and control for implementing tightly coupled THM while COMSOL offers a user-friendly GUI for many built-in multiphysics interfaces.

1.3.3 Probabilistic analysis tool - Persalys

Persalys is the computational tool dedicated to managing parameter uncertainty in material properties.

It is used to perform the probabilistic sensitivity analysis, generate random sampling (e.g., Monte Carlo simulations), and rank the dominant THM parameters.

Chapter 2

Theoretical and Numerical framework

[REVIEW] This chapter is currently a draft version and will undergo further review and revision.

2.1 Thermal behavior

2.1.1 Conduction, convection and radiation

Heat transfer is the transport of thermal energy driven by a temperature difference. The following definitions of heat transfer modes are summarized from standard references [2].

Conduction

Conduction is the transfer of energy from the more energetic to the less energetic particles of a substance

- **Physical Mechanism:**
- **Rate Equation (Fourier's Law):** For a one-dimensional plane wall having a temperature distribution $T(x)$, the rate equation is expressed as Fourier's law:

$$q''_{cond} = -\lambda \frac{dT}{dx} \quad (2.1)$$

Where q''_{cond} is the heat flux (W/m^2), λ is the thermal conductivity ($W/m \cdot K$), and the minus sign indicates that heat is transferred in the direction of decreasing temperature.

Convection

The convection heat transfer mode is

- **Physical Mechanism:** Convection heat transfer occurs between a fluid in motion and a bounding surface when the two are at different temperatures
- **Rate Equation (Newton's Law of Cooling):** Regardless of the nature of the convection process, the appropriate rate equation is:

$$q''_{conv} = h(T_s - T_\infty) \quad (2.2)$$

Where q'' is the convective heat flux (W/m^2), h is the convection heat transfer coefficient ($W/m^2 \cdot K$), T_s is the surface temperature, and T_∞ is the fluid temperature.

Radiation

Thermal radiation is energy emitted by matter that is at a nonzero temperature, and unlike conduction and convection, it does not require the presence of a material medium.

- **Physical Mechanism:** The energy of the radiation field is transported by electromagnetic waves (or photons)
- **Emissive Power (Stefan-Boltzmann law):** The upper limit to the emissive power (rate of energy released per unit area) for an ideal radiator or blackbody is given:

$$E_b = \sigma T_s^4 \quad (2.3)$$

The heat flux emitted by a real surface is given by $E = \varepsilon \sigma T_s^4$, where σ is the Stefan-Boltzmann constant and ε is the emissivity.

- **Net Radiation Exchange:** For a gray surface at T_s completely surrounded by a much larger isothermal surface at T_{sur} , the net rate of radiation heat transfer per unit area is:

$$q''_{rad} = \varepsilon \sigma (T_s^4 - T_{sur}^4) \quad (2.4)$$

2.1.2 Heat transfer

Heat Equation

Based on the principle of energy conservation and Fourier's law, the general heat diffusion equation (or heat equation) for a medium is detailed in [4] and can be expressed as:

$$\rho c_p \frac{\partial T}{\partial t} + \text{div}(-\lambda \overrightarrow{\text{grad}}(T)) - q = 0 \quad (2.5)$$

Where:

- ρ is the volumetric mass density (kg/m^3).
- c_p is the specific heat capacity ($J/kg \cdot K$).
- λ is the thermal conductivity ($W/m \cdot K$).
- T is the temperature field and t is time.
- q is the volume heat flux source (W/m^3).

To solve this equation, appropriate boundary conditions must be specified:

- **Prescribed temperatures :** The temperature is specified as $T = T_{imp}$ on the boundary surface ∂V^T .
- **Prescribed surface heat flux :** The total heat flux due to conduction, convection, and radiation on the boundary surface ∂V^φ is given by:

$$\vec{n} \cdot (\lambda \overrightarrow{\text{grad}}(T)) = \varphi_{imp} + h(T_f - T) + \varepsilon \sigma (T_\infty^4 - T^4) \quad (2.6)$$

where φ_{imp} is the prescribed heat flux, $h(T_f - T)$ represents the convection term, and $\varepsilon \sigma (T_\infty^4 - T^4)$ is the radiation term.

Thermal properties

The thermal properties of concrete are strongly influenced by both the hydric state and the material composition.

The overall heat capacity ρC_p reflects the multiphase nature of the porous medium, combining contributions from the solid skeleton, liquid water, dry air, and water vapor:

$$\rho C_p = (1 - \phi) \rho_s C_{ps} + \phi [S_l \rho_l C_{pl} + (1 - S_l) (\rho_a C_{pa} + \rho_v C_{pv})] \quad (2.7)$$

The thermal conductivity depends on saturation, porosity, and temperature:

$$\lambda = \lambda_d \left(1 + 4 \frac{S_l \phi \rho_l}{(1 - \phi) \rho_s} \right) \quad (2.8)$$

with:

$$\lambda_d = \lambda_{d0} [1 + A_\lambda (T - T_0)] \quad (2.9)$$

As drying progresses ($S_t \rightarrow 0$), both ρC_p and λ decrease, which accelerates the penetration of the thermal front into the material. These dependencies highlight the influence of the hydric state on the thermal field, which is further discussed in Section 2.4.1.

Discretization

Using the FE discretization, the temperature and temperature gradient in the spatial domain are expressed in matrix form as:

$$T(x) = [N(x)]\{T\}, \quad \overrightarrow{\text{grad}}(T) = [B(x)]\{T\} \quad (2.10)$$

From the weak formulation of the heat equation combined with the spatial discretization, we obtain the general matrix equation:

$$[C]\{\dot{T}\} + [K]\{T\} = \{F\} \quad (2.11)$$

Where the matrices are defined as follows:

- **Capacity matrix:**

$$[C] = \int_V \rho c_p [N]^T [N] dV \quad (J/K) \quad (2.12)$$

- **Conductivity matrix:**

$$[K] = \int_V [B]^T [\lambda] [B] dV + \int_{\partial V^\varphi} h [N]^T [N] dS \quad (W/K) \quad (2.13)$$

- **Equivalent nodal flux vectors:**

$$\{F\} = \int_V [N]^T q dV + \int_{\partial V^\varphi} [N]^T (\varphi_{imp} + hT_f + \varepsilon\sigma(T_\infty^4 - T^4)) dS \quad (W) \quad (2.14)$$

For steady-state thermal analysis, the temperature is time-independent ($\{\dot{T}\} = 0$) (assuming constant material properties and neglecting radiation):

$$[K]\{T\} = \{F\} \quad (2.15)$$

By solving this linear system, we can determine the unknown temperatures $\{T\}$ at the nodes across the entire global mesh.

2.2 Hydric behavior

[REVIEW]

When concrete is exposed to high temperatures, the behavior of water within the porous network plays a central role in the thermo-hydro-mechanical response of the material. This section presents the classification of water in concrete, the phase-change mechanisms, the governing equation for moisture transport, and the constitutive laws required to close the system.

2.2.1 Types of water in concrete

Concrete is a multiphase porous material whose voids can be filled with water, air and other fluids. The water present in the cement paste can be broadly classified into two categories [3]

- **Pore water (free/evaporable water):** This water evaporates when the thermodynamic conditions are met (*i.e.*, at $T = 100^\circ\text{C}$ and atmospheric pressure) and exists in three main forms:
 - *Capillary and inter-hydrate water:* fills the capillary pores (size $\sim 100\text{s}$ of nm) and inter-hydrate pores (size $\sim 10\text{s}$ of nm), corresponding to a saturation $S_{ssp} < S_l < 1$.
 - *Physically adsorbed water (gel water):* retained by the surface of the solid matrix due to Van der Waals forces, confined in gel pores (size $\sim$ a few nm).
 - *Interlayer water:* confined in ~ 1 nm space between the C-S-H layers.
- **Chemically bound water (non-evaporable):** This water is combined with anhydrous cement during hydration and forms part of the crystalline structure of hydration products (e.g., C-S-H, portlandite). It can only be released through thermal decomposition (dehydration) at elevated temperatures.

It is important to note that the range of pore sizes is a continuous one; the dimensional boundaries between capillary, inter-hydrate and gel pores are approximations to inherently blurred boundaries.

2.2.2 Evaporation and dehydration

Two distinct phase-change mechanisms govern the release of water in heated concrete:

- **Evaporation** is the transition of free liquid water into vapor. It occurs progressively as temperature increases, becoming significant above approximately 100 °C at atmospheric pressure. The evaporation rate $\dot{m}_{vap}$ is determined from the mass conservation of liquid water (see Section 2.2.3).
- **Dehydration** is the thermally-driven decomposition of hydration products, releasing chemically bound water as vapor. The main reactions occur at characteristic temperature ranges [3]:
 - Up to 300 °C: progressive decomposition of C-S-H phases and ettringite;
 - 400–500 °C: dehydroxylation of portlandite ($\text{Ca(OH)}_2 \rightarrow \text{CaO} + \text{H}_2\text{O}$);
 - ~ 570 °C: α - β quartz transformation;
 - Above 600 °C: decarbonation of calcareous aggregates ($\text{CaCO}_3 \rightarrow \text{CaO} + \text{CO}_2$).

Both evaporation and dehydration act as vapor sources that increase gas pressure within the pore network. They also consume latent energy, affecting the temperature field (see Section 2.4).

The cumulative dehydrated water mass is described by the following phenomenological relationship

$$\Delta m_{dehyd} = f_s \cdot f_m \cdot f_c \cdot f(T) \quad (2.16)$$

where f_s is a stoichiometric factor, f_m accounts for the concrete's age, f_c is the cement mass per unit volume, and $f(T)$ is a temperature-dependent function:

$$f(T) = \begin{cases} 0 & \text{if } T < 105 \text{ °C} \\ \left[1 + \sin\left(\frac{\pi}{2} (1 - 2 \exp(-0.004 (T - 105)))\right) \right] & \text{if } T \geq 105 \text{ °C} \end{cases} \quad (2.17)$$

2.2.3 Moisture transport equation

Transport mechanisms

The transport of moisture in heated concrete is governed by two mechanisms:

- **Advective flow (Darcy's law):** The bulk flow of liquid water and gas through the porous network is driven by pressure gradients:

$$\mathbf{v}_{l-s} = -\frac{K k_{rl}}{\mu_l} (\nabla p_g - \nabla p_c) \quad (2.18)$$

$$\mathbf{v}_{g-s} = -\frac{K k_{rg}}{\mu_g} \nabla p_g \quad (2.19)$$

where K is the intrinsic permeability, k_{rl} and k_{rg} are the relative permeabilities of liquid and gas, μ_l and μ_g are the dynamic viscosities, and $p_l = p_g - p_c$ is the liquid pressure.

- **Diffusive flow (Fick's law):** Water vapor diffuses within the gas mixture according to:

$$\mathbf{j}_v = -\rho_g D \nabla \left(\frac{\rho_v}{\rho_g} \right) \quad (2.20)$$

where D is the effective diffusivity accounting for the tortuous porous network.

Mass conservation equations

The mathematical framework for moisture transport in heated concrete is based on the conservation of mass for each phase. The general form of a mass conservation equation for a phase π is [3]:

$$\frac{\partial}{\partial t} (\text{density}) + \nabla \cdot (\text{flux}) = \text{source} \quad (2.21)$$

Concrete at high temperature is treated as a multiphase porous medium consisting of a solid skeleton (s), liquid water (l), water vapor (v), and dry air (a). Applying Equation (2.21) to each phase yields [3]:

- **Solid skeleton:**

$$\frac{\partial m_s}{\partial t} = \dot{m}_{dehyd} \quad (2.22)$$

- **Liquid water:**

$$\frac{\partial m_l}{\partial t} + \nabla \cdot (m_l \mathbf{v}_{l-s}) = -\dot{m}_{vap} - \dot{m}_{dehyd} \quad (2.23)$$

- **Water vapor:**

$$\frac{\partial m_v}{\partial t} + \nabla \cdot (m_v \mathbf{v}_{g-s}) + \nabla \cdot (m_v \mathbf{v}_{v-g}) = \dot{m}_{vap} \quad (2.24)$$

- **Dry air:**

$$\frac{\partial m_a}{\partial t} + \nabla \cdot (m_a \mathbf{v}_{g-s}) + \nabla \cdot (m_a \mathbf{v}_{a-g}) = 0 \quad (2.25)$$

where $\mathbf{v}_{\pi-s}$ is the velocity of phase π ($\pi = l, g$) relative to the solid skeleton, and $\mathbf{v}_{\pi-g}$ is the velocity of species π ($\pi = v, a$) relative to the gas mixture. The source term $\dot{m}_{vap}$ represents the evaporation rate ($\dot{m}_{vap} > 0$ for evaporation, < 0 for condensation), and $\dot{m}_{dehyd}$ is the dehydration rate ($\dot{m}_{dehyd} < 0$, treated as a mass loss of the solid skeleton and a mass source for liquid water).

The mass of each phase per unit volume of porous medium is [3]:

$$m_s = (1 - \phi) \rho_s \quad (2.26)$$

$$m_l = \rho_l S_l \phi \quad (2.27)$$

$$m_v = \rho_v (1 - S_l) \phi \quad (2.28)$$

$$m_a = \rho_a (1 - S_l) \phi \quad (2.29)$$

where ϕ is the porosity and S_l is the liquid saturation degree.

By combining the mass conservation of liquid water and water vapor, the evaporation source term $\dot{m}_{vap}$ is eliminated, yielding the **water species conservation equation**:

$$\begin{aligned} & S_l \rho_l \frac{\partial \phi}{\partial t} + S_l \phi \frac{\partial \rho_l}{\partial t} + \rho_l \phi \frac{\partial S_l}{\partial t} + (1 - S_l) \phi \frac{\partial \rho_v}{\partial t} - \rho_v \phi \frac{\partial S_l}{\partial t} + (1 - S_l) \rho_v \frac{\partial \phi}{\partial t} \\ & + \nabla \cdot \left(-K \frac{\rho_l k_{rl}}{\mu_l} \nabla p_l \right) + \nabla \cdot \left(-K \frac{\rho_v k_{rg}}{\mu_g} \nabla p_g - D \rho_g \frac{M_v M_a}{M_g^2} \nabla \frac{p_v}{p_g} \right) = -\dot{m}_{dehyd} \end{aligned} \quad (2.30)$$

This equation has three primary unknowns: the temperature T , the capillary pressure p_c , and the gas pressure p_g . Similarly, the **dry air conservation equation** reads:

$$(1 - S_l) \phi \frac{\partial \rho_a}{\partial t} - \rho_a \phi \frac{\partial S_l}{\partial t} + (1 - S_l) \rho_a \frac{\partial \phi}{\partial t} + \nabla \cdot \left(-K \frac{\rho_a k_{rg}}{\mu_g} \nabla p_g - D \rho_g \frac{M_v M_a}{M_g^2} \nabla \frac{p_a}{p_g} \right) = 0 \quad (2.31)$$

Constitutive relations for the gas phase

The gaseous phase (dry air + water vapor) is governed by the following relations [3]:

- **Ideal gas law:**

$$\rho_\pi = \frac{p_\pi M_\pi}{RT}, \quad \pi = a, v \quad (2.32)$$

where M_π is the molar mass and R is the universal gas constant.

- **Dalton's law:**

$$p_g = p_a + p_v \quad (2.33)$$

- **Kelvin equation** (thermodynamic equilibrium between liquid and vapor):

$$p_v = p_{vs}(T) \exp \left(\frac{M_v}{\rho_l RT} (p_g - p_c - p_{vs}) \right) \quad (2.34)$$

where $p_{vs}(T)$ is the saturation vapor pressure, approximated by the Hyland-Wexler relationship:

$$p_{vs}(T) = \exp \left[\frac{C_1}{T} + C_2 + C_3 T + C_4 T^2 + C_5 T^3 + C_6 \ln(T) \right] \quad (2.35)$$

Sorption isotherms

The relationship between capillary pressure and liquid saturation is described by the Van Genuchten model:

$$p_c = a (S_l^{-b} - 1)^{1-1/b} \quad (2.36)$$

where a and b are material parameters determined experimentally. Representative values at ambient temperature are given in Table 2.1.

Table 2.1: Van Genuchten parameters at ambient temperature

	NSC	HPC	NSM	HPM
a [MPa]	18.62	46.94	37.55	96.28
b [-]	2.275	2.060	2.168	1.954

At elevated temperatures, the parameter a is modified to account for changes in surface tension and pore structure:

$$S_l = \left(\left(\frac{E(T)}{a(T)} p_c \right)^{b/(b-1)} + 1 \right)^{-1/b} \quad (2.37)$$

where $E(T)$ accounts for the surface tension evolution and $a(T)$ accounts for microstructure changes above 100 °C.

Intrinsic permeability

Permeability is a key parameter governing moisture transport. For a thermo-hydral problem, the following relationship is adopted:

$$K = K_0 \cdot 10^{A_T(T-T_0)} \left(\frac{p_g}{p_{atm}} \right)^{A_p} \quad (2.38)$$

where K_0 is the intrinsic permeability at reference conditions, $A_T = 0.005$ and $A_p = 0.368$.

When mechanical damage is considered, the permeability increases significantly:

$$K = K_0 \cdot 10^{A_T(T-T_0)} \left(\frac{p_g}{p_{atm}} \right)^{A_p} \cdot 10^{A_D \mathcal{D}} \quad (2.39)$$

where $\mathcal{D}$ is the damage parameter and A_D is a material constant. This damage-permeability coupling is a key mechanism in the THM model (see Section 2.4).

Relative permeability

The relative permeabilities of liquid and gas are described by the Van Genuchten relationships:

$$k_{rl} = \sqrt{S_l} \left(1 - \left(1 - S_l^{1/A_S} \right)^{A_S} \right)^2 \quad (2.40)$$

$$k_{rg} = \sqrt{1 - S_l} \left(1 - S_l^{1/A_S} \right)^{2A_S} \quad (2.41)$$

where $A_S = 0.6$.

Effective diffusivity

The diffusivity of vapor in air at a given temperature and pressure is:

$$D_{va}(T, p_g) = D_{v0} \left(\frac{T}{T_0} \right)^{B_v} \frac{p_{g0}}{p_g} \quad (2.42)$$

where $D_{v0} = 2.58 \times 10^{-5}$ m²/s and $B_v = 1.667$. The effective diffusivity in the porous medium accounts for saturation and tortuosity:

$$D = (1 - S_l)^{A_v} \phi \tau D_{va}(T, p_g) \quad (2.43)$$

with the tortuosity:

$$\tau(\phi, S_l) = \phi^{1/3} (1 - S_l)^{7/3} \quad (2.44)$$

Porosity evolution

The porosity increases with temperature due to microstructural changes:

$$\phi = \phi_0 + A_\phi (T - T_0) \quad (2.45)$$

where ϕ_0 is the initial porosity and A_ϕ is a material constant.

2.2.4 Pore pressure build-up

When concrete is heated, the evaporation of free water and the release of chemically bound water (dehydration) produce vapor, raising the pressure in the pores. Due to pressure gradients, part of this vapor is evacuated toward the heated face, while another part is driven toward the interior, cooler regions of the specimen. Once the vapor reaches zones where the temperature is sufficiently low, it condenses back into liquid water. This process

continues until a quasi-saturated zone is formed, known as the *moisture clog*. This saturated layer acts as an impermeable barrier that blocks further vapor migration toward the colder region, giving rise to significant pore pressure build-up behind the drying front. In dense materials such as high-performance concrete (HPC), the low intrinsic permeability (K_0) further aggravates this phenomenon by limiting the overall gas transport capacity.

The magnitude of pore pressure depends on:

- the rate of vapor production (controlled by the heating rate and initial moisture content);
- the intrinsic permeability K_0 and its evolution with temperature and damage;
- the porosity ϕ , which governs the available volume for gas storage.

When the pore pressure exceeds the tensile strength of the material, it can trigger cracking and potentially explosive spalling. This mechanism is discussed in more detail in Section 2.5.2.

2.3 Mechanical behavior

[REVIEW]

The mechanical response of concrete under high-temperature conditions is characterized by an initial linear elastic phase, followed by severe stiffness degradation due to the formation of micro-cracks. In this numerical framework, the behavior is modeled by coupling a linear elastic constitutive law with a continuum damage mechanics approach.

[REVIEW]

The mechanical equilibrium presented above assumes a staggered (sequential) solution strategy: the TH subsystem is solved first to obtain p_g , p_c , T , which are then passed as known loading to the mechanical step.

The specific coupling method between the TH and mechanical solvers has not yet been finalized and will be detailed and modified in Chapter 2 and Chapter 3 as the study progresses.

2.3.1 Linear elastic model

In the present work, concrete is modeled as a linear elastic material. The effective stress tensor $\tilde{\sigma}$, defined as the stress acting on the undamaged material, is related to the elastic

strain tensor $\boldsymbol{\varepsilon}_e$ through the isotropic Hooke's law:

$$\boldsymbol{\sigma} = \mathbb{C} : \boldsymbol{\varepsilon}_e \quad (2.46)$$

where $\mathbb{C}$ is the constant fourth-order elastic stiffness tensor, defined by the Young's modulus E and Poisson's ratio ν .

The total strain is decomposed into mechanical and free (stress-free) components, as detailed in Section 2.4.2. Since creep is neglected in this work, the elastic strain reduces to:

$$\boldsymbol{\varepsilon}_e = \boldsymbol{\varepsilon} - \boldsymbol{\varepsilon}_{th} - \boldsymbol{\varepsilon}_{sh} \quad (2.47)$$

which enters directly into Hooke's law (Equation (2.46)).

Linear finite element formulation

[REVIEW]

[REVIEW] Further references are needed to strengthen the scientific basis of this section. Such as "Numerical Methods for Nonlinear Mechanics lectures" by Stefano DAL PONT

The spatial discretization of the momentum conservation equation (Equation (2.82)) is carried out using the standard Galerkin finite element method.

The continuous displacement field $\mathbf{u}$ is approximated by nodal displacements $\mathbf{U}$ using shape functions $\mathbf{N}$, and the strain is obtained via the compatibility matrix $\mathbf{B}$ such that $\boldsymbol{\varepsilon} = \mathbf{B}\mathbf{U}$.

Applying the principle of virtual work, the global system takes the form:

$$\mathbf{K}_M \mathbf{U} = \mathbf{F} \quad (2.48)$$

where $\mathbf{K}_M = \int_V \mathbf{B}^T \mathbb{C} \mathbf{B} dV$ is the elastic stiffness matrix. The load vector $\mathbf{F}$ receives contributions from two distinct thermo-hydric mechanisms (Section 2.4.1):

$$\mathbf{F} = \mathbf{f}_{ext} + \underbrace{\int_V \mathbf{B}^T \mathbb{C} \boldsymbol{\varepsilon}^{th} dV + \int_V \mathbf{B}^T \mathbb{C} \boldsymbol{\varepsilon}^{sh} dV}_{\text{strain decomposition (Equation (2.71))}} + \underbrace{\int_V \mathbf{B}^T \alpha p_s \mathbf{I} dV}_{\text{effective stress (Equation (2.77))}} \quad (2.49)$$

Since $\boldsymbol{\varepsilon}^{th}$, $\boldsymbol{\varepsilon}^{sh}$, p_c , and p_g are known from the TH solution at each time step, all three terms enter the right-hand side as prescribed loading. In Cast3M, this system is assembled and solved using the RIGI and RESO operators.

2.3.2 Mazars damage model

Concrete cracks when tensile strains become too large. In this work, this behaviour is represented with the Mazars damage model [5].

Damage parameter and equivalent strain

The model introduces a single scalar internal variable $\mathcal{D}$, damage parameter, ranging from 0 (intact material) to 1 (fully broken material). The apparent macroscopic stress is reduced according to the effective stress concept:

$$\boldsymbol{\sigma}' = (1 - \mathcal{D}) \boldsymbol{\sigma} \quad (2.50)$$

The term $\boldsymbol{\sigma}'$ in Equation (2.50) then enters Bishop's relation (Equation (2.77)) to form the total stress $\boldsymbol{\sigma}^{Total}$.

[REVIEW]

Because concrete cracking is primarily governed by tensile extensions, Mazars introduced an *equivalent strain* (ε_{eq}) to translate any 3D multiaxial strain state into a scalar uniaxial indicator. In the case of a thermo-mechanical loading, it is important to note that only the elastic strain tensor $\boldsymbol{\varepsilon}_e$ contributes to the evolution of damage. The equivalent strain is calculated solely from the positive principal elastic strains ε_i :

$$\varepsilon_{eq} = \sqrt{\langle \boldsymbol{\varepsilon}_e \rangle_+ : \langle \boldsymbol{\varepsilon}_e \rangle_+} = \sqrt{\sum_{i=1}^3 \langle \varepsilon_i \rangle_+^2} \quad (2.51)$$

where the Macaulay brackets $\langle x \rangle_+$ denote the positive part of x (i.e., $\langle x \rangle_+ = x$ if $x \geq 0$, and 0 if $x < 0$).

Damage initiates when the equivalent strain exceeds the initial damage threshold, denoted as ε_{d0} .

$$\varepsilon_{d0} = \frac{f_t}{E}. \quad (2.52)$$

At the damage onset ($\varepsilon_{eq} = \varepsilon_{d0}$), the damage variable is zero:

$$\mathcal{D} = 0 \quad \text{for} \quad \varepsilon_{eq} \leq \varepsilon_{d0}. \quad (2.53)$$

For uniaxial tension, damage onset corresponds to:

$$\sigma_t = f_t. \quad (2.54)$$

In this simplified interpretation, f_t denotes the uniaxial tensile strength of the concrete

and E is Young's modulus.

Damage evolution laws for tension and compression

To accurately represent concrete behavior, the total damage D is formulated as a combination of two independent damage variables: D_t for tension and D_c for compression.

When the damage threshold is exceeded ($\varepsilon_{eq} > \varepsilon_{d0}$), the evolution of these two modes is explicitly governed by exponential laws:

$$\mathcal{D}_t = 1 - \frac{(1 - A_t)\varepsilon_{d0}}{\varepsilon_{eq}} - A_t \exp[-B_t(\varepsilon_{eq} - \varepsilon_{d0})] \quad (2.55)$$

$$\mathcal{D}_c = 1 - \frac{(1 - A_c)\varepsilon_{d0}}{\varepsilon_{eq}} - A_c \exp[-B_c(\varepsilon_{eq} - \varepsilon_{d0})] \quad (2.56)$$

where A_t , B_t , A_c , and B_c are material parameters identified from uniaxial tensile and compressive tests. These parameters modulate the shape of the post-peak softening curves: parameters A define the residual asymptotic stress level, while parameters B control the slope of the stress drop.

The global macroscopic damage $\mathcal{D}$ is then calculated using a linear combination with weighting coefficients α_t and α_c :

$$\mathcal{D} = \alpha_t^\beta \mathcal{D}_t + \alpha_c^\beta \mathcal{D}_c \quad (2.57)$$

The coefficients α_t and α_c depend on the principal stress state, evaluating the respective contributions of tensile and compressive stresses. In pure tension, $\alpha_t = 1$ and $\alpha_c = 0$; conversely, in pure compression, $\alpha_c = 1$ and $\alpha_t = 0$. The parameter β (typically fixed at 1.06) is a shear-correction coefficient introduced to improve the structural response under shear loadings.

Non-linear equilibrium and Imbalance vector (R)

[REVIEW]

[REVIEW] Further references are needed to strengthen the scientific basis of this section. Such as "Numerical Methods for Nonlinear Mechanics lectures" by Stefano DAL PONT

In the general case with damage, the stiffness matrix reads:

$$[\mathbf{K}_M] = \int_V \mathbf{B}^T (1 - \mathcal{D}) \mathbf{C} \mathbf{B} dV \quad (2.58)$$

When $\mathcal{D} = 0$ (intact material), this reduces to the standard linear elastic stiffness matrix $\int_V \mathbf{B}^T \mathbb{C} \mathbf{B} dV$.

Due to damage evolution, the constitutive relation becomes non-linear and Equation (2.48) cannot be solved in a single step. The equilibrium is enforced iteratively using a Newton-Raphson-type algorithm. At each iteration i , the imbalance vector is evaluated:

$$\{\mathbf{R}\}^i = \{\mathbf{F}\} - \int_V \mathbf{B}^T \boldsymbol{\sigma}^i dV \quad (2.59)$$

where $\{\mathbf{F}\}$ includes all thermo-hydric contributions as defined in ???. The correction is obtained from:

$$[\mathbf{K}_M]\{\delta \mathbf{U}\}^{i+1} = \{\mathbf{R}\}^i \quad (2.60)$$

The displacements and damage variable $\mathcal{D}$ are updated until convergence ($\|\mathbf{R}\| < \epsilon F_{ref}$). In Cast3M, this iterative procedure is handled by the PASAPAS operator.

2.3.3 Mesh dependency and fracture energy regularization

A major drawback of local softening models is the pathological mesh dependency. Mathematically, softening causes a loss of ellipticity in the differential equations, leading to strain localization in a band whose width depends entirely on the finite element size.

[REVIEW]

[REVIEW] This section requires additional references to support the statements presented.

To overcome this issue without resorting to complex non-local formulations, a regularization technique based on Hillerborg's specific fracture energy (G_f) is utilized. Physically, the fracture energy G_f represents the energy required to propagate a discrete crack per unit *area* (expressed in J/m²). However, in the continuum damage mechanics framework of the Finite Element Method, cracking is modeled as a smeared softening phenomenon occurring over the *volume* of the 3D finite element.

To reconcile the areal energy dissipation of a real crack with the volumetric dissipation of the continuum element, a characteristic length of the finite element, L_e , is introduced. In the Cast3M implementation (using the @LONGEF procedure), this equivalent length is evaluated based on the element's geometry, calculated as $L_e = V^{1/D}$ where D is the spatial dimension.

The total fracture energy G_f dissipated by a finite element of size L_e is the product of L_e and the total area under the uniaxial stress-strain ($\sigma - \varepsilon$) softening curve (which represents the volumetric dissipated energy density $g_f = G_f/L_e$). This total energy is strictly partitioned into two components: the reversible elastic strain energy stored up to the peak stress, and the energy dissipated strictly during the non-linear damage

softening phase:

$$G_f = G_{elastic} + G_{softening} \quad (2.61)$$

Evaluation of the elastic energy ($G_{elastic}$)

[REVIEW]

[REVIEW] This section requires additional references to support the statements presented.

The elastic energy density up to the onset of damage (when the stress reaches the tensile strength f_t at the initial strain threshold $\varepsilon_{d0} = f_t/E_0$) corresponds to the area of the elastic triangle under the curve:

$$g_{elastic} = \frac{1}{2} f_t \varepsilon_{d0} = \frac{f_t^2}{2E_0} \quad (2.62)$$

Multiplying by the characteristic length yields the areal elastic energy: $G_{elastic} = \frac{f_t^2}{2E_0} L_e$. Consequently, the remaining energy strictly available for the damage softening phase is calculated as:

$$G_{softening} = G_f - \frac{f_t^2}{2E_0} L_e \quad (2.63)$$

Analytical evaluation of $G_{softening}$ and the softening parameter B_t

[REVIEW]

[REVIEW] This section requires additional references to support the statements presented.

In the original Mazars formulation, the evolution of damage in pure tension is governed by an exponential law. Assuming a purely brittle failure in tension ($A_t \approx 1$), the post-peak stress-strain relationship can be simplified to:

$$\sigma(\varepsilon) \approx f_t \exp[-B_t(\varepsilon - \varepsilon_{d0})] \quad (2.64)$$

The volumetric softening energy density ($g_{softening}$) is the integral of this stress-strain curve from the peak strain ε_{d0} to infinity:

$$g_{softening} = \int_{\varepsilon_{d0}}^{\infty} f_t \exp[-B_t(\varepsilon - \varepsilon_{d0})] d\varepsilon = \frac{f_t}{B_t} \quad (2.65)$$

By converting this volumetric density into areal energy via the characteristic length L_e , we establish the fundamental relationship between the fracture energy and the Mazars

tensile parameter:

$$G_{softening} = g_{softening} \cdot L_e = \frac{f_t \cdot L_e}{B_t} \quad (2.66)$$

Dynamic regularization of B_t (B_t^{mod})

To ensure that each finite element dissipates exactly the objective intrinsic energy G_f regardless of its size L_e , the parameter B_t must be dynamically recalculated. By equating the integral of the Mazars softening curve to the available softening energy, we deduce the modified parameter B_t^{mod} :

$$B_t^{mod} = \frac{f_t \cdot L_e}{G_{softening}} = \frac{f_t \cdot L_e}{G_f - \frac{f_t^2}{2E_0} L_e} \quad (2.67)$$

This energetic adjustment guarantees that the macroscopic crack propagation and global energy dissipation remain completely objective and independent of the selected spatial discretization.

2.4 Coupling mechanisms

The thermal, hydric, and mechanical behaviors presented in the previous sections are not independent: they interact through a network of coupling mechanisms. This section identifies and formulates the two main coupling paths that govern the response of concrete exposed to fire.

2.4.1 Thermo-Hydric (TH) coupling mechanisms

The thermal and hydric fields are coupled in both directions: temperature drives phase changes and modifies transport properties, while fluid flow and phase changes affect the energy balance.

Temperature as a driver of hydric phenomena

Temperature influences the hydric field through three main mechanisms:

- **Phase changes:** As temperature rises, evaporation and dehydration release vapor into the pore network (see Section 2.2.2), acting as mass source terms in the water species conservation Equation (2.30).

- **Temperature-dependent transport properties:** Most constitutive parameters governing moisture transport depend explicitly on temperature [3]: intrinsic permeability K increases (Equation (2.38)), porosity ϕ increases (Equation (2.45)), fluid viscosities μ_l, μ_v, μ_a decrease (enhancing advective flow), saturating vapor pressure p_{vs} increases sharply, liquid water density ρ_l decreases, and the effective diffusivity D increases.
- **Sorption isotherms:** The relationship between capillary pressure and liquid saturation is modified at high temperatures through the temperature-dependent parameter $a(T)$ in the Van Genuchten model (Equation (2.37)).

Energy conservation equation

The energy conservation equation governs the temperature field within the porous medium. Similar to the heat equation in Section 2.1.2, it includes a storage term, a conductive flux, and additionally accounts for advective heat transport and phase-change energy terms [3]:

$$\rho C_p \frac{\partial T}{\partial t} + \underbrace{(m_l C_l \mathbf{v}_{l-s} + m_g C_g \mathbf{v}_{g-s}) \cdot \nabla T}_{\text{advection}} + \nabla \cdot (-\lambda \cdot \nabla T) = \underbrace{-H_{vap} \dot{m}_{vap} + H_{dehyd} \dot{m}_{dehyd}}_{\text{phase-change energy}} \quad (2.68)$$

Compared to the classical heat equation Equation (2.5) $\rho C_p \frac{\partial T}{\partial t} - \nabla \cdot (\lambda \nabla T) = 0$, two additional contributions appear:

- **Advective heat transport:** The bulk flow of liquid water and gas, driven by pressure gradients, transport enthalpy through the material. This term redistributes energy along the flow paths and can be significant when permeability and pressure gradients are large.
- **Phase-change energy (right-hand side):** Concrete does not self-generate heat; these terms represent energy consumed by evaporation ($-H_{vap} \dot{m}_{vap}$, heat sink since $\dot{m}_{vap} > 0$) and dehydration ($+H_{dehyd} \dot{m}_{dehyd}$, also a heat sink since $\dot{m}_{dehyd} < 0$). Both locally slow the temperature rise.

After replacing the mass fluxes by Darcy's law (Equations (2.18) and (2.19)), the energy conservation takes its final coupled form:

$$\begin{aligned} \rho C_p \frac{\partial T}{\partial t} - K \left(C_l \frac{\rho_l k_{rl}}{\mu_l} (\nabla p_g - \nabla p_c) + C_g \frac{\rho_g k_{rg}}{\mu_g} \nabla p_g \right) \cdot \nabla T \\ - \nabla \cdot (\lambda \cdot \nabla T) = -H_{vap} \dot{m}_{vap} + H_{dehyd} \dot{m}_{dehyd} \end{aligned} \quad (2.69)$$

where the overall heat capacity ρC_p (Equation (2.7)) and thermal conductivity λ (Equation (2.8)) are defined in Section 2.1.2.

Thus, the thermal and hydric fields are *strongly coupled*: temperature modifies the source terms and transport coefficients in the moisture equation, while moisture content and fluid flow modify the heat capacity, conductivity, and introduce latent heat and advection terms in the energy equation.

2.4.2 Thermo-hydric input to the mechanical field

The mechanical behavior of heated concrete is driven by the thermal and hydric fields. In the framework adopted here, the coupling is *one-way*: the outputs of the TH problem — temperature T , gas pressure p_g , and capillary pressure p_c — serve as input to the mechanical problem. The mechanical field feeds back into the TH equations only through the damage-enhanced permeability; this coupling is discussed in Section 2.5.1.

In the staggered TH→M coupling, the thermo-hydric fields produce two types of mechanical loading on the solid skeleton:

1. **Free strains** (ϵ_{th} , ϵ_{sh}), which modify the elastic strain entering Hooke's law (Equation (2.47));
2. **Pore pressure loading**, which acts directly on the stress state through the Biot effective stress:

$$\boldsymbol{\sigma}' = \boldsymbol{\sigma} + \mathbf{I} \alpha p_s \quad (2.70)$$

where $\boldsymbol{\sigma}$ is the total (nominal) stress from Equation (2.50) and p_s is the average pore pressure defined in Equation (2.76).

Strain decomposition

When a mechanically loaded concrete element is exposed to high temperature, the total strain is decomposed as a superposition of components of different origins [3]:

$$\boldsymbol{\epsilon} = \boldsymbol{\epsilon}_\sigma + \boldsymbol{\epsilon}_{th} + \boldsymbol{\epsilon}_{sh} \quad (2.71)$$

where:

- $\boldsymbol{\epsilon}_\sigma$ represents the *mechanical strains* induced by external loading (elastic strain, creep strain, etc.);
- $\boldsymbol{\epsilon}_{th}$ represents the *thermal dilation strain*, driven by the temperature field;

- $\boldsymbol{\varepsilon}_{sh}$ represents the *capillary shrinkage strain*, driven by the capillary pressure field.

In general, the mechanical strain includes elastic and creep contributions:

$$\boldsymbol{\varepsilon}_\sigma = \boldsymbol{\varepsilon}_{el} + \boldsymbol{\varepsilon}_{creep} \quad (2.72)$$

Since creep is neglected in this work, $\boldsymbol{\varepsilon}_{creep} = \mathbf{0}$ and thus $\boldsymbol{\varepsilon}_\sigma = \boldsymbol{\varepsilon}_{el}$

Thermal dilation

The thermal dilation strain is isotropic and produces a uniform expansion of the material, which is expressed in incremental form as [3]:

$$d\boldsymbol{\varepsilon}_{th} = \beta_s(T) dT \mathbf{I} \quad (2.73)$$

where $\mathbf{I}$ is the second-order identity tensor and $\beta_s(T)$ is the thermal dilation coefficient, which for concrete can be approximated as a linear function of temperature:

$$\beta_s(T) = A_{B1} (T - T_0) + A_{B0} \quad (2.74)$$

with A_{B0} and A_{B1} being material constants.

The thermal dilation strain is isotropic and produces a uniform expansion of the material. Near the heated surface, the steep thermal gradient creates a strong differential expansion: the hot surface layer tends to expand while the cooler interior restrains it, inducing compressive stresses at the surface and tensile stresses at depth.

Capillary shrinkage

The drying process modifies the pore pressure state, which in turn induces a volumetric deformation of the solid skeleton. The capillary shrinkage strain is expressed as [3]:

$$d\boldsymbol{\varepsilon}_{sh} = \frac{\alpha}{K_T} \frac{dp_s}{dt} \mathbf{I} \quad (2.75)$$

where α is the Biot coefficient, K_T is the bulk modulus of the drained skeleton, and p_s is the average pore pressure acting on the solid skeleton, defined as:

$$p_s = p_g - S_l p_c = S_g p_g + S_l p_l \quad (2.76)$$

This expression represents the saturation-weighted average of the gas and liquid pressures. Since p_g and p_c are direct outputs of the TH problem, p_s is entirely determined by the

TH solution.

As the concrete dries during heating, the capillary pressure increases (the pores desaturate), leading to a contraction (shrinkage) of the solid matrix. This effect is most pronounced in the drying front region where the saturation gradient is steepest.

Effective stress and pore pressure loading

Beyond the free strains (ϵ_{th} , ϵ_{sh}), the pore pressure directly modifies the stress state in the solid skeleton through the concept of effective stress introduced in Equation (2.50), which is defined as:

$$\boldsymbol{\sigma}' = \boldsymbol{\sigma}^{Total} + \mathbf{I} \alpha p_s \quad (2.77)$$

where $\boldsymbol{\sigma}^{Total}$ is the total stress tensor and p_s is the average pore pressure defined in Equation (2.76).

In heated concrete, gas pressure builds up due to evaporation and dehydration (see Section 2.2.4). This increase in p_g raises p_s , which reduces the effective compressive stress in the skeleton, effectively pushing the material towards tensile failure. When the tensile effective stress exceeds the tensile strength f_t , cracking initiates.

Note that f_t , along with Young's modulus E and compressive strength f_c , are prescribed as empirical functions of temperature to account for the progressive degradation of the cementitious matrix at high temperatures.

2.5 THM model and spalling

This section assembles the governing equations of the thermo-hydro-mechanical (THM) model from the conservation laws and constitutive relations developed in the previous sections. The coupled system is then used to explain how spalling arises from the interaction between thermal, hydric, and mechanical fields.

2.5.1 Full THM governing formulation

The state of concrete at high temperature is described by four primary variables [3]:

$$\mathcal{U} = \{p_g, p_c, T, \mathbf{u}\} \quad (2.78)$$

where p_g is the gas pressure, p_c is the capillary pressure, T is the temperature, and $\mathbf{u}$ is the displacement vector.

The model consists of four conservation equations, each associated with one primary variable. Their final forms, after substitution of Darcy's law, Fick's law, and the constitutive relations, are as follows.

Dry air conservation

$$\begin{aligned} & \phi(1 - S_l) \left(\frac{\partial \rho_a}{\partial T} \frac{\partial T}{\partial t} + \frac{\partial \rho_a}{\partial p_c} \frac{\partial p_c}{\partial t} + \frac{\partial \rho_a}{\partial p_g} \frac{\partial p_g}{\partial t} \right) + (1 - S_l) \rho_a \frac{\partial \phi}{\partial T} \frac{\partial T}{\partial t} \\ & - \phi \rho_a \left(\frac{\partial S_l}{\partial p_c} \frac{\partial p_c}{\partial t} + \frac{\partial S_l}{\partial T} \frac{\partial T}{\partial t} \right) - \nabla \cdot \left(\frac{K \rho_a k_{rg}}{\mu_g} \nabla p_g \right) - \nabla \cdot \left(D \rho_g \frac{M_v M_a}{M_g^2} \nabla \frac{p_a}{p_g} \right) = 0 \end{aligned} \quad (2.79)$$

Water species conservation

$$\begin{aligned} & (S_l \rho_l - (1 - S_l) \rho_v) \frac{\partial \phi}{\partial T} \frac{\partial T}{\partial t} + S_l \phi \frac{\partial \rho_l}{\partial T} \frac{\partial T}{\partial t} + \phi (\rho_l - \rho_v) \left(\frac{\partial S_l}{\partial T} \frac{\partial T}{\partial t} + \frac{\partial S_l}{\partial p_c} \frac{\partial p_c}{\partial t} \right) \\ & + (1 - S_l) \phi \left(\frac{\partial \rho_v}{\partial T} \frac{\partial T}{\partial t} + \frac{\partial \rho_v}{\partial p_c} \frac{\partial p_c}{\partial t} + \frac{\partial \rho_v}{\partial p_g} \frac{\partial p_g}{\partial t} \right) \\ & - \nabla \cdot \left(\frac{K \rho_l k_{rl}}{\mu_l} (\nabla p_g - \nabla p_c) \right) - \nabla \cdot \left(\frac{K \rho_v k_{rg}}{\mu_g} \nabla p_g \right) - \nabla \cdot \left(D \rho_g \frac{M_v M_a}{M_g^2} \nabla \frac{p_v}{p_g} \right) = -\dot{m}_{dehyd} \end{aligned} \quad (2.80)$$

Energy conservation

$$\begin{aligned} & \rho C_p \frac{\partial T}{\partial t} - K \left(C_l \frac{\rho_l k_{rl}}{\mu_l} (\nabla p_g - \nabla p_c) + C_g \frac{\rho_v k_{rg}}{\mu_g} \nabla p_g \right) \cdot \nabla T - \nabla \cdot (\lambda \cdot \nabla T) \\ & = -H_{vap} \dot{m}_{vap} + H_{dehyd} \dot{m}_{dehyd} \end{aligned} \quad (2.81)$$

Momentum conservation

By neglecting inertial forces:

$$\nabla \cdot \boldsymbol{\sigma}^{Total} + \rho \mathbf{g} = \mathbf{0} \quad (2.82)$$

where $\mathbf{g}$ is the gravitational acceleration and the total density is:

$$\rho = (1 - \phi) \rho_s + \phi (S_l \rho_l + (1 - S_l) \rho_g) \quad (2.83)$$

The total stress $\boldsymbol{\sigma}^{Total}$ is related to the effective stress via Bishop's relation (Equation (2.77)), which in turn depends on the primary variables p_g and p_c .

The governing equations presented in this chapter — dry air conservation, water species conservation, energy conservation, and momentum conservation — together with the con-

stitutive laws, form a complete THM model for concrete exposed to fire. These equations are continuous partial differential equations defined on the domain Ω . Their numerical solution requires spatial and temporal discretization, which is the subject of the following Chapter 3.

2.5.2 Spalling mechanisms

Spalling is defined as the violent or non-violent detachment of layers or pieces of concrete from the surface of a structural element during or after exposure to rapidly rising temperatures. It may lead to premature structural failure through reinforcement exposure and cross-section reduction. Several catastrophic tunnel fires (Channel Tunnel 1996, Mont-Blanc 1999, St. Gotthard 2001) have illustrated the severity of this phenomenon [3].

Despite extensive experimental research, the mechanisms behind spalling are not yet fully understood and no general consensus on a single theory has been reached. The two principal mechanisms most broadly accepted are presented below, followed by their combined action.

Thermal gradient mechanism

[REVIEW] This section is currently under development and will be refined as the study progresses.

This mechanism is related to the thermo-mechanical processes. When one face of a concrete member is exposed to fire, a steep temperature gradient develops through the thickness. The resulting differential thermal dilation produces (see Figure ??):

1. **Compressive stresses in the heated cover:** The surface layers tend to expand but are restrained by the cooler interior, generating significant compressive stresses parallel to the heated surface.
2. **Tensile stresses in the interior:** The restraint of the expanding surface layers induces tensile stresses in deeper layers of the material.
3. **Fracture and energy release:** When the tensile stress exceeds the (temperature-degraded) tensile strength $f_t(T)$, cracks develop parallel to the surface. The sudden, unstable release of the elastic energy stored in the compressed surface layers can drive the explosive ejection of concrete fragments.

In terms of the THM model, this mechanism involves the energy equation (2.81) (which determines the temperature field), the thermal dilation strain (Eq. (2.73)), and the Mazars damage model which captures the tensile cracking.

High performance concrete (HPC) is more prone to thermal gradient-induced spalling because it is far more *brittle* than normal strength concrete: the higher elastic energy stored before failure leads to a more violent release.

Pore pressure mechanism (moisture clog)

[REVIEW] This section is currently under development and will be refined as the study progresses.

This mechanism is related to the thermo-hydral processes. The sequence of events is (see Figure ??):

1. **Formation of a dry zone:** As the surface is heated, free water evaporates and chemically bound water is released as vapor through dehydration. A dry zone forms near the heated face.
2. **Vapor migration:** Due to pressure gradients, part of the vapor is evacuated toward the heated face, while part is driven toward the cooler interior.
3. **Condensation and moisture clog:** The inward-migrating vapor condenses when it reaches regions where the thermodynamic conditions are satisfied ($T < T_{sat}$). This process continues until a quasi-saturated zone is formed, known as the *moisture clog*, which acts as an impermeable barrier preventing further vapor migration toward the cold side.
4. **Pressure build-up:** Behind the moisture clog, the gas pressure p_g increases sharply as continued evaporation feeds vapor into a region from which it cannot escape. In addition, the thermal dilation of liquid water in saturated pores also contributes to pressure build-up.
5. **Tensile failure:** When the pore pressure exceeds the tensile strength of the material, cracks develop parallel to the surface, potentially leading to explosive spalling.

In terms of the THM model, this mechanism involves the water species conservation equation (2.80) (which determines the pressure field), the permeability law Equation (2.39)), and the effective stress (Eq. (??)) through which pore pressure loads the solid skeleton.

The key material parameters governing this mechanism are the *intrinsic permeability* K_0 and the *initial moisture content*. Low permeability hinders vapor evacuation, while high moisture content provides more water to be evaporated, both promoting higher pore pressures.

Combined mechanism

[REVIEW] This section is currently under development and will be refined as the study progresses.

In practice, explosive spalling generally occurs under the *combined action* of pore pressures and thermal stresses. The spalling condition can be expressed schematically as:

$$\sigma_{thermal}(T) + \sigma_{pore}(p_g, p_c, S_l) \geq f_t(T) \quad (2.84)$$

where $\sigma_{thermal}$ represents the thermal stress from differential dilation, σ_{pore} represents the stress from pore pressure loading (via effective stress), and $f_t(T)$ is the temperature-degraded tensile strength. When the sum of stresses exceeds the tensile strength, cracks develop parallel to the heated surface, often leading to violent failure of the fire-exposed region.

This combined criterion highlights why the complete THM model is needed: neither a purely thermal analysis (T only) nor a purely hydal analysis (p_g, p_c only) can capture the full picture.

Chapter 3

Numerical implementation

[REVIEW] This chapter is currently empty and is intended to outline the proposed structure of the thesis.

This chapter describes the numerical solution of the THM governing equations developed in Chapter 2. The implementation proceeds incrementally: the thermal, hydric, and mechanical models are first solved separately, then coupled to form the full THM system. All implementations are carried out in the finite element code Cast3M.

3.1 Discretization

3.1.1 Spatial discretization

[REVIEW]

The specific coupling method mentioned in Section 2.3 between the TH and mechanical solvers has not yet been finalized and will be updated in Chapter 2 and Chapter 3 as the study progresses.

Applying the standard Galerkin finite element method to the three TH conservation equations (Equations (2.79) to (2.81)) yields the semi-discrete system [3]:

$$\mathbf{C} \dot{\mathbf{Y}} + \mathbf{K} \mathbf{Y} = \mathbf{f} \quad (3.1)$$

where $\mathbf{Y} = \{\bar{p}_g, \bar{p}_c, \bar{T}\}$ is the vector of nodal TH unknowns. The operators $\mathbf{C}$ (capacity),

$\mathbf{K}$ (conductivity), and $\mathbf{f}$ (forcing) are 3×3 block matrices:

$$\mathbf{K} = \begin{pmatrix} K_{gg} & K_{gc} & K_{gt} \\ K_{cg} & K_{cc} & K_{ct} \\ K_{tg} & K_{tc} & K_{tt} \end{pmatrix}, \quad \mathbf{C} = \begin{pmatrix} C_{gg} & C_{gc} & C_{gt} \\ 0 & C_{cc} & C_{ct} \\ 0 & C_{tc} & C_{tt} \end{pmatrix}, \quad \mathbf{f} = \begin{pmatrix} f_g \\ f_c \\ f_t \end{pmatrix} \quad (3.2)$$

The off-diagonal entries K_{ij} , C_{ij} ($i \neq j$) encode the coupling between the thermal and hydric fields. Detailed expressions of each block are given in [3], Appendix A.

The mechanical problem (Equation (2.82)) is solved in a staggered manner: at each time step, the converged TH fields $\bar{T}$, $\bar{p}_g$, $\bar{p}_c$ enter as prescribed loading. The discrete equilibrium (Equation (2.48)) reads:

$$[\mathbf{K}_M]\{\mathbf{U}\} = \{\mathbf{F}\} \quad (3.3)$$

where $\mathbf{K}_M$ (Equation (2.58)) contains the damaged stiffness $(1-\mathcal{D})\mathbf{C}$ — the displacement-dependent part that remains on the left-hand side — and $\mathbf{F}$ (Equation (2.49)) collects the TH-prescribed loads $(\boldsymbol{\varepsilon}^{th}, \boldsymbol{\varepsilon}^{sh}, \alpha p_s)$ that do not depend on $\mathbf{U}$.

3.1.2 Temporal discretization

[REVIEW] This section is currently under development and will be refined as the study progresses.

The time integration of Equation (3.1) is carried out using the Wilson- θ method [3], which evaluates the equation at an intermediate time $t_{n+\theta} = t_n + \theta \Delta t$ with $\theta \in [0, 1]$. This transforms the semi-discrete system into a fully discrete algebraic system at each time step:

$$\tilde{\mathbf{K}} \Delta \mathbf{Y}^{n+1} + \mathbf{K} \mathbf{Y}^n = \mathbf{f}^{n+\theta} \quad (3.4)$$

where:

$$\Delta \mathbf{Y}^{n+1} = \mathbf{Y}^{n+1} - \mathbf{Y}^n, \quad \tilde{\mathbf{K}} = \frac{\mathbf{C}}{\Delta t} + \theta \mathbf{K} \quad (3.5)$$

The parameter θ controls the scheme: $\theta = 0$ gives the explicit forward Euler method, $\theta = 1$ the fully implicit backward Euler, and $\theta = 0.5$ the Crank-Nicolson scheme. In practice, $\theta = 1$ is used for unconditional stability.

Since the capacity and conductivity matrices depend nonlinearly on the unknowns ($\mathbf{C} = \mathbf{C}(\mathbf{Y})$, $\mathbf{K} = \mathbf{K}(\mathbf{Y})$), Equation (3.4) is solved iteratively using the Newton-Raphson method within each time step.

3.1.3 Solution strategy

[REVIEW] This section is currently under development and will be refined as the study progresses.

The TH subsystem (Equation (3.4)) is solved *monolithically*: all three unknowns p_g , p_c , T are updated simultaneously within a single Newton-Raphson loop at each time step.

The mechanical problem (Equation (3.3)) is solved in a *staggered* manner: at each time step, the converged TH solution provides $\bar{T}$, $\bar{p}_g$, $\bar{p}_c$, which are used to assemble $\mathbf{F}$ (Equation (2.49)) and solve for $\mathbf{U}$. The damage variable $\mathcal{D}$ computed from the Mazars model feeds back to the intrinsic permeability via Equation (2.39), creating a weak M→H coupling updated at the next time step.

3.2 Model description and parameters

This geometry is chosen as a representative benchmark for validating the THM implementation against the experimental results presented in Chapter 4, obtained from an experimental campaign conducted under the supervision of S. Dal Pont. The model geometry, material properties, and boundary conditions are described in the following subsections.

3.2.1 Geometry

This section is currently under development and will be refined as the study progresses.

Sample mesh code:

```

1  OPTI ECHO 0;
2  OPTI 'DIME' 2 'ELEM' 'QUA4' ;
3
4  * 1) GEOMETRY AND MESH DEFINITION
5
6  *GEOMETRY DEFINITION
7  LONG      = 3.;
8  HAUT      = 0.5;
9
10 *NUMBER OF MESH SEGMENT
11 NLONG     = 35;
12 NHAUT     = 5;
13
14 *POINTS CREATION

```

```

15 PA      = 0. 0.;
16 PB      = LONG 0.;
17 PC      = LONG HAUT;
18 PD      = 0. HAUT;
19 TRAC (PA ET PB ET PC ET PD);
20
21 *MESH LINES CREATION
22 LAB      = DROI NLONG PA PB;
23 LBC      = DROI NHAUT PB PC;
24 LCD      = DROI NLONG PC PD;
25 LDA      = DROI NHAUT PD PA;
26
27 *MESH SURFACE CREATION
28 MAIL1    = DALL LAB LBC LCD LDA;
29 TRAC MAIL1;

```

3.2.2 Material properties

3.2.3 Boundary conditions and loadings

This section is currently under development and will be refined as the study progresses.

3.3 Implementation of the thermal model

3.3.1 Stationary linear thermal analysis

This section is currently under development and will be refined as the study progresses.

3.3.2 Transient linear and non-linear thermal analysis

This section is currently under development and will be refined as the study progresses.

3.4 Implementation of the hydric model

3.4.1 Drying

This section is currently under development and will be refined as the study progresses.

3.4.2 Shrinkage

This section is currently under development and will be refined as the study progresses.

3.5 Implementation of the mechanical model

3.5.1 Elastic linear mechanical model

This section is currently under development and will be refined as the study progresses.

3.5.2 Mazars model

This section is currently under development and will be refined as the study progresses.

3.6 Implementation of the TH coupled model

This section is currently under development and will be refined as the study progresses.

3.7 Implementation of the THM coupled model

This section is currently under development and will be refined as the study progresses.

3.8 Numerical results

This section is currently under development and will be refined as the study progresses.

Chapter 4

Experimental data and Model validation

[REVIEW] This chapter is currently empty and is intended to outline the proposed structure of the thesis.

4.1 Experimental data

4.1.1 Experimental tests and material properties

This section is currently under development and will be refined as the study progresses.

4.1.2 Thermal, hydraulic and mechanic loadings

This section is currently under development and will be refined as the study progresses.

4.1.3 Measured data

This section is currently under development and will be refined as the study progresses.

4.2 Validation

4.2.1 Comparison between numerical and experimental results

This section is currently under development and will be refined as the study progresses.

4.2.2 Discussions on model performance

This section is currently under development and will be refined as the study progresses.

Chapter 5

Probabilistic analysis of the THM model

[REVIEW] This chapter is currently a draft version and will undergo further review and revision.

5.1 Sources of uncertainty and concrete heterogeneity

This section follows the foundational framework presented in [1].

[REVIEW]

Main ideas:

- Concrete is not uniform, so its properties vary from place to place.
- Material parameters (e.g., stiffness and permeability) are uncertain.
- Measurements and model assumptions also add uncertainty.

5.1.1 Motivation for probabilistic assessment

In civil engineering, a structure or mechanical system is considered safe when it remains fit for duty for the duration of its service life, without causing damage to itself or its environment. Traditionally, deterministic models have been used to evaluate structural safety. However, the inevitable gap between a real physical system and a simplified numerical model, along with the unforeseeable nature of future loads and environmental conditions, inherently leads to uncertainty.

5.1.2 Classification of uncertainties

Predicting the exact lifetime or mechanical response of a construction project is impossible without accounting for multiple sources of uncertainty. According to reliability theory, these uncertainties can be broadly classified into two main categories: Aleatoric and Epistemic.

5.1.3 Concrete heterogeneity and material variability

A critical source of aleatoric uncertainty in civil engineering is the inherent heterogeneity of construction materials, such as concrete and geomaterials.

- **Historical and environmental dependence:** Concrete is not perfectly uniform. Its physical and mechanical properties depend heavily on its entire formation history, the conditions during casting, internal chemical reactions (like alkali-silica reactions), and long-term degradation processes caused by the surrounding environment.
- **Continuous and discrete spatial variations:** Because of this historical dependence, material parameters vary significantly from place to place. This spatial heterogeneity manifests in two ways:
 1. *Continuous variations:* Gradual spatial fluctuations in properties such as stiffness, Young's modulus, Poisson's ratio, density, or friction.
 2. *Discrete variations:* The localized appearances of defects such as micro-cracks, water inlets, networks of capillaries, or weak points within the structure.

5.2 Stochastic finite element framework (Monte Carlo)

[REVIEW]

Main ideas:

- Treat uncertain material parameters as random variables.
- Generate many random samples.
- Run the THM model for each sample.
- Collect the outputs and analyze variability and sensitivity.

5.2.1 Random Field theory and Spatial variability

[REVIEW] This section is currently under development and will be refined as the study progresses.

Random fields

Spatial variability of material properties can be described using random field theory, in which a parameter is modeled as a stochastic function defined over the spatial domain. In this representation, the value of the property varies from point to point according to a prescribed probability distribution and spatial correlation structure. Random fields therefore provide a convenient framework to represent the heterogeneous nature of materials such as concrete.

Discretized random field

For numerical simulations, the continuous random field must be discretized in order to be implemented within a finite element model. This discretization assigns random values of the considered property to the elements or integration points of the mesh. In this way, the spatial variability of the material parameters can be incorporated directly into the computational model.

Spatial correlation length (λ)

[REVIEW] This section requires additional references to support the statements presented.

A fundamental parameter in the generation of random fields is the spatial correlation length, often denoted as λ (or b).

Depending on the assigned value of λ :

- A very small correlation length ($\lambda \rightarrow 0$) implies that the material properties fluctuate rapidly and erratically over short distances
- A large correlation length ($\lambda \rightarrow \infty$) implies a slow spatial variation, moving towards a uniformly homogeneous material

[REVIEW]

In the context of this study, the choice of the correlation length is closely related to

the maximum aggregate size of the concrete mixture.

5.2.2 Transformation of Lognormal to Gaussian distribution

In practical finite element implementations using the Cast3M software, material parameters like the Young's modulus (E) are often assigned a lognormal random field to ensure the generated stiffness values remain strictly positive. However, the built-in random field operator (ALEA) generates Gaussian (normal) distributions, necessitating a mathematical transformation.

[REVIEW]

[REVIEW] This section requires additional references to support the statements presented.

Assuming the actual mean of the material's Young's modulus is μ_E and its standard deviation is σ_E . The fundamental relationship between these two variables is expressed through the exponential transformation:

$$E = \exp(G) \iff G = \ln(E)$$

From statistical properties, we can establish a system of two equations relating the moments of E (μ_E, σ_E) and G (μ_G, σ_G) as follows:

$$\begin{cases} \mu_E = \exp\left(\mu_G + \frac{\sigma_G^2}{2}\right) \\ \sigma_E^2 = [\exp(\sigma_G^2) - 1] \exp(2\mu_G + \sigma_G^2) \end{cases} \quad (5.1)$$

To find the input parameters μ_G and σ_G for the random number generation algorithm, we need to solve the above system of equations.

1. Solving for σ_G^2

By squaring the first equation, we get:

$$\mu_E^2 = \exp(2\mu_G + \sigma_G^2)$$

Substituting this result into the second equation yields:

$$\sigma_E^2 = [\exp(\sigma_G^2) - 1] \mu_E^2$$

Rearranging the terms, we obtain:

$$\exp(\sigma_G^2) = \frac{\sigma_E^2}{\mu_E^2} + 1$$

Taking the natural logarithm of both sides gives the variance of the Gaussian distribution:

$$\sigma_G^2 = \ln \left(1 + \frac{\sigma_E^2}{\mu_E^2} \right)$$

2. Solving for μ_G

Using the first equation and isolating $\exp(\mu_G)$, we have:

$$\mu_E = \exp(\mu_G) \cdot \exp \left(\frac{\sigma_G^2}{2} \right)$$

Substituting $\sigma_G^2 = \ln \left(1 + \frac{\sigma_E^2}{\mu_E^2} \right)$ into the exponential term, we get:

$$\mu_E = \exp(\mu_G) \cdot \exp \left(\ln \left(\sqrt{1 + \frac{\sigma_E^2}{\mu_E^2}} \right) \right) = \exp(\mu_G) \cdot \sqrt{1 + \frac{\sigma_E^2}{\mu_E^2}}$$

Rearranging to solve for μ_G :

$$\exp(\mu_G) = \frac{\mu_E}{\sqrt{1 + \frac{\sigma_E^2}{\mu_E^2}}} \implies \mu_G = \ln \left(\frac{\mu_E}{\sqrt{1 + \frac{\sigma_E^2}{\mu_E^2}}} \right)$$

Summary of calculation steps in the numerical algorithm

Based on the exact solutions derived above, the implementation follows these sequential steps:

1. The coefficient of variation (cov_E) of the desired lognormal distribution is calculated:

$$cov_E = \frac{\sigma_E}{\mu_E}$$

2. The mean of the equivalent Gaussian distribution (μ_G):

$$\mu_G = \ln \left(\frac{\mu_E}{\sqrt{1 + cov_E^2}} \right)$$

3. The variance of the equivalent Gaussian distribution (σ_G^2):

$$\sigma_G^2 = \ln(1 + cov_E^2)$$

4. The standard deviation of the Gaussian distribution (σ_G):

$$\sigma_G = \sqrt{\ln(1 + cov_E^2)}$$

5. A standard Gaussian random field (**GFIELD**) is then generated using the **ALEA** operator with the computed Gaussian mean μ_G and standard deviation σ_G .
6. Finally, this Gaussian field is transformed back into the actual lognormal distribution (**EFIELD**) using the exponential function. A scale factor of 10^9 is multiplied to convert the physical unit from GPa to Pa for the mechanical solver:

$$EFIELD = \exp(GFIELD) \times 10^9$$

5.2.3 Integration of spatial variability into the THM model

This section is currently under development and will be refined as the study progresses.

5.2.4 Monte Carlo simulation framework

After successfully implementing the log-normal random fields to represent the concrete's spatial heterogeneity, the next step in the probabilistic assessment is to perform multiple independent realizations. This is achieved through a Monte Carlo simulation framework.

In the finite element code Cast3M, this iterative process is seamlessly governed by the **REPETER** operator.

Simulation loop and dynamic material updating

This section is currently under development and will be refined as the study progresses

Data extraction and post-processing

This section is currently under development and will be refined as the study progresses

5.3 Gaussian Quadrature framework

This section is currently under development and will be refined as the study progresses.

5.3.1 Principle of Gaussian Quadrature

[REVIEW]

Main ideas as follows:

From integration to weighted sum

Orthogonal polynomials and weighting functions

Abscissas and weights construction

5.3.2 Statistical moment estimation

[REVIEW]

Main ideas as follows:

Mean, variance, skewness, kurtosis from quadrature

Variance decomposition per variable

5.3.3 PDF, CDF and reliability assessment

[REVIEW]

Main ideas as follows:

Approximation methods (Pearson, Winterstein, Exp-Polynomial)

Probability of failure and reliability index

5.3.4 Computational efficiency

[REVIEW]

Main ideas as follows:

Cost comparison with Monte Carlo

Quick Quadrature for high-dimensional problems

Data extraction: moments computed directly from weighted sum

Limitations: curse of dimensionality

5.4 Sensitivity analysis

[REVIEW]

Main ideas:

- Sensitivity indicators: Young modulus...
- Change one input parameter at a time (or groups of parameters).
- Measure how much the outputs change.
- Rank the parameters from most to least influential.

[REVIEW]

18 key parameters are selected for sensitivity analysis [6].

5.4.1 Characterization of input parameters

This section is currently under development and will be refined as the study progresses.

Characterize the chosen input parameters in terms of domain variations and coefficient

of variation.

[REVIEW]

Main ideas as follows:

Chosen Random variables

Correlated vs uncorrelated parameters

Physical correlations

5.4.2 Sensitivity indicators and ranking methods

This section is currently under development and will be refined as the study progresses.

Pearson correlation, Sobol indices (if variance-based), or Sensitivity derivatives (OAT - One-At-a-Time)

[REVIEW]

Main ideas as follows:

Variance decomposition

Uncorrelated parameters

Correlated parameters

Quadrature: one-variable-at-a-time moments

Monte Carlo: Sobol indices and Pearson correlation

5.4.3 Identification of dominant parameters

This section is currently under development and will be refined as the study progresses.

[REVIEW]

Main ideas as follows:

Ranking from most to least influential

Comparison: Quadrature ranking vs Monte Carlo ranking

Physical interpretation of dominant parameters

5.5 Reliability analysis

[REVIEW]

Main ideas as follows:

5.5.1 Probability of failure and reliability index

This section is currently under development and will be refined as the study progresses.

5.5.2 Probability of failure from moment-based PDF

This section is currently under development and will be refined as the study progresses.

5.5.3 Probability of failure from Monte Carlo sampling

This section is currently under development and will be refined as the study progresses.

5.5.4 Effect of spatial heterogeneity on structural safety

This section is currently under development and will be refined as the study progresses.

Chapter 6

Conclusions and Perspectives

[REVIEW] This chapter is currently empty and is intended to outline the proposed structure of the thesis.

6.1 Main findings

This section is currently under development and will be refined as the study progresses.

6.2 Model limitations and possible improvements

This section is currently under development and will be refined as the study progresses.

6.3 Perspectives for future research

This section is currently under development and will be refined as the study progresses.

List of Figures

List of Tables

2.1	Van Genuchten parameters at ambient temperature	13
-----	---	----

Bibliography

- [1] Julien Baroth, Breysse Denys, and Franck Schoefs. “Introduction”. In: *Construction Reliability - Safety, Variability and Sustainability*. Jan. 2011, pp. xvii–xxxiii. ISBN: 978-1-84821-230-5. DOI: [10.1002/9781118601099](https://doi.org/10.1002/9781118601099).
- [2] Theodore Bergman and Adrienne Lavine. “Introduction”. In: *Fundamentals of Heat and Mass Transfer*. 8th ed. John Wiley & Sons, Inc., [2017, pp. 1–45. ISBN: 978-1-119-32042-5.
- [3] Dorjan Dauti. “A Combined Experimental and Numerical Approach to Spalling of High-Performance Concrete Due to Fire”. Theses. Université Grenoble Alpes, Sept. 2018.
- [4] François Di Paola. *Starting with Cast3m: Thermomechanical Calculations*. CEA, Mar. 27, 2023. URL: <https://www-cast3m.cea.fr/index.php?xml=maj2011>.
- [5] François Hamon. *Model of Damage of MAZARS*. R7.01.08. Université du Québec à Trois-Rivières, Sept. 25, 2013.
- [6] Ning Liu, Bin Hu, and Zhi-Wen Yu. “Stochastic Finite Element Method for Random Temperature in Concrete Structures”. In: *International Journal of Solids and Structures* 38 (Sept. 2001), pp. 6965–6983. DOI: [10.1016/S0020-7683\(00\)00414-5](https://doi.org/10.1016/S0020-7683(00)00414-5).