

AMENDMENT NO. 1 JULY 2021

TO

IS 1417 : 2016 GOLD AND GOLD ALLOYS, JEWELLERY/ ARTEFACTS — FINENESS AND MARKING — SPECIFICATION

(*Fourth Revision*)

(*Page 1, clause 1.2*) — Substitute the following for existing note below clause **1.2**

‘NOTES:

1 Artefacts cover medallions and utensils

2 “Watches” and “Pens” made of gold/gold alloys do not fall under the purview of Artefacts.’”

(*Page 1, clause 2*) — Substitute the following references for the existing:

<i>‘IS No.</i>	<i>Title</i>
1418 : 2009	Determination of gold in gold bullion, gold alloys and gold jewellery/artefacts — Cupellation (fire assay) method (<i>third revision</i>)
3095 : 1999	Gold solders for use in manufacture of jewellery — Specification (<i>second revision</i>)
15820 : 2009	General requirements for establishment and operation of assaying and hallmarking centre’

(*Page 1, clause 4.1*) — Substitute the following for existing:

‘Gold and gold alloys used for manufacture of gold jewellery and artefacts, gold bullion and gold coins shall be classified based on the minimum declared

Price Group 1

fineness and shall be in accordance with the following grades/designations depending upon minimum declared fineness:

Grades / Designations	Declared Minimum Fineness (in ppt)	Purity in Carat (K) (Approximate)
(1)	(2)	(3)
24 KF	999	-
24 KS	995	-
23 K	958	23
22 K	916	22
20 K	833	20
18 K	750	18
14 K	585	14

NOTES:

1 Purity in Carat mentioned are approximate values and are given for easy identification of consumer.

2 Grade of 24 KF means Fine gold of fineness of 999 parts per thousand (‰) and above.

3 Grade of 24 KS means Standard gold of fineness of 995 parts per thousand (‰) and above.

4 Gold/gold alloy of “24 KF” designation is applicable for bullion and Coins only and is not applicable for Gold jewellery and artefacts.’

(Page 1, clause **4.1.1 a**) — Delete

(Page 1, clause **4.1.1 b**) — Renumber the clause as **4.1.1 a**) and substitute the following for the existing:

‘a) Gold alloys used for manufacturing gold jewellery/artefacts shall be free from cadmium, iridium, ruthenium and osmium.’

(Page 1, clause **4.1.1 c**) — Renumber the clause as **4.1.1 b**) and substitute the following for the existing:

‘b) Presence of cadmium, iridium, ruthenium and osmium in the gold jewellery/Artefacts shall be detected by X-ray fluorescence (XRF) test method.

NOTE — Standard for XRF test method is under development. Clauses **4.1.1 a**) and **4.1.1 b**) shall be in abeyance till XRF test method is established.’

(Page 2, clause 5.1, line 7 and 8) — Substitute ‘their cadmium content is within permissible limit as given in 4.1.1 b)’ by ‘they are free from cadmium’.

(Page 2, clause 6.1 a) — Substitute the following for the existing:

- ‘a) The gold jewellery/artefacts shall be hallmarked by BIS recognized assaying and hallmarking centres only. The hallmarked articles shall carry the following markings in the order mentioned:
- 1) BIS standard mark,
 - 2) Grade/ designation and its declared minimum fineness in ppt, and
 - 3) “Unique alphanumeric ID” of the article issued by the assaying and hallmarking center.’