TEST REPORT

Document ID: DOC-0001704
Project: PRJ-036
Uploaded on: 2025-01-25
Uploaded by: user044
Export class: EAR99

Report No: TR-511260
Laboratory: Lab South
Test Date: 2025-01-25

Part P-102080 rev B.1

Test	Requirement	Measured	Result
Dimensional check	0.05 - 0.5 mm	0.544	FAIL
Salt spray	48 - 500 hours	307.973	PASS
Hardness	20 - 60 HRC	57.691	PASS
Tensile strength	250 - 520 MPa	235.475	FAIL

Overall result for P-102080: FAIL

Part P-100107 rev C.1

Test	Requirement	Measured	Result
Thermal cycle	50 - 500 cycles	440.888	PASS
Salt spray	48 - 500 hours	251.356	PASS
Dimensional check	0.05 - 0.5 mm	0.334	PASS
Hardness	20 - 60 HRC	57.262	PASS

Overall result for P-100107: PASS