# TEST REPORT

**Document ID:** DOC-0000668
**Project:** PRJ-015
**Uploaded on:** 2023-09-11
**Uploaded by:** user120
**Export class:** EAR99

**Report No:** TR-769505
**Laboratory:** Lab South
**Test Date:** 2023-09-11

## Part P-100379 rev B.1

| Test | Requirement | Measured | Result |
|---|---|---|---|
| Flatness | 0.01 - 0.2 mm | 0.03 | PASS |
| Salt spray | 48 - 500 hours | 256.986 | PASS |
| Hardness | 20 - 60 HRC | 28.04 | PASS |
| Tensile strength | 250 - 520 MPa | 300.936 | PASS |

Overall result for P-100379: PASS